
Guidance on Controlling Corrosion in Drinking Water Distribution Systems

Federal-Provincial-Territorial Committee on Drinking Water
Federal-Provincial-Territorial Committee on Health and the Environment

Health Canada
Ottawa, Ontario

April 2008

This document may be cited as follows:

Health Canada (2008) Guidance on Controlling Corrosion in Drinking Water Distribution Systems. Water, Air and Climate Change Bureau, Healthy Environments and Consumer Safety Branch, Health Canada, Ottawa, Ontario.

The document was prepared by the Federal-Provincial-Territorial Committee on Drinking Water of the Federal-Provincial-Territorial Committee on Health and the Environment.

Any questions or comments on this document may be directed to:

Water, Air and Climate Change Bureau
Healthy Environments and Consumer Safety Branch
Health Canada
269 Laurier Avenue West, Address Locator 4903D
Ottawa, Ontario
Canada K1A 0K9

Tel.: 613-948-2566

Fax: 613-952-2574

E-mail: water_eau@hc-sc.gc.ca

Other documents concerning Canadian drinking water quality can be found on the following web page: <http://www.hc-sc.gc.ca/waterquality>.

Table of contents

Background on Guidance Documents	1
<u>Part A. Guidance on corrosion control</u>	2
A.1 Introduction and background	2
A.2 Corrosion control programs and protocols	3
A.2.1 Monitoring program for residential sites - option 1 (two tier protocol)	4
A.2.1.1 Tier 1 sampling protocol	5
A.2.1.2 Tier 2 sampling protocol	6
A.2.1.3 Follow-up sampling	6
A.2.2 Monitoring program for residential sites - option 2 (lead service line residences)	6
A.2.2.1 Sampling protocol	7
A.2.3 Frequency of sampling for residential monitoring	8
A.2.4 Number and selection of sites for residential monitoring	9
A.2.5 Monitoring program for non-residential sites (two tier protocol)	10
A.2.5.1 Tier 1 sampling protocol	11
A.2.5.2 Tier 2 sampling protocol	12
A.2.5.3 Selection of monitoring sites and monitoring frequency	13
A.3 Responsibilities	14
A.4 Sampling protocols and action levels for lead	16
A.4.1 Initial monitoring for residential sites-option 1 (two tier protocol)	16
A.4.2 Initial monitoring for residential sites-option 2 (lead service line residences) ..	16
A.4.3 Initial monitoring for non-residential sites-(two tier protocol)	17
<u>Part B. Supporting information</u>	18
B.1 Principles of corrosion in drinking water distribution systems	18
B.1.1 Main contaminants from corrosion of drinking water distribution systems	19
B.1.2 Sources of contaminants in distribution systems	19
B.1.2.1 Lead pipes, solders and fittings	19
B.1.2.2 Copper pipes and brass fittings	19
B.1.2.3 Iron pipes	20
B.1.2.4 Galvanized pipes	20
B.1.2.5 Cement pipes	20
B.1.2.6 Plastic pipes	20
B.2 Measuring corrosion	21
B.2.1 Levels of contaminants at the tap	21
B.2.2 Factors influencing levels of contaminants at the tap	24
B.2.2.1 Age of the plumbing system	24

B.2.2.2	Stagnation time of the water	25
B.2.2.3	pH	27
B.2.2.4	Alkalinity	30
B.2.2.5	Temperature	32
B.2.2.6	Calcium	33
B.2.2.7	Free chlorine residual	34
B.2.2.8	Chloramines	35
B.2.2.9	Chloride and sulphate	35
B.2.2.10	Natural organic matter	37
B.3	Methods for measuring corrosion	37
B.3.1	Corrosion indices	37
B.3.2	Coupons and pipe rig systems	38
B.3.3	Lead monitoring at the tap	39
B.4	Treatment/control measures for lead, copper and iron	39
B.4.1	Materials in drinking water distribution systems	40
B.4.2	Controlling pH and alkalinity	41
B.4.3	Corrosion inhibitors	42
B.4.3.1	Phosphate-based inhibitors	42
B.4.3.2	Silicate-based inhibitors	44
B.4.4	Flushing and maintenance	44
B.4.5	Drinking water treatment devices	45
B.5	Rationale for monitoring programs for assessing corrosion	47
B.5.2	Determination of sampling protocols and action level for residential monitoring program - option 1 (two tier)	48
B.5.2.1	Tier 1 sampling protocol	48
B.5.2.2	Tier 2 sampling protocol	51
B.5.3	Determination of sampling protocols and action levels for residential monitoring program-option 2 (lead service line residences)	52
B.5.3.1	Limitations	55
B.5.4	Determination of residential monitoring sites	56
B.5.5	Determination of sampling protocols and action levels for non-residential monitoring programs	57
B.5.5.1	Tier 1 sampling protocol	57
B.5.5.2	Tier 2 sampling protocol	59
B.5.6	Determination of non-residential monitoring sites	60
Part C.	Acronyms, tables and references	62
C.1	Acronyms	62
C.2	Guidance on determination of 90th percentile	63
C.3	Principal factors influencing the corrosion and leaching of lead, copper, iron and cement	64

C.4	Conditions favouring lead leaching and indicators of lead leaching in drinking water distribution and plumbing systems	65
C.4.1	At the treatment plant	65
C.4.2	Within the distribution system	66
C.4.3	Within the plumbing system	67
C.4.4	At the tap	67
C.5	Guidance on prioritizing residential monitoring sites	68
C.6	Plumbing profile determination	69
C.7	References	71

Guidance on Controlling Corrosion in Drinking Water Distribution Systems

Background on Guidance Documents

The main role of the Federal-Provincial-Territorial Committee on Drinking Water is the development of the Guidelines for Canadian Drinking Water Quality. This role has evolved over the years, and new methodologies and approaches have led the Committee to develop a new type of document, Guidance documents, to provide advice and guidance on issues related to drinking water quality for parameters that do not require a formal Guideline for Canadian Drinking Water Quality.

There are two instances when the Federal-Provincial-Territorial Committee on Drinking Water may choose to develop guidance documents. The first would be to provide operational or management guidance related to specific drinking water related issues (such as boil water advisories), in which case the documents would provide only limited scientific information or health risk assessment.

The second instance would be to make risk assessment information available when a guideline is not deemed necessary. The Federal-Provincial-Territorial Committee on Drinking Water establishes the Guidelines for Canadian Drinking Water Quality specifically for contaminants that meet all of the following criteria:

1. exposure to the contaminant could lead to adverse health effects;
2. the contaminant is frequently detected or could be expected to be found in a large number of drinking water supplies throughout Canada; and
3. the contaminant is detected, or could be expected to be detected, at a level that is of possible health significance.

If a contaminant of interest does not meet all these criteria, the Federal-Provincial-Territorial Committee on Drinking Water may choose not to develop a Guideline Technical Document. In that case, a guidance document may be developed.

Guidance documents undergo a similar process as Guideline Technical Documents, including public consultations through the Health Canada web site. They are offered as information for drinking water authorities, and to help provide guidance in spill or other emergency situations.

Part A of this document provides the guidance for controlling corrosion in distribution systems; Part B provides the scientific and technical information to support this guidance; and Part C provides the tools and information required to develop specific corrosion control programs and activities.

Part A. Guidance on corrosion control

A.1 Introduction and background

Corrosion is a common issue in Canadian drinking water supplies. Corrosion is the deterioration of a material, usually a metal, that results from a reaction with its environment. In drinking water distribution systems, materials that could be affected by corrosion and leach increased amounts of contaminants include metal pipes and fittings, cement in pipe linings and polyvinyl chloride (PVC) pipes. Corrosion in drinking water distribution systems can be caused by several factors, including the type of materials used, the age of the piping and fittings, the stagnation time of the water and the water quality in the system, including its pH. The most influential properties of drinking water when it comes to the corrosion and leaching of distribution system materials are pH and alkalinity. Other drinking water quality parameters of interest are temperature, calcium, free chlorine residual, chloramines, chloride, sulphate and natural organic matter (NOM). Any change to the drinking water treatment process may impact corrosion in the distribution system, including in household plumbing.

In this document, “corrosion control” refers to the action of controlling the leaching of metals, specifically lead, that results from the corrosion of materials in drinking water distribution systems. Although corrosion itself cannot readily be measured by any single, reliable method, the levels of lead at a consumer’s tap can be used as an indication of corrosion. Monitoring of lead levels at the tap can help identify sources of lead and aid in the selection of strategies to effectively control corrosion and reduce levels of lead at the tap.

The intent of this document is to provide responsible authorities such as municipalities and water suppliers with guidance on assessing corrosion and implementing corrosion control for distribution systems in residential settings. It also provides sampling protocols and corrective measures for non-residential buildings for authorities, such as school boards, building owners or employers, that are responsible for the health and safety of the occupants of non-residential buildings including schools, day cares and office buildings. This document outlines the steps that should be taken to reduce population exposure to lead, which may also reduce the consumer’s exposure to other contaminants. Concerns related to other contaminants whose concentrations may be affected by corrosion, such as copper and iron, are also briefly discussed. This guidance is meant to complement the information provided in the Technical Documents of the Guidelines for Canadian Drinking Water Quality for the respective parameters. Microbiologically-influenced corrosion is beyond the scope of this document.

There are no direct health effects linked to corrosion in distribution systems. However, corrosion may cause the leaching of contaminants that would be a concern for the health of Canadians. The main contaminant of concern is lead, which is used as the trigger to initiate corrosion control programs. The current drinking water guideline for lead, which was established in 1992 based on health effects in children, is a Maximum Acceptable Concentration of 0.010 mg/L. Other contaminants that can be leached as a consequence of corrosion in drinking water distribution systems include copper and iron. The drinking water guidelines for copper and iron are based on aesthetic considerations such as colour and taste. The guideline for copper is an aesthetic objective of ≤ 1.0 mg/L. Copper is generally considered to be non-toxic except at high doses, in excess of 15 mg/day, although gastrointestinal irritation has been observed at oral doses

of 5.3 mg/day. The guideline for iron is an aesthetic objective of ≤ 0.3 mg/L in drinking water. Both copper and iron are considered to be essential nutrients in humans.

Although the protocols described in this document represent the best approach to address corrosion in drinking water distribution systems, based on currently available science and monitoring data, they may not be practical or feasible in all systems. In such cases, a scaled down version of this approach may provide some improvement in health protection and water quality.

A.2 Corrosion control programs and protocols

Any size and type of drinking water distribution system can be subject to corrosion, therefore it is important for responsible authorities to conduct a monitoring program to assess if and to what degree corrosion may be occurring in a system and to take corrective measures when needed. The steps that need to be taken in a corrosion control program for a drinking water system are based on the levels of specific contaminants at the consumer's tap. Although corrosion will affect the leaching of several contaminants, the primary focus should be lead, since it is the contaminant whose presence is most likely to result in adverse health effects.

The first step in implementing a corrosion control program is to conduct monitoring of levels of lead at consumers' taps. Conducting monitoring of lead at the tap provides responsible authorities with information on the corrosiveness of the water towards lead. Given that a major source of metals in drinking water is related to corrosion in distribution and plumbing systems, measuring the contaminant at the tap is the best tool to assess corrosion and reflect population exposure. A monitoring program also provides the information that is needed to determine the corrective measures that should be taken when elevated concentrations of lead are observed in the system as well as information on the level of monitoring that should be conducted in the future. Water quality monitoring for parameters such as pH and alkalinity are essential to assess both corrosion issues and the best corrective measures to undertake. It will also help determine the effectiveness of a corrosion control program.

If monitoring done as part of a corrosion control program shows lead concentrations in excess of the specified action levels, then any or several of the suggested corrective measures should be taken, after which the effectiveness of the corrective measure(s) should be determined by appropriate monitoring. This is important to ensure the corrosion control program is optimized to minimize lead concentrations and reduce exposure to lead and other materials.

When monitoring for lead as part of a corrosion control program, there are 2 different situations and exposure patterns to be addressed, residential and non-residential settings. In a residential setting, which includes any type of residential dwelling, such as single-family homes and multiple-family dwellings, monitoring will seek to assess lead concentrations across the system and to identify sources of lead in both the distribution system and the residential plumbing. The purpose of the residential monitoring programs is generally to identify and diagnose systems in which corrosion is an issue and to determine the best corrective measures to take when needed. Depending on the program selected, it may also be used to assess the effectiveness of a system-wide corrosion control program and determine if treatment has been optimized.

For non-residential sites and buildings, which include child care centres and schools, monitoring will focus primarily on the source of lead within the plumbing system in the building. The purpose of the non-residential monitoring program is to locate specific lead problems and identify where and how to proceed with remedial actions. Given that the goal of

the residential and non-residential sampling protocols are different, the number of samples and sampling frequency will differ for these two types of settings.

The implementation of corrosion control programs is intended to minimize leaching from distribution system materials to protect the health of consumers. Additional benefits include extended pipe life, reduced leakage and decreased plumbing repairs and replacements. It is generally expected that the costs of implementing corrosion control would both protect human health and extend the life of distribution system materials.

Utilities should ensure that changes made to treatment processes do not make the water corrosive towards lead. Although it is recognized that a utility's responsibility does not generally include residential plumbing systems, most of the established guidelines are designed to apply at the consumer's tap. As such, corrosion control programs need to ensure that the delivered water is not aggressive for all components of the distribution system, including the plumbing system.

In this document, the term "distribution system" will be used more broadly, to include both the system of conduits by which a public water supply is distributed to its consumers, as well as the pipes, fittings and other apparatus within and adjacent to a building or home for bringing in the water supply. Corrosion control programs will vary depending on the responsible authority, ranging from extensive system-wide programs implemented by the water supplier to localized programs implemented by a building owner to ensure a safe and healthy environment for the occupants of non-residential buildings.

A.2.1 Monitoring program for residential sites - option 1 (two tier protocol)

The first option provided, for sampling at residential sites, is a two-tier approach for assessing corrosion of a variety of leaded material in residential distribution systems. This protocol is based on sampling after a period of stagnation of at least six hours. The first tier sampling provides an indication of lead concentrations throughout the system and the need to take action to control corrosion and reduce exposure to lead. Once a corrosion control program has been put in place, it also provides the appropriate data to assess if corrective measures have been effective in reducing corrosion of different types of lead containing material throughout the system. When more than 10% of sites* exceed a lead concentration of 0.015 mg/L (lead action level), then Tier 2 sampling should be conducted.

Tier 2 sampling is conducted at a reduced number of sites from Tier 1 and will provide more detailed information on the concentrations of lead contributed from different lead containing material in the distribution system (lead profile). This will enable responsible authorities to determine the source and potentially highest levels of lead so that the best corrective measures can be selected and corrosion control can be optimized.

In some cases, the responsible authority may wish to collect samples for both tiers during the same site visit. This step eliminates the need to return to the residence if the action level for Tier 1 is not met. The analysis for the second tier are then done only on the appropriate samples, based on the results of the Tier 1 samples.

A.2.1.1 Tier 1 sampling protocol

The first tier sampling determines the contribution of lead at the consumer's tap from the internal plumbing following a period of stagnation and from the transitory contact with the lead

* Based on the 90th percentile value as determined in Appendix C2.

service line. A period of stagnation of a minimum of six hours increases the likelihood that the concentrations of lead in the first litre of water are close to a maximum value so that systems that should be implementing corrective measures are being accurately detected. For systems in which lead service lines (LSLs) are present, a minimum of 50% of the sampling sites should target LSL residences.

A first-draw 1-L sample is taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been stagnant for a minimum of six hours. When more than 10% of the sites* have a lead concentration greater than 0.015 mg/L (lead action level), it is recommended that utilities take the following measures:

1. Initiate a public education program to encourage consumers to flush the water after a period of stagnation while appropriate corrective measures are being assessed or undertaken. Flushing should be conducted so that any water that has been in contact with lead present in faucets, fittings and the associated solders as well as the lead service line following a period of stagnation is removed.
2. Conduct additional sampling (as outlined in the Tier 2 sampling protocol) at 10% of the sites sampled in Tier 1 at which the highest lead concentrations (above 0.015 mg/L) were observed.
3. Communicate results of the testing and inform customers of the appropriate measures they can take to reduce exposure to lead. Corrective measures that consumers can take may include any or a combination of the following:
 - flushing the system;
 - replacing their portion of the lead service line;
 - replacing brass fittings or in-line devices; and/or
 - using certified drinking water treatment devices.
4. Implement appropriate corrective measures to control corrosion in the system. Results of the Tier 2 sampling should be used to help determine the best corrective measure(s) for the system which may include any or a combination of the following:
 - replacing lead service lines;
 - adjusting the pH and alkalinity;
 - adjusting the pH and adding corrosion inhibitors; and/or
 - replacing brass fittings or in-line devices.
5. Encourage homeowners to periodically clean debris from the screens or aerators of drinking water outlets. Where a substantial amount of debris was removed from the aerator or screen, authorities may want to re-test the water from these outlets following this same protocol. If results of the re-testing show lead concentrations below 0.015 mg/L, utilities should investigate if particulate lead may be contributing significantly to elevated lead levels and if regular cleaning of the aerator or screen is an appropriate corrective measure.

In cases where less than 10% of sites have lead concentrations above 0.015 mg/L, utilities should provide consumers in residences with a lead concentration above 0.010 mg/L information on methods to reduce exposure to lead such as those listed above in measure #3. It is also recommended that utilities conduct follow-up sampling for these sites to assess the effectiveness of the corrective measures undertaken by the consumer.

* Based on the 90th percentile value as determined in Appendix C2

A.2.1.2 Tier 2 sampling protocol

Tier 2 sampling is only required when the Tier 1 sampling identified more than 10% of sites with lead concentrations above 0.015 mg/L. Sampling is conducted at 10 % of the sites sampled in Tier 1, specifically the sites in which the highest lead concentrations were measured. For smaller systems (i.e., serving 500 people or less), a minimum of 2 sites should be sampled to provide sufficient lead profile data for the system.

Four consecutive 1-L samples are taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been stagnant for a minimum of six hours. Each 1-L sample is analysed individually to obtain a profile of lead contributions from the faucet, plumbing (lead in solder, brass and bronze fittings, brass water meters, etc.) and the lead service line. Alternatively, utilities that choose to collect four 1-L samples during the site visits for Tier 1 sampling can proceed with analysis of the remaining three 1-L samples once the analysis of the first Tier 1 sample identifies the appropriate residences (i.e., those with the highest lead concentrations).

A.2.1.3 Follow-up sampling

Monitoring data collected over time can be used by utilities to assess the effectiveness of corrosion control and optimize their programs. The frequency and duration of follow-up sampling will depend on the type of corrosion control measures selected. General guidance for the frequency and duration of monitoring for different corrective measures can be found in section A.2.3. Follow-up sampling that is intended to demonstrate that lead concentrations throughout the system have been adequately reduced and that corrosion control has been optimized should be conducted for a minimum of two consecutive sampling rounds. Depending on the most significant source of lead in a system, utilities may need to supplement follow-up Tier 1 sampling with Tier 2 sampling to assess if corrosion control has been optimized. Comparison of the highest lead levels in the system before and after corrosion control is implemented is the best approach for accurately quantifying the effects of corrosion control treatment on reducing lead levels and for demonstrating optimization. Once it has been determined that corrosion control is optimized, annual monitoring can be resumed.

A.2.2 Monitoring program for residential sites - option 2 (lead service line residences)

For jurisdictions in which sampling after a 6-hour stagnation time is not practical and/or regulatory obligations restrict the use of the two tier approach, an alternate sampling protocol is provided.

This sampling protocol provides an indication of the lead concentrations that are representative of residences that have lead service lines (LSLs) and the need to take action to control corrosion and reduce exposure to lead. It is important to note that there are significant limitations to the use of this sampling protocol, since there are limited scientific data available to evaluate its effectiveness for assessing system-wide corrosion and for optimizing corrosion control. The focus of this sampling protocol is to evaluate corrosion at residences with lead service lines. The number of residences to be monitored are the same as for option 1 and are described at the end of this section.

In order to increase the likelihood that systems that would benefit from a corrosion control program are accurately identified, this protocol should incorporate the practice of sampling after a 6-hour stagnation. A subset of 6 hour stagnation samples should be taken before

and after corrosion control measures to conduct an assessment of corrosion control efficacy and optimization.

A.2.2.1 *Sampling protocol*

This sampling protocol measures the concentration of lead in water that has been in contact for a transitory and short period of time (30 minutes) with the lead service line as well as with the interior plumbing (e.g., lead solder, leaded brass fittings, etc.). Four consecutive 1-L samples are taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been fully flushed for 5 minutes and the water has then been left to stagnate for 30 minutes. Each 1-L sample is analysed individually to obtain a profile of lead contributions from the faucet, plumbing and a portion or all of the lead service line. If the average lead concentration from the four samples taken at each site is greater than 0.010 mg/L at more than 10% of the sites** during one monitoring event (lead action level), it is recommended that utilities take the following measures:

1. Initiate a public education program to encourage consumers to flush the water after a period of water stagnation while appropriate corrective measures are being assessed or undertaken. Flushing should be conducted so that any water that has been in contact with lead present in faucets, fittings and the associated solders as well as the lead service line following a period of stagnation is removed.
2. Conduct additional sampling following the Tier 2 protocol (6-hr stagnation samples) outlined above (in section A.2.1.2) from homes already identified for the 30 minute stagnation period. This sampling should occur before and after corrosion control measures are implemented to better determine the efficacy of the corrosion control program.
3. Communicate results of the testing and inform customers of the appropriate measures they can take to reduce exposure to lead. Corrective measures that consumers can take may include any or a combination of the following:
 - flushing the system;
 - replacing their portion of the lead service line;
 - replacing brass fittings or in-line devices; and/or
 - using certified drinking water treatment devices.
4. Implement appropriate corrective measures to control corrosion in the system. Analysis of individual 1-L samples will help provide information on the source of lead in the system, however, if the source of the lead problem cannot be identified by the lead profile in the four 1-L samples, further investigation may be required. Depending on the source of the lead problem and on the number of residences affected, corrective measures may include any or a combination of the following:
 - replacing lead service lines;
 - adjusting the pH and alkalinity;
 - adjusting the pH and adding corrosion inhibitors; and/or
 - replacing brass fittings or in-line devices.
5. Encourage homeowners to periodically clean debris from the screens or aerators of drinking water outlets. Where a substantial amount of debris was removed from the aerator or screen, authorities may want to re-test the water from these outlets following

**Based on the 90th percentile value as determined in Appendix C2.

this same protocol. If results of the re-testing show lead concentrations below 0.010 mg/L, utilities should investigate if particulate lead may be contributing significantly to elevated lead levels and if regular cleaning of the aerator or screen is an appropriate corrective measure.

In cases where less than 10% of sites have average lead concentrations above 0.010 mg/L, utilities should provide consumers in residences with an individual sample concentration above 0.010 mg/L of lead, information on methods to reduce exposure to lead such as those listed above in measure #3. It is also recommended that utilities conduct follow-up sampling for these sites to assess the effectiveness of the corrective measures undertaken by the consumer.

This sampling protocol requires the collection of four 1-L samples to determine if contributions from the interior plumbing and lead service line are resulting in elevated lead concentrations. Given the high variability in lead concentrations, particularly during short stagnation times, this protocol is expected to underestimate the highest levels of lead at the tap. Although using a 30-minute stagnation will provide an indication of the effectiveness of a corrosion control program, it is not as reliable as a 6-hour stagnation period. As a result, it should not be used to evaluate whether a system-wide corrosion control program is optimized.

A.2.3 Frequency of sampling for residential monitoring

Lead levels should be monitored at the tap at least once a year to assess if corrosion is occurring in a water distribution system. When implementing a corrosion control program, the frequency of monitoring will increase, depending on the control measures selected, and this increased monitoring must be maintained until the control measures are optimized. Because lead corrosion and lead levels are easily influenced by small changes in the quality of the water distributed, annual sampling for lead should continue even when corrosion control has been optimized. Monitoring is also recommended when changes in the water quality in the distribution system are noted (i.e., nitrification) or when there are changes made to the treatment process which would alter water quality parameters affecting corrosion, such as pH and alkalinity, including changes in the disinfectant or the coagulant. Under certain circumstances, additional sampling may be required when localized changes in the distribution and/or plumbing systems are made.

When pH and alkalinity adjustments or pH adjustment and corrosion inhibitors are used as system-wide corrosion control methods, the water quality should be monitored at least weekly at the entry point to the distribution system and monthly within the distribution system, including at the tap. At a minimum, water quality parameters such as pH, alkalinity, lead and corrosion inhibitor residuals (where applicable) should be monitored for at least 6 months for pH and alkalinity adjustment and for 18 months when pH adjustment and corrosion inhibitors are used. During the implementation stage, copper, iron and disinfectant residuals should also be monitored within the distribution system. When replacing lead service lines (LSL), especially when there is only partial LSL replacement, extensive initial flushing by the consumer should be encouraged and weekly or bi-weekly sampling should be conducted until lead levels stabilize. Once it has been determined that corrosion control is optimized, annual monitoring can be resumed.

Routine annual sampling should be conducted during the same period every year, since lead leaching as well as the leaching of other materials within the distribution system are influenced by changes in temperature as well as seasonal variations. The warmer season from

May to October is chosen both for practical purposes in Canada and because levels of lead are expected to be highest in those months.

A.2.4 Number and selection of sites for residential monitoring

The number of residences to be monitored is determined based on the size of the drinking water system, and are outlined in Table 1. The suggested number of monitoring sites is considered to be the minimum required to characterize the distribution of lead levels in a system. The number of sites was determined by the U.S. EPA by conducting a statistical analysis of data from system-wide studies of lead concentrations at the tap. The U.S. EPA used statistical methods to estimate the number of samples that need to be taken from a group to accurately represent the group as a whole. Based on this evaluation, sampling the suggested number of sites will provide a 90% confidence level that all systems which serve more than 100 people and have lead concentrations exceeding 0.015 mg/L after a six hour stagnation period will be correctly identified (U.S. EPA, 1991b). To increase the confidence level, monitoring twice a year and targeting high-risk residences should be done. This is particularly important for systems serving 100 people or less.

It should be noted that the U.S. EPA evaluation was conducted using data collected using a first draw (6-hour stagnation) one litre sampling protocol and an action level of 0.015 mg/L. Data using a 30 minute stagnation period and an action level of 0.010 mg/L were not evaluated in this context. Therefore, the confidence level that systems with lead concentrations above 0.010 mg/L will be accurately detected using this protocol is not known and cannot be reliably estimated without doing a similar analysis with a much larger data set than is currently available.

High-risk residences should be chosen as sampling sites to reflect potential lead problems in the community and to adequately reduce population exposure to lead. Monitoring sites should be determined based on the selected sampling protocol. It must be noted that in some cases further investigation may be required to identify the lead problem. This additional investigation could include the collection of several 1-L sequential samples to more accurately identify the lead profile of a residence.

When using option 1 of the residential monitoring programs (6 hour stagnation samples as described in section A.2.1), monitoring sites should be selected based on the presence of leaded materials in the distribution system and/or residential plumbing. Sites should be chosen to include: (1) at least 50% of sites with lead service lines (for systems where lead service lines are present); (2) locations that contain copper pipes with lead solders or lead pipes; and (3) locations with lead-containing brass fittings or in-line devices. For option 2 of the residential monitoring programs (30 minute stagnation samples: Section A.2.2), only sites where lead service lines are present should be targeted.

Where possible, responsible authorities should develop an inventory of monitoring sites where leaded material is likely to be present. Historical records such as plumbing codes, building permits, and water meter records may provide utilities with useful information on the materials used during certain time periods or in certain areas of the distribution system which can be used to identify potential monitoring sites. It is recognized that historical information may be limited and/or incorrect and utilities may need to assess the sampling results to determine if additional monitoring sites are needed to ensure that the system has been adequately assessed. It is also recognized that where contaminant levels are highly variable — as with lead — it is impossible to design a selective monitoring protocol that will reflect with complete confidence the levels throughout the entire system.

Table 1: Suggested minimum number of monitoring sites^a

System size (number of people served)	Number of sites (annual monitoring)	Number of sites (reduced annual monitoring)
>100 000	100	50
10 001–100 000	60	30
3301–10 000	40	20
501–3300	20	10
101–500	10	5
≤100	5	5

^a Adapted from U.S. EPA (1991a).

Table 1 provides the suggested number of reduced monitoring sites that should continue to be monitored annually once the corrosion control program has been optimized. For smaller systems a reduced number of monitoring sites is not possible since a minimum number of sites is required to adequately characterize lead concentrations in the system. If at any time a system does not meet the action levels outlined in section A.2.1 or A.2.2 in a reduced annual monitoring program, corrective measures should be re-evaluated and the appropriate action should be taken. Subsequent sampling should be conducted at the number of sites used for annual monitoring until a minimum of two monitoring events demonstrates that corrosion control has been effective.

In cases where utilities have already been conducting lead sampling and/or implementing corrosion control measures, the option of a reduced number of sites should only be undertaken when the criteria for the protocol are met for a minimum of two consecutive periods of testing, based on either a 6-hour or 30-minute stagnation sampling protocol.

A.2.5 Monitoring program for non-residential sites (two tier protocol)

The purpose of the sampling protocols for non-residential sites such as child care centres, schools and office buildings is to locate specific lead problems within the building and identify where and how to proceed with remedial measures to protect the occupants from lead exposure. The levels of lead in drinking water will vary from one non-residential site to the next as well as between outlets within the same building, because of the variation in the stagnation periods, the materials used within the plumbing system and the variable use patterns in these buildings.

A sampling plan should be developed to take into consideration the type of building being sampled and to target priority sites for sampling. A plumbing profile of the building is recommended to identify potential sources of lead and areas of stagnation, and to assess the potential for lead contamination at each drinking water fountain, cold drinking water or cooking outlet. A list of questions to help authorities determine the plumbing profile can be found in Appendix C.6. Information in the plumbing profile can then be used to identify and prioritize

outlets that should be included in a sampling plan that is appropriate for the type of building that is being sampled.

Stagnation periods will be influenced by such things as the frequency of use of the outlet, whether bottled water is distributed in the buildings, whether the building is occupied 24 or 8 hours per day and the number of occupants. As such, establishing the source of the problem within a specific building becomes a critical tool in assessing which measures to take to reduce lead exposure. The locations of specific lead problems are determined by measuring lead levels at water fountains and cold drinking water outlets. When elevated concentrations of lead occur at an outlet, it can be from lead containing material within the outlet itself (e.g., faucet, bubbler, water cooler), from the plumbing upstream of the outlet, or from the water entering the building. A two-tier sampling approach is used to identify the source of the elevated lead.

Since elevated concentrations of lead can be found in drinking water as a result of leaching from plumbing materials including fittings and fixtures within a building, this protocol should be followed by responsible authorities such as building owners or managers, school boards and employers as part of the overall management of the health and safety of the occupants of schools, child care centres, and non-residential buildings. This protocol may also be followed by utilities who want to include non-residential buildings such as schools in their corrosion control monitoring programs. The extent of sampling conducted by an individual responsibility authority within a building may vary depending on the objective of the sampling and the authority conducting the sampling.

In some cases, responsible authorities may want to collect samples from Tiers 1 and 2 during the same sampling period. This approach may be convenient and cost effective, however, it should be recognized that depending on the plumbing configuration this may decrease the level of confidence in the subsequent flushed samples collected in the building during the same sampling period. As a result, it may be more difficult to pinpoint the source of lead within the building.

A.2.5.1 Tier 1 sampling protocol

The objective of Tier 1 sampling is to identify specific cold drinking water outlets that have elevated levels of lead following periods of stagnation. Collection of a smaller sample volume helps to pinpoint if the source of lead is from the specific outlet and helps to direct the appropriate corrective measures. Tier 1 sampling should be conducted at the locations identified in the sampling plan for the non-residential building. In addition, a sample that is representative of the water that is entering the building (water main sample) should be collected at each monitoring event. Water main samples should be collected from a drinking water faucet in close proximity to the service line following a period of approximately 5 minutes of flushing (longer flushing may be necessary to ensure the sample is representative of water that has been flowing in the main). All other samples in the building should be collected using the protocol described below.

A first-draw 250-mL sample is taken at the locations identified in the sampling plan after the water has been stagnant for a minimum of 8 hours but generally not more than 24 hours. To ensure that representative samples are collected, the aerator or screen on the outlet should not be removed prior to sampling. If the lead concentration is equal to or exceeds 0.020 mg/L (lead action level) at any of the monitoring locations, the following measures should be taken:

-
- conduct additional sampling at the outlets that exceed lead concentrations of 0.020 mg/L to determine the source of lead as outlined in the Tier 2 protocol.
 - implement interim corrective measures immediately to reduce the exposure of occupants to lead in first draw water. These may include cleaning debris from the screens or aerators of the outlet, flushing the plumbing system following periods of stagnation, taking the outlet out of service, use of certified drinking water treatment devices or supplying an alternate water supply;
 - educate the occupants (e.g., teachers, daycare providers, students) of the building and other interested parties (e.g., parents, occupational health and safety committees) on the sampling results and the interim measures that are being taken as well as the plans for additional sampling;
 - where a substantial amount of debris was removed from the aerator or screen, authorities may want to re-test the water from these outlets following this same protocol. If results of the re-testing show lead concentrations below 0.020 mg/L, authorities should investigate if particulate lead may be contributing significantly to elevated lead levels and if regular cleaning of the aerator or screen should be implemented as part of the maintenance or flushing program.

A.2.5.2 *Tier 2 sampling protocol*

Tier 2 sampling is used in combination with results from Tier 1, to determine the source of the lead in the plumbing within the building. Sampling after a short period of flushing (30 seconds) will determine the concentration of lead in the water that has been stagnant in the plumbing upstream of the outlet.

At those water fountains and cold drinking water outlets that exceeded concentrations of 0.020 mg/L for Tier 1, a second 250- mL flushed sample is taken after the water has been stagnant for a minimum of 8 hours (but generally not more than 24 hours) and then flushed for 30 seconds. When the lead concentration in any of these second samples is equal to or exceeds 0.020 mg/L (lead action level), corrective measures should be taken immediately. Corrective measures can include interim measures, such as routine flushing of the outlet before the facility opens (a minimum of 5 minutes to obtain water from the water main), removing the outlet from service, use of certified drinking water treatment devices or providing an alternate water supply, that are put in place until a permanent solution can be implemented. In addition, depending on the results of the Tier 1 and 2 sampling, one or a combination of the following corrosion control measures should be initiated:

- educate the occupants of the building (e.g., teachers, daycare providers, students) and other interested parties (e.g., parents, occupational health and safety committees) on the sampling results and the interim and long-term corrective measures that are being taken;
- compare the Tier 1 and Tier 2 sampling results to determine if the source of the lead contamination is originating from the fitting or fixture or the internal plumbing; if the results of the Tier 1 and Tier 2 sampling both indicate lead contamination, conduct additional sampling from the interior plumbing within the building to further determine the source(s) of lead contamination;
- flush the outlet(s);
- replace the outlet(s), fountain(s) or pipes;
- remove the outlet from service;

-
- replace leaded brass fittings or in-line components;
 - work collaboratively with the water supplier to ensure that the water delivered to the building is not aggressive;
 - install drinking water treatment devices; and/or
 - distribute an alternate water supply.

A.2.5.3 *Selection of monitoring sites and monitoring frequency*

The number of sites sampled in a building may vary depending on the objective of the sampling, the responsible authority conducting the sampling and the type of occupants within the building. Where schools and day care facilities and other non-residential buildings fall under the responsibility of utilities, the priority for sampling should be schools and child care facilities. Other authorities that are responsible for maintaining and monitoring the water quality within non-residential buildings will need to do more extensive sampling at individual outlets based on the sampling plan developed for the building. The sampling plan should prioritize drinking water fountains and cold water outlets used for drinking or cooking based on information obtained in the plumbing profile, including areas with leaded solder or brass fittings containing lead, areas of stagnation, areas serviced by lead pipe, and areas that provide water to high-risk populations, such as infants, children and pregnant women.

Utilities, building owners and other responsible authorities (e.g., school boards) should work collaboratively to ensure that sampling programs are designed to be protective of the health of the occupants, including high risk populations such as young children and pregnant women. It must be noted that large variations in lead concentrations can be expected to be found between individual outlets in a building and that sampling programs should be carefully designed and implemented so that outlets with potentially elevated levels of lead are correctly identified.

When outlets with elevated lead concentrations have been identified, corrective measures should be implemented. Depending on the type of corrective measure selected (i.e., replacement of outlets, routine flushing, etc.) additional sampling should be conducted to ensure that the lead levels have been effectively reduced. When routine flushing programs are implemented as a corrective measure, sampling should be conducted so that it can be demonstrated that flushing is effective at reducing lead concentrations throughout the period of the day that the building is occupied. Similarly, when outlets are replaced sampling should be conducted up to three months following replacement to ensure that lead levels have been adequately lowered.

Once appropriate corrective measures are in place, subsequent sampling should be conducted at the sites used for initial monitoring, until a minimum of two monitoring events demonstrates that the corrosion control program is effective. Once sampling has been completed at all sites identified in the sampling plan of a non-residential building, and a corrosion control program is implemented effectively, only priority (high-risk) sites need to be monitored annually. Localized changes in the distribution system such as changes in the piping, faucets, or fittings used as a result of repairs or new construction as well as changes in water use patterns should also trigger additional monitoring.

It is also recommended that at each monitoring event, samples be taken from an outlet close to the point where the water enters the non-residential building, to determine the level of lead in the water contributed by either the service line or the main water distribution system (water main). Ideally, samples should be collected after an appropriate period of flushing so that they are representative of water from the service line and from the water main. The volume of

water to flush will depend on the characteristics of the building plumbing system (i.e., the distance between the service line and the water main).

Schools and Child Care Facilities

The sampling plan for schools, private schools and child care centres/providers should take into consideration that the types of occupants in these buildings are among the most susceptible to adverse health effects from lead. Consequently, sampling plans for these facilities should prioritize every drinking water fountain and cold water outlet used for drinking or cooking where lead contamination is possible and sample these in the first year. Other sampling sites such as outlets in classrooms that are used infrequently for drinking or first-aid rooms that are not identified as priority sites could then be sampled in subsequent years so that ultimately all sites identified in the sampling plan have been tested within a five to seven year period.

Other Non-residential Buildings

Every priority site identified in the sampling plan should be sampled in the first year. The remaining sites in the plan should then be sampled in subsequent years so that ultimately all sites identified in the sampling plan have been tested within a five to seven year period.


A.3 Responsibilities

Responsibility for the quality of drinking water is shared by all levels of government. The federal government's role is primarily one of science and research, including the development of guidelines for drinking water and providing scientific and technical expertise to the provincial and territorial governments. Provincial and territorial governments are generally in charge of regulating drinking water systems, including setting quality standards and managing source waters, treatment plants and distribution systems. Municipalities are usually responsible for the actual treatment and distribution of drinking water to the public, except private home owners who draw drinking water from a source on their property. Because of the complexity of water issues, effective collaboration is key to maintaining drinking water quality.

The key to ensuring safe and reliable drinking water from the source all the way to the consumer's tap (source-to-tap) is the use of a multi-barrier approach which includes monitoring of the water quality in the distribution system and at the consumer's tap and when necessary implementing a corrosion control program. The responsibility of the water quality at the consumer's tap may vary by jurisdiction and may ultimately be a shared responsibility between parties such as the water utility, building owners, water managers, and residential homeowners. Although it is recognized that a utility's responsibility may not include the building or household plumbing system, it is expected to ensure that the delivered water is not aggressive to the distribution system as a whole, including the internal distribution system. Utilities should include sampling locations within non-residential buildings such as child care centres or schools, in their lead sampling program, to ensure that the delivered water is not aggressive to these types of facilities. Nevertheless, buildings supplied with a non-corrosive water may have high lead levels at outlets due to factors such as materials used in the plumbing system and water use patterns which should be addressed by authorities such as the building owner or school board. This document is intended to provide information on the technical considerations of corrosion, sampling protocols, lead action levels and control methods to minimize corrosion.


A.4 Sampling protocols and action levels for lead

A.4.1 Initial monitoring for residential sites- option 1 (two tier protocol)




* Defined as 90th percentile

A.4.2 Initial monitoring for residential sites- option 2 (lead service line residences)



* Defined as 90th percentile

A.4.3 Initial monitoring for non-residential sites- (two tier protocol)



Part B. Supporting information

B.1 Principles of corrosion in drinking water distribution systems


Exposure to contaminants resulting from the internal corrosion of drinking water systems can be the result of corrosion in either the distribution system or the plumbing system, or both. The degree to which corrosion is controlled, for a contaminant in a system, can be assessed adequately by measuring the contaminant at the tap over time and correlating its concentrations with corrosion control activities.

Corrosion is defined as “the deterioration of a material, usually a metal, that results from a reaction with its environment” (NACE International, 2000). In drinking water distribution systems, the material may be, for example, a metal pipe or fitting, the cement in a pipe lining or a polyvinyl chloride (PVC) pipe.

This document focuses primarily on the corrosion and leaching of lead-, copper- and iron-based materials. It also briefly addresses the leaching from PVC and cement pipes, but does not include microbiologically influenced corrosion.

The corrosion of metallic materials is electrochemical in nature and is defined as the “destruction of a metal by electron transfer reactions” (Snoeyink and Wagner, 1996). For this type of corrosion to occur, all four components of an electrochemical cell must be present: 1) an anode, 2) a cathode, 3) a connection between the anode and the cathode for electron transport and 4) an electrolyte solution that will conduct ions between the anode and the cathode. In the internal corrosion of drinking water distribution systems, the anode and the cathode are sites of different electrochemical potential on the metal surface, the electrical connection is the metal and the electrolyte is the water.

The key reaction in corrosion is the oxidation or anodic dissolution of the metal to produce metal ions and electrons:



where:

- M is the metal
- e is an electron
- n is the valence and the corresponding number of electrons.

In order for this anodic reaction to proceed, a second reaction must take place that uses the electrons produced. The most common electron acceptors in drinking water are dissolved oxygen and aqueous chlorine species.

The ions formed in the reaction above may be released into drinking water as corrosion products or may react with components present in the drinking water to form a scale on the surface of the pipe. The scale that forms on the surface of the metal may range from highly soluble and friable to adherent and protective. Protective scales are usually created when the metal cation combines with a hydroxide, oxide, carbonate, phosphate or silicate to form a precipitate.

The concentration of a specific metal in drinking water is determined by the corrosion rate and by the dissolution and precipitation properties of the scale formed. Initially, with bare metal, the corrosion rate far exceeds the dissolution rate, so a corrosion product layer builds over the metal’s surface. As this layer tends to stifle corrosion, the corrosion rate drops towards the dissolution rate (Snoeyink and Wagner, 1996).

B.1.1 Main contaminants from corrosion of drinking water distribution systems

The materials present in the distribution system determine which contaminants are most likely to be found at the tap. The principal contaminants of concern that can leach from materials in drinking water distribution systems are aluminum, antimony, arsenic, bismuth, cadmium, copper, iron, lead, nickel, organolead, organotin, selenium, tin, vinyl chloride and zinc. It is important to assess whether these contaminants will be present in concentrations that exceed levels considered safe for human consumption.

B.1.2 Sources of contaminants in distribution systems

In Canada, copper plumbing with lead–tin solders (widely used until 1989) and brass faucets and fittings are predominant in domestic plumbing systems (Churchill et al., 2000).

Cast iron and ductile iron pipes account for more than two thirds of the existing water mains in use across Canada (InfraGuide, 2001). In new installations, PVC pipes often replace copper tubing, lead service lines and/or distribution pipes. Cement-based materials are also commonly used to convey water in large-diameter pipes.

B.1.2.1 Lead pipes, solders and fittings

Lead may leach into potable water from lead pipes in old water mains, lead service lines, lead in pipe jointing compounds and soldered joints, lead in brass and bronze plumbing fittings, and lead in goosenecks, valve parts or gaskets used in water treatment plants or distribution mains. Lead was a common component of distribution systems for many years. All provinces and territories use the National Plumbing Code of Canada (NPC) as a basis for their plumbing regulations. The NPC allowed lead as an acceptable material for pipes (service lines) until 1975. Under the NPC, all fittings must comply to the ASME 112.18.1/CSA B125.1 for plumbing supply fittings (formerly CSA B125.1). This standard limited the lead content of solder to 0.2% in 1986. The NPC officially prohibited lead solders from being used in new plumbing or in repairs to plumbing for drinking water supplies in the 1990 version (NRCC, 2005). The most common replacements for lead solders are tin–antimony, tin–copper and tin–silver solders.

A new generation of reasonably priced brass alloys are now available for plumbing fittings and in-line devices. These “very low lead” brasses contain <0.25% lead as an impurity, and bismuth or a combination of bismuth and selenium replaces the lead in the alloy (AwwaRF, 2007).

B.1.2.2 Copper pipes and brass fittings and fixtures

Copper is used in pipes and copper alloys found in domestic plumbing. Copper alloys used in potable water systems are brasses (in domestic fittings) and bronzes (in domestic plumbing valves). Brasses are basically alloys of copper and zinc, with other minor constituents such as lead. Brass fittings are also often coated with a chromium–nickel compound. Bronzes (also referred to as red brass) are alloys of copper, tin and zinc, with or without lead. Most brasses contain between 2 to 8 percent lead.

In addition to lead that can be found in brass and bronze fittings such as faucets and valves, fixtures such as refrigerated water coolers and bubblers commonly used in schools and other non-residential buildings may contain lead. Selected components of water coolers such as soldered joints within the fixtures or the lining in the tank may contain alloys with lead (U.S. EPA, 2006b).

B.1.2.3 Iron pipes

The following iron-based materials are the principal sources of iron in drinking water distribution systems: cast iron, ductile iron, galvanized iron and steel. The specific components that are likely to come in contact with drinking water in its transit from the treatment plant to the consumer include walls or working parts of well casings, pumps, mixing equipments, meters, pipes, valves and fittings. Iron may be released directly from iron-based materials or indirectly through the iron corrosion by-products, or tubercles, formed during the corrosion process.

B.1.2.4 Galvanized pipes

Galvanized pipes will release zinc, since they are manufactured by dipping steel pipes in a bath of molten zinc. Galvanized pipes can also be sources of cadmium and lead, since these materials are present as impurities (Leroy et al., 1996). The NPC permitted the use of galvanized steel as an acceptable material for pipes for plumbing system until 1980 (NRCC, 2005).

B.1.2.5 Cement pipes

Cement-based materials used to convey drinking water include reinforced concrete pipes, cement mortar linings and asbestos-cement pipes. In addition to the aggregates (sand, gravel or asbestos), which constitute the basic structure of the cement, the binder, which is responsible for the cohesion and mechanical properties of the material, consists mostly of calcium silicates and calcium aluminates in varying proportions (Leroy et al., 1996). Degradation of cement-based materials can be a source of calcium hydroxide (lime) in the distributed water, which may result in an increase in pH and alkalinity. The degradation of cement-based materials can also be a source of aluminum and asbestos in drinking water.

According to the literature, cement-based materials rarely cause serious water quality problems. However, newly installed *in situ* mortar linings have been reported to cause water quality problems in dead ends or low-flow water conditions when water alkalinity is low (Douglas and Merrill, 1991).

B.1.2.6 Plastic pipes

PVC, polyethylene and chlorinated PVC pipes used in the distribution system have the potential to release organic chemicals into the distributed water. PVC mains manufactured prior to 1977 contain elevated levels of vinyl chloride which they are prone to leaching (Flournoy et al., 1999). Stabilizers are used to protect PVC from decomposition when exposed to extreme heat during production. In Canada, organotin compounds are the most common stabilizers used in the production of PVC pipes for drinking water and have been found in drinking water distributed by PVC pipes. Chlorinated PVC pipes are made using stabilizers containing lead which can then leach into the distributed water. It must be noted that fittings intended for PVC pipes can be made of brass which contains lead and can be a potential source of lead where PVC pipes are used. Under the NPC, all plastic pipes must comply to the CSA B137 series of standards for plastic pipe which require that pipes and the associated fittings comply with the NSF/ANSI standard 61 requirements for leaching of contaminants.

B.2 Measuring corrosion

There is no single, reliable index or method to measure water corrosivity and reflect population exposure to contaminants that are leached by the distribution system. Given that a

major source of metals in drinking water is related to corrosion in distribution and plumbing systems, measuring the contaminant at the tap is the best tool to assess corrosion and reflect population exposure.

B.2.1 Levels of contaminants at the tap

The literature indicates that lead, copper and iron are the contaminants whose levels are most likely to exceed guideline values due to the corrosion of materials in drinking water distribution systems. The maximum acceptable concentration (MAC) for lead is based on health considerations for the most sensitive population (i.e., children). Guidelines for copper and iron are based on aesthetic considerations such as colour and taste. An aesthetic objective of ≤ 1.0 mg/L has been established for copper in drinking water; copper is an essential element in humans and is generally considered to be non-toxic except at high doses, in excess of 15 mg/day. An aesthetic objective of ≤ 0.3 mg/L has been established for iron in drinking water; iron is also an essential element in humans. Based on these considerations, measures of lead at the tap are used as the basis for initiating corrosion control programs.

A recent review of the literature (Schock, 2005) indicates that a number of contaminants can be accumulated in and released from the distribution system. Scales formed in distribution system pipes that have reached a dynamic equilibrium can subsequently release contaminants such as aluminum, arsenic, other trace metals and radionuclides. Changes made to the treatment process, particularly those that affect water quality parameters such as pH, alkalinity and ORP should be accompanied by close monitoring in the distributed water.

A national survey was conducted in 1981 to ascertain the levels of cadmium, calcium, chromium, cobalt, copper, lead, magnesium, nickel and zinc in Canadian distributed drinking water (Méranger et al., 1981). Based on the representative samples collected at the tap after 5 minutes of flushing at maximum flow rate, the survey concluded that only copper levels increased to a significant degree in the drinking water at the tap when compared with raw and treated water.

Concurrently, several studies showed that trace elements from household tap water sampled after a period of stagnation can exceed guideline values (Wong and Berrang, 1976; Lyon and Lenihan, 1977; Nielsen, 1983; Samuels and Méranger, 1984; Birden et al., 1985; Neff et al., 1987; Schock and Neff, 1988; Gardels and Thomas, 1989; Schock, 1990a; Singh and Mavinic, 1991; Lytle et al., 1993; Viraraghavan et al., 1996).

A study on the leaching of copper, iron, lead and zinc from copper plumbing systems with lead-based solders in high-rise apartment buildings and single-family homes was conducted by Singh and Mavinic (1991). The study showed that for the generally corrosive water (pH 5.5–6.3; alkalinity 0.6–3.7 mg/L as calcium carbonate) of the Greater Vancouver Regional District, the first litre of tap water taken after an 8-hour period of stagnation exceeded the Canadian drinking water guidelines for lead and copper in 43% (lead) and 62% (copper) of the samples from high-rise buildings and in 47% (lead) and 73% (copper) of the samples from single-family homes. Even after prolonged flushing of the tap water in the high-rise buildings, the guidelines were still exceeded in 6% of the cases for lead and in 9% of the cases for copper. In all cases in the single-family homes, flushing the cold water for 5 minutes successfully reduced levels of lead and copper below the guideline levels.

Subramanian et al. (1991) examined the leaching of antimony, cadmium, copper, lead, silver, tin and zinc from new copper piping with non-lead-based soldered joints exposed to tap water. The levels of antimony, cadmium, lead, silver, tin and zinc were below the detection

limits even in samples that were held in pipes for 90 days. However, copper levels were found to be above 1 mg/L in some cases. The authors concluded that tin–antimony, tin–silver and tin–copper–silver solders used in copper pipes do not leach antimony, cadmium, lead, silver, tin or zinc into drinking water.

Samuels and Méranter (1984) conducted a study on the leaching of trace metals from kitchen faucets in contact with the City of Ottawa’s water. Water was collected after a 24-hour period of stagnation in new faucets not washed prior to testing. Cadmium, chromium, copper, lead and zinc were leached from the kitchen faucets in varying amounts depending on the type of faucet and the solutions used. In general, the concentrations of cadmium, chromium, copper and zinc in the leachates did not exceed the Canadian drinking water guideline values applicable at that time. However, levels well above the guideline value for lead were leached from the faucets containing lead-soldered copper joints.

Similar work by Schock and Neff (1988) revealed that new chrome-plated brass faucets can be a significant source of copper, lead and zinc contamination of drinking water, particularly upon stagnation of the water. The authors also concluded that faucets, as well as other brass fittings in household systems, provide a continuous source of lead, even when lead-free solders and fluxes are used in copper plumbing systems.

Studies have also examined lead concentrations in drinking water in non-residential buildings such as workplaces and schools. Maas et al. (1994) conducted a statistical analysis of water samples collected after an overnight stagnation period from over 12,000 water fountains, bubblers, chillers, faucets and ice makers. The analysis indicated that over 17% of the samples had lead concentrations over 15 µg/L. Further analysis indicated that the drinking water collected from bubblers, chillers and faucets had over 15 µg/L of lead in over 25% of the samples. Other studies have found that between 5 and 21% of drinking water fountains or faucets had lead concentrations above 20 µg/L following a period of stagnation greater than 8 hours (Gnaedinger, 1993; Sathyanarayana et al., 2006; Bryant, 2004; Boyd et al., 2008a).

Studies conducted in Copenhagen, Denmark, found that nickel was leaching from chromium–nickel-plated brass after periods of water stagnation (Anderson, 1983). Nickel concentrations measured in the first 250 mL ranged from 8 to 115 µg/L. These concentrations dropped to 9–19 µg/L after 5 minutes of flushing. Similarly, large concentrations of nickel (up to 8700 µg/L in one case) were released from newly installed chromium–nickel-plated brass, nickel-plated parts and nickel-containing gunmetal following 12-hour periods of water stagnation (Nielsen and Andersen, 2001). Experience with the U.S. Environmental Protection Agency’s Lead and Copper Rule also revealed that brass was a potential source of nickel at the tap (Kimbrough, 2001). Nickel was found in the first litre after a period of water stagnation (mean concentrations in the range of 4.5–9.2 µg/L and maximum concentrations in the range of 48–102 µg/L). The results also indicated that almost all of the nickel was contained in the first 100 mL.

Since cast iron and ductile iron make up more than two thirds of Canadian drinking water distribution systems, it is not surprising that red water is the most common corrosion problem reported by consumers. When iron exceeds the aesthetic objective of ≤ 0.3 mg/L established in the Guidelines for Canadian Drinking Water Quality, it can stain laundry and plumbing fixtures, produce undesirable taste in beverages and impart a yellow to red-brownish colour to the water.

In addition to aesthetic problems, iron tubercles may contain several types of microorganisms. Tuovinen et al. (1980) isolated sulphate reducers, nitrate reducers, nitrate oxidizers, ammonia oxidizers, sulphur oxidizers and unidentified heterotrophic microorganisms

from iron tubercles. Similarly, Emde et al. (1992) isolated coliform species, including *Escherichia coli*, *Enterobacter aerogenes* and *Klebsiella* spp., from iron tubercles in Yellowknife's distribution system. High levels of coliforms (>160 bacteria/g of tubercles) were also detected in iron tubercles at a New Jersey utility that experienced long-term bacteriological problems in its distribution system, even though no coliforms were detected in the treatment plant effluents. The coliform bacteria identified were *E. coli*, *Citrobacter freundii* and *Enterobacter agglomerans* (LeChevallier et al., 1988). Although most pipe surfaces in distribution systems are colonized with microorganisms, iron tubercles can especially favour microorganism growth. The nodular areas of the scale can physically protect bacteria from disinfection by providing rough-surfaced crevices in which the bacteria can hide (LeChevallier et al., 1987).

Iron hydroxides may also adsorb and concentrate chemicals. The installation of chlorination at a Midwestern water system in the United States, caused exceptionally high arsenic levels at the tap. Chlorination of the groundwater (whose arsenic levels never exceeded 10 µg/L) induced the formation of ferric hydroxide solids that readily sorbed and concentrated arsenic present in the groundwater. The addition of chlorine also affected the scale formed on copper plumbing, resulting in the release of copper oxides, which in turn sorbed and concentrated arsenic. Arsenic levels as high as 5 mg/L were found in water samples collected (Reiber and Dostal, 2000). Furthermore, the scale may adsorb chemicals, such as arsenic, which can be later released if the quality of the water distributed is modified (Reiber and Dostal, 2000; Lytle et al., 2004). After finding arsenic concentrations in the range of 10–13 650 µg/L in iron pipe scales of 15 drinking water utilities, Lytle et al. (2004) concluded that distribution systems transporting water containing less than 10 µg/L arsenic could still produce dangerous levels of arsenic at the consumer's tap. Arsenic that accumulates in corrosion by-products found in the distribution system over time could be released back into the water, especially during changes in hydraulic regime and/or water quality.

High concentrations of aluminum were found in the drinking water of Willemstad, Curaçao, Netherlands Antilles, following the installation of 2.2 km of new factory-lined cement mortar pipes (Berend and Trouwborst, 1999). Aluminum concentrations in the distributed water increased from 5 to 690 µg/L within 2 months of the installation. More than 2 years later, aluminum continued to leach from the lining at concentrations above 100 µg/L. These atypical elevated aluminum concentrations were attributed to the high aluminum content of the cement mortar lining (18.7% as aluminum oxide), as well as to the low hardness (15–20 mg/L as calcium carbonate), low alkalinity (18–32 mg/L as calcium carbonate), high pH (8.5–9.5), long contact time (2.3 days) of the distributed water and use of polyphosphate as a corrosion inhibitor.

Aluminum was also found to leach from *in situ* portland cement-lined pipes in a series of field trials carried out throughout the United Kingdom in areas with different water qualities (Conroy, 1991). Aluminum concentrations above the European Community (EC) Directive of 0.2 mg/L were found for the first 2 months following installation in very low alkalinity water (around 10 mg/L as calcium carbonate) with elevated pH (>9.5) and contact times of 6 hours. Aluminum concentrations dropped below the EC Directive level after 2 months of pipe service. Furthermore, in water with slightly higher alkalinity (around 50 mg/L as calcium carbonate), aluminum was not found to exceed the EC Directive at any time. The Canadian guideline for aluminum in drinking water is an operational guidance value, which applies to treatment plants using aluminum-based coagulants in their treatment process. Because of the lack of “consistent,

convincing evidence that aluminum in drinking water causes adverse health effects in humans,” a health-based guideline has not been established for aluminum in drinking water.

Asbestos fibres have been found to leach from asbestos-cement pipes (Leroy et al., 1996). Although a Guideline Technical Document is available for asbestos in drinking water, it states that “there is no consistent, convincing evidence that ingested asbestos is hazardous. There is, therefore, no need to establish a maximum acceptable concentration for asbestos in drinking water.”

A study of organotin levels in Canadian drinking water distributed through newly installed PVC pipes was conducted in the winter and spring (28 sites) and autumn (21 sites) of 1996 (Sadiki and Williams, 1999). Approximately 29% and 40% of the samples of distribution water supplied through PVC pipes contained organotin compounds in the winter/spring and autumn surveys, respectively. The most commonly detected organotin compounds were monomethyltin and dimethyltin, at levels ranging from 0.5 to 257 ng tin/L. An additional study in the summer of 1996 of locations where the highest organotin levels were detected in the winter/spring survey indicated that organotin levels had decreased in 89% of the distribution water samples (tin levels ranging from 0.5 to 21.5 ng/L). There is no Canadian drinking water guideline for organotins.

B.2.2 Factors influencing levels of contaminants at the tap

Many factors contribute to the corrosion and leaching of contaminants from drinking water distribution systems. However, the principal factors are the type of materials used, the age of the plumbing system, the stagnation time of the water and the quality of the water in the system. The concentrations of all corrosive or dissolvable materials present in the distribution system will be influenced by some or all of these factors. However, the manner in which these factors will impact each contaminant will vary from one contaminant to another.

Factors influencing the corrosion and leaching of lead, copper, iron and cement are discussed here, since these materials are most likely to produce contaminants that exceed the Canadian drinking water guidelines, pose health risks to the public or are a source of consumer complaints. A list of the specific key factors and their main effects is provided in Part C.

B.2.2.1 Age of the plumbing system

Lead concentrations at the tap originating from lead solders and brass fittings decline with age (Sharrett et al., 1982; Birden et al., 1985; Boffardi, 1988, 1990; Schock and Neff, 1988; Neuman, 1995). Researchers have concluded that the highest lead concentrations appear in the first year following installation and level off after a number of years of service (Sharrett et al., 1982; Boffardi, 1988). However, unlike lead-soldered joints and brass fittings, lead piping can continue to provide a consistently strong source of lead after many years of service (Britton and Richards, 1981; Schock et al., 1996). In a field study in which lead was sampled in tap water, Maas et al. (1991) showed that homes of all ages were at a substantial risk of lead contamination.

Copper release into the drinking water largely depends on the type of scale formed within the plumbing system. It can be assumed that at a given age, a corrosion by-product governs the release of copper into the drinking water. A decrease in solubility in the following order is observed when the following scales predominate: cuprous hydroxide $[\text{Cu}(\text{OH})_2]$ > bronchantite $[\text{Cu}_4(\text{SO}_4)(\text{OH})_6]$ >> cupric phosphate $[\text{Cu}_3(\text{PO}_4)_2]$ > tenorite $[\text{CuO}]$ and malachite $[\text{Cu}_2(\text{OH})_2\text{CO}_3]$ (Schock et al., 1995). Copper concentrations continue to decrease with the increasing age of plumbing materials, even after 10 or 20 years of service, when tenorite or

malachite scales tend to predominate (Sharrett et al., 1982; Neuman, 1995; Edwards and McNeill, 2002). In certain cases, sulphate and phosphate can at first decrease copper concentrations by forming bronchantite and cupric phosphate, but in the long run they may prevent the formation of the more stable tenorite and malachite scales (Edwards et al., 2002).

The age of an iron pipe affects its corrosion. In general, both iron concentration and the rate of corrosion increase with time when a pipe is first exposed to water, but both are then gradually reduced as the scale builds up (McNeill and Edwards, 2001). However, most red water problems today are caused by heavily tuberculated old unlined cast iron pipes that are subject to stagnant water conditions prevalent in dead ends. Sarin et al. (2003) removed unlined cast iron pipes that were 90–100 years old from distribution systems. The internal surface of these pipes was so heavily corroded that up to 76% of the cross-section of the pipes was blocked by scales. Such pipes are easily subject to scouring and provide the high surface areas that favour the release of iron.

A newly installed cement-based material will typically leach lime, which, in turn, will increase water pH, alkalinity and concentrations of calcium (Holtschulte and Schock, 1985; Douglas and Merrill, 1991; Conroy et al., 1994; Douglas et al., 1996; Leroy et al., 1996). Experiments by Douglas and Merrill (1991) showed that after 1, 6 and 12 years in low-flow, low-alkalinity water, lime continued to leach from cement mortar linings upon prolonged exposure. The rate of lime leaching, however, significantly decreased from the 6- and 12-year-old pipes when compared with the 1-year-old pipe. These observations were explained by the fact that the lime leaching rate naturally slows down as surface calcium becomes depleted. As well, the deposits formed after extensive exposure may serve to protect the mortar against further leaching.

B.2.2.2 Stagnation time of the water

Concentrations of lead and copper in drinking water from various sources of leaded material including lead service lines, leaded solder, and brass fittings which contain lead can increase significantly following a period of water stagnation of a few hours in the distribution system. Many factors such as the water quality and the age, composition and diameter and length of the lead pipe impact the shape of stagnation curves and the time to reach an equilibrium state (Lytle and Schock, 2000).

In reviewing lead stagnation curves drawn by several authors, Schock et al. (1996) concluded that lead levels increase exponentially upon stagnation, but ultimately approach a fairly constant equilibrium value after overnight stagnation. Lytle and Schock (2000) showed that lead levels increased rapidly with the stagnation time of the water, with the most critical period being during the first 20–24 hours for both lead pipe and brass fittings. Lead levels increased most rapidly over the first 10 hours, reaching approximately 50–70% of the maximum observed value. In their experiment, lead levels continued to increase slightly even up to 90 hours of stagnation.

Figure 4 illustrates lead concentrations versus time for two different water qualities and lead pipe diameters. The upper curve represents lead concentrations in ½-inch pipe where the pH of the water is 6.8 and the alkalinity is 10 mg/L CaCO₃. The lower curve represents lead concentrations in 3/8-inch pipe where the pH of the water is 7.2 and the alkalinity is 213 mg/L CaO₃. Additional data from Kuch and Wagner (1983) indicates that lead levels approach maximum or equilibrium concentrations at greater than 300 minutes (5 hrs) for ½-inch pipe (lead service line) and at greater than 400 minutes (6.7 hrs) for 3/4-inch pipe. The diameter of pipes, or

lead service lines (LSL) in Canada range from 1/2-inch to 3/4-inch but are typically 5/8-inch to 3/4-inch. In addition, lead concentrations have been demonstrated to be highly sensitive to stagnation time in the first three hours of standing time for 1/2 inch to 3/4-inch pipe. Depending on the water quality characteristics and pipe diameters, differences between 10 to 30% could be observed with differences in standing time as little as 30 and 60 minutes (Kuch and Wagner, 1983; Shock, 1990). Long lead or copper pipe of small diameter produces the greatest concentrations of lead or copper respectively upon stagnation (Kuch and Wagner, 1983; Ferguson et al., 1996).

Lead is also leached during no-flow periods from soldered joints and brass fittings (Birden et al., 1985; Neff et al., 1987; Schock and Neff, 1988). Wong and Berrang (1976) concluded that water sampled in a 1-year-old household plumbing system made of copper with tin-lead solders could exceed 0.05 mg lead/L after 4–20 hours of stagnation, and that water in contact with lead water pipes could exceed this value in 10–100 minutes. In a study examining the impact of stagnation time on lead release from brass coupons, Lytle and Schock (1995) observed that for brass containing 6% lead, lead concentrations increased slowly for the first hour but ultimately reached a maximum concentration of 0.08 mg/L following 15 hours of stagnation. Following a six hour stagnation period the lead level was greater than 0.04 mg/L. The amount of lead released from brass fittings was found to vary with both alloy composition and




Figure 1 Lead concentration vs. pipe diameter and water quality parameters. Upper curve is water with pH 6.9, alkalinity of 10 mg/L CaCO₃ in a 1/2-inch pipe. Lower curve is water with pH 7.2, alkalinity of 213 mg/L in a 3/8-inch pipe (from Kuch and Wagner, 1983)

stagnation time.

Copper behaviour is more complex than lead behaviour when it comes to the stagnation of the water. Copper levels will initially increase upon stagnation of the water, but can then decrease or continue to increase, depending on the oxidant levels. Lytle and Schock (2000)

showed that copper levels increased rapidly with the stagnation time of the water, but only until dissolved oxygen fell below 1 mg/L, after which they dropped significantly. Sorg et al. (1999) also observed that in softened water, copper concentrations increased to maximum levels of 4.4 and 6.8 mg/L after about 20–25 hours of standing time, then dropped to 0.5 mg/L after 72–92 hours. Peak concentrations corresponded to the time when the dissolved oxygen was reduced to 1 mg/L or less. In non-softened water, the maximum was reached in less than 8 hours, because the dissolved oxygen decreased more rapidly in the pipe loop exposed to non-softened water.

Cyclic periods of flow and stagnation were reported as the primary cause of red water problems resulting from iron corrosion of distribution systems (Benjamin et al., 1996). Iron concentration was also shown to increase with longer water stagnation time prevalent in dead ends (Beckett et al., 1998; Sarin et al., 2000).

Long contact time between distributed water and cement materials has been correlated with increased water quality deterioration (Holtshulte and Schock, 1985; Conroy, 1991; Douglas and Merrill, 1991; Conroy et al., 1994; Douglas et al., 1996; Berend and Trouwborst, 1999). In a survey of 33 U.S. utilities with newly installed *in situ* lined cement mortar pipes carrying low-alkalinity water, Douglas and Merrill (1991) concluded that degraded water quality was most noticeable in dead ends or where the flow was low or intermittent. Similar conclusions were reached by the Water Research Centre in the United Kingdom, where the longer the supply water was in contact with the mortar lining, the greater was the buildup of leached hydroxides, and hence the higher the pH (Conroy, 1991; Conroy et al., 1994). Long residence times in new cement mortar pipes installed in Curaçao were also linked with elevated concentrations of aluminum in drinking water (Berend and Trouwborst, 1999), but these were due to the high aluminum content of the mortar (18.7% as aluminum oxide).

B.2.2.3 *pH*

The effect of pH on the solubility of the corrosion by-products formed during the corrosion process is often the key to understanding the concentration of metals at the tap. An important characteristic of distributed water with higher pH is that the solubility of the corrosion by-products formed in the distribution system typically decreases.

The solubility of the main lead corrosion by-products (divalent lead solids: cerussite [PbCO₃], hydrocerussite [Pb₃(CO₃)₂(OH)₂] and lead hydroxide [Pb(OH)₂]) largely determines the lead levels at the tap (Schock, 1980, 1990b; Sheiham and Jackson, 1981; De Mora and Harrison, 1984; Boffardi, 1988, 1990; U.S. EPA, 1992; Leroy, 1993; Peters et al., 1999). From thermodynamic considerations, lead solubility of corrosion by-products in distribution systems decreases with increasing pH (Britton and Richards, 1981; Schock and Gardels, 1983; De Mora and Harrison, 1984; Boffardi, 1988; Schock, 1989; U.S. EPA, 1992; Singley, 1994; Schock et al., 1996). Solubility models show that the lowest lead levels occur when pH is around 9.8 (Schock and Gardels, 1983; Schock, 1989; U.S. EPA, 1992; Schock et al., 1996). However, these pH relationships may not be valid for insoluble tetravalent lead dioxide (PbO₂) solids, which have been discovered in lead pipe deposits from several different water systems (Schock et al., 1996, 2001). Based on tabulated thermodynamic data, the pH relationship of lead dioxide may be opposite to that of divalent lead solids (i.e., cerussite, hydrocerussite) (Schock et al., 2001; Schock and Giani, 2004). Lytle and Schock (2005) demonstrated that lead dioxide easily formed at pH 6–6.5 in water with persistent free chlorine residuals in weeks to months.

Unlike contamination from lead pipes and leaded copper alloys, which is mainly controlled by the solubility of the corrosion products, contamination from leaded solders is

largely controlled by galvanic corrosion (Oliphant, 1983b; Schock, 1990b; Reiber, 1991; Singley, 1994). Increase in pH is associated with a decrease in galvanic corrosion of leaded solders (Oliphant, 1983b; Gregory, 1990; Reiber, 1991; Singley, 1994).

Utility experience has also shown that the lowest levels of lead at the tap are associated with pH levels above 8 (Karalekas et al., 1983; Lee et al., 1989; Dodrill and Edwards, 1995; Douglas et al., 2004). From 1999 to 2003, the City of Ottawa evaluated a number of chemical alternatives to provide corrosion control of their distribution system (Douglas et al., 2004). Based on bench- and pilot-scale experimental results and analysis of the impacts on a number of criteria, a corrosion control strategy was established whereby a pH of 9.2 and a minimum alkalinity target of 35 mg/L as calcium carbonate would be achieved through the use of sodium hydroxide and carbon dioxide. During the initial implementation phase, the switch to sodium hydroxide occurred while maintaining the pH at 8.5. However, subsequent to a request for lead testing by a client, the investigators found an area of the city with high levels of lead at the tap (10–15 µg/L for flowing samples). The problem was attributed to nitrification within the distribution system, which caused a reduction in the pH from 8.5 to a range of 7.8–8.2 and resulted in lead leaching from lead service lines. The pH was increased from 8.5 to 9.2 to address the nitrification issue and reduce the dissolution of lead. This increase in the pH almost immediately reduced lead concentrations at the tap in the problem area to a range of 6–8 µg/L for flowing samples. On-going monitoring has demonstrated that lead levels at the tap consistently ranged from 1.3 to 6.8 µg/L following the increase in pH, well below the regulated level (Ontario Drinking Water Standard) of 10 µg/L (Douglas et al., 2007).

Examination of utility data provided by 365 utilities under the U.S. EPA Lead and Copper Rule revealed that the average 90th percentile lead levels at the tap were dependent on both pH and alkalinity (Dodrill and Edwards, 1995). In the lowest pH category (pH <7.4) and lowest alkalinity category (alkalinity <30 mg/L as calcium carbonate), utilities had a 80% likelihood of exceeding the U.S. EPA Lead and Copper Rule Action Level for lead of 15 µg/L. In this low-alkalinity category, only a pH greater than 8.4 seemed to reduce lead levels at the tap. However, when an alkalinity greater than 30 mg/L as calcium carbonate was combined with a pH greater than 7.4, the water produced could, in certain cases, meet the U.S. EPA Lead and Copper Rule Action Level for lead.

A survey of 94 water utilities conducted in 1988 to determine lead levels at the consumer's tap and to evaluate the factors that influence their levels showed similar results (Lee et al., 1989). In total, 1484 sites, including both non-lead and lead service lines, were sampled after an overnight stagnation of at least 6 hours. The results of the study clearly demonstrated that maintaining a pH of at least 8.0 effectively controlled lead levels (<10 µg/L) in the first litre collected at the tap. The Boston, Massachusetts, metropolitan area conducted a 5-year study to reduce lead concentrations in its drinking water distribution system (Karalekas et al., 1983). Fourteen households were examined for lead concentrations at the tap, in their lead service lines and in their adjoining distribution system from 1976 to 1981. Average concentrations reported combined samples taken 1) after overnight stagnation at the tap, 2) after the water turned cold and 3) after the system was flushed for an additional 3 minutes. Even if alkalinity remained very low (on average 12 mg/L as calcium carbonate), raising the pH from 6.7 to 8.5 reduced average lead concentrations from 0.128 to 0.035 mg/L.

Although the hydrogen ion does not play a direct reduction role on copper surfaces, pH can influence copper corrosion by altering the equilibrium potential of the oxygen reduction half-reaction and by changing the speciation of copper in solution (Reiber, 1989). Copper

corrosion increases rapidly as the pH drops below 6; in addition, uniform corrosion rates can be high at low pH values (below about pH 7), causing metal thinning. At higher pH values (above about pH 8), copper corrosion problems are almost always associated with non-uniform or pitting corrosion processes (Edwards et al., 1994a; Ferguson et al., 1996). Edwards et al. (1994b) found that for new copper surfaces exposed to simple solutions that contained bicarbonate, chloride, nitrate, perchlorate or sulphate, increasing the pH from 5.5 to 7.0 roughly halved corrosion rates, but further increases in pH yielded only subtle changes.

The prediction of copper levels in drinking water relies on the solubility and physical properties of the cupric oxide, hydroxide and basic carbonate solids that comprise most scales in copper water systems (Schock et al., 1995). In the cupric hydroxide model of Schock et al. (1995), a decrease in copper solubility with higher pH is evident. Above a pH of approximately 9.5, an upturn in solubility is predicted, caused by carbonate and hydroxide complexes increasing the solubility of cupric hydroxide. Examination of experience from 361 utilities reporting copper levels under the U.S. EPA Lead and Copper Rule revealed that the average 90th percentile copper levels were highest in waters with pH below 7.4 and that no utilities with pH above 7.8 exceeded the U.S. EPA's action level for copper of 1.3 mg/L (Dodrill and Edwards, 1995). However, problems associated with copper solubility were also found to persist up to about pH 7.9 in cold, high-alkalinity and high-sulphate groundwater (Edwards et al., 1994a).

In the pH range of 7–9, both the corrosion rate and the degree of tuberculation of iron distribution systems generally increase with increasing pH (Larson and Skold, 1958; Stumm, 1960; Hatch, 1969; Pisigan and Singley, 1987). Iron levels, however, were usually reported to decrease with increasing pH (Karalekas et al., 1983; Kashinkunti et al., 1999; Broo et al., 2001; Sarin et al., 2003). In a pipe loop system constructed from 90- to 100-year-old unlined cast iron pipes taken from a Boston distribution system, iron concentrations were found to steadily decrease when the pH was raised from 7.6 to 9.5 (Sarin et al., 2003). Similarly, when iron was measured in the distribution system following a pH increase from 6.7 to 8.5, a consistent downward trend in iron concentrations was found over 2 years (Karalekas et al., 1983). These observations are consistent with the fact that the solubility of iron-based corrosion by-products decreases with increasing pH.

Water with low pH, low alkalinity and low calcium is particularly aggressive towards cement materials. The water quality problems that may occur are linked to the chemistry of the cement. Lime from the cement releases calcium ions and hydroxyl ions into the drinking water. This, in turn, may result in a substantial pH increase, depending on the buffering capacity of the water (Leroy et al., 1996). Pilot-scale tests were conducted to simulate low-flow conditions of newly lined cement mortar pipes carrying low-alkalinity water (Douglas et al., 1996). In the water with an initial pH of 7.2, alkalinity of 14 mg/L as calcium carbonate and calcium at 13 mg/L as calcium carbonate, measures of pH as high as 12.5 were found. Similarly, in the water with an initial pH of 7.8, alkalinity of 71 mg/L as calcium carbonate and calcium at 39 mg/L as calcium carbonate, measures of pH as high as 12 were found. The most significant pH increases were found during the first week of the experiment, and pH decreased slowly with aging of the lining. In a series of field and test-rig trials to determine the impact of *in situ* cement mortar lining on water quality, Conroy et al. (1994) observed that in low-flow and low-alkalinity water (around 10 mg/L as calcium carbonate), pH increases exceeding 9.5 could occur for over 2 years following the lining.

A series of field trials carried out throughout the United Kingdom in areas with different water qualities found that high pH in cement pipes can render lead soluble. Lead levels increased

significantly with increasing pH when pH was >10.5. The concentration of lead ranged from just less than 100 µg/L at pH 11 to greater than 1000 µg/L at pH >12 (Conroy, 1991). This brings into the question the accuracy of the solubility models for high pH ranges, and the point at which pH adjustment may become detrimental.

Elevated pH levels resulting from cement leaching may also contribute to aluminum leaching from cement materials, since high pH may increase aluminum solubility (Berend and Trouwborst, 1999).

B.2.2.4 Alkalinity

Alkalinity serves to control the buffer intensity of most water systems; therefore, a minimum amount of alkalinity is necessary to provide a stable pH throughout the distribution system for corrosion control of lead, copper and iron and for the stability of cement-based linings and pipes.

Alkalinity of the finished water is affected by the use of reverse osmosis (RO) and nanofiltration (NF) processes. These processes remove sodium, sulfate, chloride calcium and bicarbonate ions and result in a corrosive finished water (Taylor and Wiesner, 1999). This underlines the important of process adjustments such as addition of base and aeration of the permeate stream to recover alkalinity prior to distribution.

According to thermodynamic models, the minimum lead solubility occurs at relatively high pH (9.8) and low alkalinity (30–50 mg/L as calcium carbonate) (Schock, 1980, 1989; Schock and Gardels, 1983; U.S. EPA, 1992; Leroy, 1993; Schock et al., 1996). These models show that the degree to which alkalinity affects lead solubility depends on the form of lead carbonate present on the pipe surface. When cerussite is stable, increasing alkalinity reduces lead solubility; when hydrocerussite is stable, increasing alkalinity increases lead solubility (Sheiham and Jackson, 1981; Boffardi, 1988, 1990). Cerussite is less stable at pH values where hydrocerussite is stable and may form. Eventually, hydrocerussite will be converted to cerussite, which is found in many lead pipe deposits. Higher lead release was observed in pipes where cerussite was expected to be stable given the pH/alkalinity conditions. However, when these conditions are adjusted so that hydrocerussite is thermodynamically stable, lead release will be lower than in any place where cerussite is stable (Schock, 1990a).

Laboratory experiments also revealed that, at pH 7–9.5, optimal alkalinity for lead control is between 30 and 45 mg/L as calcium carbonate, and that adjustments to increase alkalinity beyond this range yields little additional benefit (Schock, 1980; Sheiham and Jackson, 1981; Schock and Gardels, 1983; Edwards and McNeill, 2002) and can be detrimental in some cases (Sheiham and Jackson, 1981).

Schock et al. (1996) reported the existence of significant amounts of insoluble tetravalent lead dioxide in lead pipe deposits from several different water systems. However, the alkalinity relationship for lead dioxide solubility is not known, as no complexes or carbonate solids have been reported. The existence of significant amounts of insoluble lead dioxide in lead pipe deposits may explain the erratic lead release from lead service lines and poor relationship between total lead and alkalinity (Lytle and Schock, 2005).

Alkalinity is not expected to influence the release of lead from leaded solders, since this release is mostly dependent on the galvanic corrosion of the leaded solders as opposed to the solubility of the corrosion by-products formed (Oliphant, 1983a). However, Dudi and Edwards (2004) predicted that alkalinity could play a role in the leaching of lead from galvanic connections between lead- and copper-bearing plumbing. A clear relationship between alkalinity

and lead solubility based on utility experience remains to be established. Trends in field data of 47 U.S. municipalities indicated that the most promising water chemistry targets for lead control were a pH level of 8–10 with an alkalinity of 30–150 mg/L as calcium carbonate (Schock et al., 1996). A subsequent survey of 94 U.S. water companies and districts revealed no relationship between lead solubility and alkalinity (Lee et al., 1989). In a survey of 365 utilities under the U.S. EPA Lead and Copper Rule, lead release was significantly lower when alkalinity was between 30 and 74 mg/L as calcium carbonate than when alkalinity was <30 mg/L as calcium carbonate. Lower lead levels were also observed in utilities with alkalinities between 74 and 174 mg/L and greater than 174 mg/L when the pH was 8.4 or lower (Dodrill and Edwards, 1995).

Laboratory and utility experience demonstrated that copper corrosion releases are worse at higher alkalinity (Edwards et al., 1994b, 1996; Schock et al., 1995; Ferguson et al., 1996; Broo et al., 1998) and are likely due to the formation of soluble cupric bicarbonate and carbonate complexes (Schock et al., 1995; Edwards et al., 1996).

Examination of utility data for copper levels, obtained from 361 utilities under the U.S. EPA Lead and Copper Rule, also revealed the adverse effects of alkalinity and estimated that they were approximately linear and more significant at lower pH: a combination of low pH (<7.8) and high alkalinity (>74 mg/L as calcium carbonate) produced the worst-case 90th percentile copper levels (Edwards et al., 1999).

However, low alkalinity (<25 mg/L as calcium carbonate) also proved to be problematic under utility experience (Schock et al., 1995). For high-alkalinity waters, the only practical solutions to reduced cuprosolvency are lime softening, removal of bicarbonate or rather large amounts of orthophosphate addition (U.S. EPA, 2003).

Lower copper can be associated with higher alkalinity when the formation of the less soluble malachite and tenorite has been favoured (Schock et al., 1995). A laboratory experiment conducted by Edwards et al. (2002) revealed the possible dual effect of high alkalinity. For relatively new pipes, at pH 7.2, the maximum concentration of copper released was nearly a linear function of alkalinity. However, as the pipes aged, lower releases of copper were measured at an alkalinity of 300 mg/L as calcium carbonate, where malachite had formed, than at alkalinities of 15 and 45 mg/L as calcium carbonate, at which the relatively soluble cupric hydroxide prevailed.

Lower iron corrosion rates (Stumm, 1960; Pisigan and Singley, 1987; Hedberg and Johansson, 1987; Kashinkunti et al., 1999) and iron concentrations (Horsley et al., 1998; Sarin et al., 2003) in distribution systems have been associated with higher alkalinities.

Experiments using a pipe loop system built from 90- to 100-year-old unlined cast iron pipes taken from a Boston distribution system showed that decreases in alkalinity from 30–35 mg/L to 10–15 mg/L as calcium carbonate at a constant pH resulted in an immediate increase of 50–250% in iron release. Changes in alkalinity from 30–35 mg/L to 58–60 mg/L as calcium carbonate and then back to 30–35 mg/L also showed that higher alkalinity resulted in lower iron release, but the change in iron release was not as dramatic as the changes in the lower alkalinity range (Sarin et al., 2003). An analysis of treated water quality parameters (pH, alkalinity, hardness, temperature, chloride and sulphate) and red water consumer complaints was conducted in the City of Topeka, Kansas (Horsley et al., 1998). Data from the period 1989–1998 were used for the analysis. The majority of red water problems were found in unlined cast iron pipes that were 50–70 years old. From 1989 to 1998, the annual average pH of the distributed water ranged from 9.1 to 9.7; its alkalinity ranged from 47 to 76 mg/L as calcium carbonate, and

its total hardness ranged from 118 to 158 mg/L as calcium carbonate. The authors concluded that the strongest and most useful relationship was between alkalinity and red water complaints and that maintaining finished water with an alkalinity greater than 60 mg/L as calcium carbonate substantially reduced the number of consumer complaints.

Alkalinity is a key parameter in the deterioration of water quality by cement materials. When poorly buffered water comes into contact with cement materials, the soluble alkaline components of the cement pass rapidly into the drinking water. Conroy et al. (1994) observed that alkalinity played a major role in the deterioration of the quality of the water from *in situ* mortar lining in dead-end mains with low-flow conditions. When the alkalinity was around 10 mg/L as calcium carbonate, pH levels remained above 9.5 for up to 2 years, and aluminum levels were above 0.2 mg/L for 1–2 months following the lining process. However, when alkalinity was around 35 mg/L as calcium carbonate, the water quality problem was restricted to an increase in pH level above 9.5 for 1–2 months following the lining process. When the alkalinity was greater than 55 mg/L as calcium carbonate, no water quality problems were observed.

B.2.2.5 Temperature

No simple relationship exists between temperature and corrosion processes, because temperature influences several water quality parameters, such as dissolved oxygen solubility, solution viscosity, diffusion rates, activity coefficients, enthalpies of reactions, compound solubility, oxidation rates and biological activities (McNeill and Edwards, 2002).

These parameters, in turn, influence the corrosion rate, the properties of the scales formed and the leaching of materials into the distribution systems. The corrosion reaction rate of lead, copper and iron is expected to increase with temperature. However, the solubility of several corrosion by-products decreases with increasing temperature (Schock, 1990a; Edwards et al., 1996; McNeill and Edwards, 2001, 2002).

Seasonal variations in temperature between the summer and winter months were correlated with lead concentrations, with the warmer temperatures of the summer months increasing lead concentrations (Britton and Richards, 1981; Karalekas et al., 1983; Colling et al., 1987, 1992; Douglas et al., 2004). From 1999 to 2003, the City of Ottawa investigated a number of corrosion control options for their distribution system (Douglas et al., 2004). The investigators reported a strong seasonal variation in lead concentration, with the highest lead levels seen during the months of May to November.

Similarly, in a survey of the release of copper corrosion by-products in the drinking water of high-rise buildings and single-family homes in the Greater Vancouver Regional District, Singh and Mavinic (1991) noted that water run through cold water taps typically contained one third the copper concentrations measured in running hot water taps. A laboratory experiment that compared copper release at 4, 20, 24 and 60°C in a soft, low-alkalinity water showed higher copper release at 60°C, but little difference in copper release between 4 and 24°C (Boulay and Edwards, 2001). However, copper hydroxide solubility was shown to decrease with increasing temperature (Edwards et al., 1996; Hidmi and Edwards, 1999).

In a survey of 365 utilities under the U.S. EPA Lead and Copper Rule, no significant trend between temperature and lead or copper levels was found (Dodrill and Edwards, 1995).

Red water complaints as a function of temperature were analysed by Horsley et al. (1998). Although no direct correlation was found between temperature and red water complaints, more red water complaints were reported during the warmer summer months. Corrosion rates,

measured in annular reactors made of new cast iron pipes, were also strongly correlated with seasonal variations (Volk et al., 2000). The corrosion rates at the beginning of the study (March) were approximately 2.5 milli-inch per year (mpy) at a temperature below 13°C. The corrosion rates started to increase in May and were highest during the months of July to September (5–7 mpy and >20°C).

No information was found in the reviewed literature on the relationship between temperature and cement pipe degradation.

B.2.2.6 Calcium

Traditionally, it was thought that calcium stifled corrosion of metals by forming a film of calcium carbonate on the surface of the metal (also called passivation). However, many authors have refuted this idea (Stumm, 1960; Nielsen, 1983; Lee et al., 1989; Schock, 1989, 1990b; Leroy, 1993; Dodrill and Edwards, 1995; Lyons et al., 1995; Neuman, 1995; Reda and Alhajji, 1996; Rezanian and Anderl, 1997; Sorg et al., 1999). No published study has demonstrated, through compound-specific analytical techniques, the formation of a protective calcium carbonate film on lead, copper or iron pipes (Schock, 1989). Leroy (1993) even showed that in certain cases, calcium can slightly increase lead solubility. Furthermore, surveys of U.S. water companies and districts revealed no relationship between lead or copper levels and calcium levels (Lee et al., 1989; Dodrill and Edwards, 1995).

For iron, many authors have reported the importance of calcium in various roles, including calcium carbonate scales, mixed iron/calcium carbonate solids and the formation of a passivating film at cathodic sites (Larson and Skold, 1958; Stumm, 1960; Merrill and Sanks, 1978; Benjamin et al., 1996; Schock and Fox, 2001). However, calcium carbonate by itself does not form protective scales on iron materials (Benjamin et al., 1996).

Calcium is the main component of cement materials. Calcium oxide makes up 38–65% of the composition of primary types of cement used for distributing drinking water (Leroy et al., 1996). Until an equilibrium state is reached between the calcium in the cement and the calcium of the conveyed water, it is presumed that calcium from the cement will be either leached out of or precipitated into the cement pores, depending on the calcium carbonate precipitation potential of the water.

B.2.2.7 Free chlorine residual

Hypochlorous acid is a strong oxidizing agent used for the disinfection of drinking water and is the predominant form of free chlorine below pH 7.5. Free chlorine species (i.e., hypochlorous acid and hypochlorite ion) can also act as primary oxidants towards lead and thus increase lead corrosion (Boffardi, 1988, 1990; Schock et al., 1996; Lin et al., 1997). However, a pipe loop study on the effect of chlorine on corrosion demonstrated that a free chlorine residual (0.2 mg/L) did not increase lead concentrations (Cantor et al., 2003). A survey of 94 U.S. water companies and districts also revealed no relationship between lead levels and free chlorine residual concentrations (in the range of 0–0.5 mg/L) (Lee et al., 1989).

Significant lead dioxide deposits in scales were first reported by Schock et al. (1996) in pipes from several different water systems. Suggestions were made as to the chemical conditions that would favour these tetravalent lead deposits and the changes in treatment conditions (particularly disinfection changes) that could make the tetravalent lead scales vulnerable to destabilization. In 2001, Schock et al. found deposits in lead pipes of the Cincinnati, Ohio, distribution system that contained lead dioxide as the primary protective solid phase. Subsequent

to these findings, different attributes of the theoretical solubility chemistry of lead dioxide were expanded upon, particularly the association with high free chlorine residuals and low oxidant demand.

Following the discovery of elevated lead concentrations after sections of Washington, DC, converted to chloramination, Renner (2004) described the link of the disinfectant change to the previous U.S. EPA research on tetravalent lead scale formation (Schock et al., 2001). Schock and Giani (2004) reported the results of tap monitoring history and scale analysis from the Water and Sewer Authority system in Washington, DC, confirming lead dioxide as the primary starting material, thus validating the hypothesis that the lowering of oxidation–reduction potential (ORP) by changing from high dosages of free chlorine to chloramination caused high rates of lead dissolution. The laboratory experiments of Edwards and Dudi (2004) and Lytle and Schock (2005) confirmed that lead dioxide deposits could be readily formed and subsequently destabilized in weeks to months under realistic conditions of distribution system pH, ORP and alkalinity. A recent laboratory study by Switzer et al. (2006) demonstrated that water with free chlorine oxidized lead to insoluble lead dioxide deposits and that lead was almost completely dissolved in a chloramine solution. These study findings further support the hypothesis that a change from free chlorine to chloramine can cause lead dissolution.

When hypochlorous acid is added to a water supply, it becomes a dominant oxidant on the copper surface (Atlas et al., 1982; Reiber, 1987, 1989; Hong and Macauley, 1998). Free chlorine residual was shown to increase copper corrosion at lower pH (Atlas et al., 1982; Reiber, 1989). Conversely, free chlorine residual was shown to decrease copper corrosion rate at pH 9.3 (Edwards and Ferguson, 1993; Edwards et al., 1999). However, Schock et al. (1995) concluded that free chlorine species would affect the equilibrium solubility of copper by stabilizing copper(II) solid phases, which results in a substantially higher level of copper release. The authors did not observe any direct effects of free chlorine on copper (II) solubility other than the change in valence state and, hence, the indirect change in potential of cuprosolvency.

Several authors reported an increase in the iron corrosion rate with the presence of free chlorine (Pisigan and Singley, 1987; Cantor et al., 2003). However, a more serious health concern is the fact that iron corrosion by-products readily consume free chlorine residuals (Fraturet et al., 1999). Furthermore, when iron corrosion is microbiologically influenced, a higher level of free chlorine residual may actually decrease corrosion problems (LeChevallier et al., 1993). No information was found in the literature correlating iron levels with free chlorine residuals.

No information was found in the literature correlating free chlorine residual with cement pipe degradation.

B.2.2.8 Chloramines

Chloramines have been reported to influence lead in drinking water distribution systems. As noted previously, in 2000, the Water and Sewer Authority in Washington, DC, modified its disinfection treatment to comply with the U.S. EPA's Disinfection Byproducts Rule. The utility started using chloramines instead of chlorine for the purpose of secondary disinfection. Following this change, more than 1000 homes in Washington, DC, exceeded the U.S. EPA's Action Level for lead of 15 µg/L, and more than 157 homes were found to have lead levels at the tap greater than 300 µg/L (Renner, 2004; U.S. EPA, 2007). Since chlorine is a powerful oxidant, the lead oxide scale formed over the years had reached a dynamic equilibrium in the distribution system. Switching from chlorine to chloramines reduced the oxidizing potential of the

distributed water and destabilized the lead oxide scale, which resulted in increased lead leaching (Schock and Giani, 2004; Lytle and Schock, 2005). The work of Edwards and Dudi (2004) also showed that chloramines do not form a low-solubility solid on lead surfaces, resulting in a greater probability of lead leaching into drinking water. The ORP brought about by chloramination favours divalent lead solids. Generally, lead solubility and lead release are dependent on pH, alkalinity and corrosion inhibitor (orthophosphate) concentration (Schock et al., 2005b). Thermodynamic models suggest that lead dioxide is relatively insensitive to orthophosphate and alkalinity. For chloramines to have an impact on lead release through the mechanism of ORP, lead dioxide formation and stability must occur. A study by Treweek et al. (1985) also indicated that under some conditions, chloraminated water is more solubilizing than water with free chlorine, although the apparent lead corrosion rate is slower.

Little information has been reported in the literature about the effect of chloramines on copper or iron. Some authors reported that chloramines were less corrosive towards iron than free chlorine (Treweek et al., 1985; Cantor et al., 2003). Hoyt et al. (1979) also reported an increase in red water complaints following the use of chlorine residual instead of chloramines.

No information was found in the reviewed literature linking chloramines and cement pipe degradation.

B.2.2.9 Chloride and sulphate

Studies have shown the effect of chloride on lead corrosion in drinking waters to be negligible (Schock, 1990b). In addition, chloride is not expected to have a significant impact on lead solubility (Schock et al., 1996). However, Oliphant (1993) found that chloride increases the galvanic corrosion of lead-based soldered joints in copper plumbing systems.

Chloride has traditionally been reported to be aggressive towards copper (Edwards et al., 1994b). However, high concentrations of chloride (71 mg/L) were shown to reduce the rate of copper corrosion at pH 7–8 (Edwards et al., 1994a,b, 1996; Broo et al., 1997, 1999). Edwards and McNeill (2002) suggested that this dichotomy might be reconciled when long-term effects are considered instead of short-term effects: chloride would increase copper corrosion rates over the short term; however, with aging, the copper surface would become well protected by the corrosion by-products formed.

Studies have shown the effect of sulphate on lead corrosion in drinking water to be generally negligible (Boffardi, 1988; Schock, 1990b; Schock et al., 1996). Sulphate was found to stifle galvanic corrosion of lead-based solder joints (Oliphant, 1993). Its effect was to change the physical form of the normal corrosion product to crystalline plates, which were more protective.

Sulphate is a strong corrosion catalyst implicated in the pitting corrosion of copper (Schock, 1990b; Edwards et al., 1994b; Ferguson et al., 1996; Berghult et al., 1999). Sulphate was shown to decrease concentrations of copper in new copper materials; however, upon aging of the copper material, high sulphate concentrations resulted in higher copper levels in the experimental water (Edwards et al., 2002). The authors concluded that this was due to the ability of sulphate to prevent the formation of the more stable and less soluble malachite and tenorite scales. However, Schock et al. (1995) reported that aqueous sulphate complexes are not likely to significantly influence cuprosolvency in potable water.

A review of lead levels reported by 365 water utilities, following the implementation of the U.S. EPA Lead and Copper Rule, revealed that higher chloride to sulphate ratios were associated with higher 90th-percentile lead levels at the consumer's tap. The study showed that 100% of the utilities that delivered drinking water with a chloride to sulphate ratio below 0.58

met the U.S. EPA's action level for lead of 0.015 mg/L. However, only 36% of the utilities that delivered drinking water with a chloride to sulphate ratio higher than 0.58 met the U.S. EPA's action level for lead of 0.015 mg/L (Edwards et al., 1999). Dudi and Edwards (2004) also conclusively demonstrated that higher chloride to sulphate levels increased lead leaching from brass due to galvanic connections. High levels of lead in the drinking water of Durham, North Carolina, were found to be the primary cause of elevated blood lead concentrations in a child. This was initially believed to be linked with a change in the secondary disinfectant from chlorine to chloramine. However, upon further investigation, it was determined that a concurrent change in coagulant from alum to ferric chloride increased the chloride to sulphate ratio, resulting in lead leaching from the plumbing system (Renner, 2006; Edwards and Triantafyllidou, 2007).

No clear relationship between chloride or sulphate and iron corrosion can be established from a review of the literature. The studies of Larson and Skold (1958) found that the ratio of chloride and sulphate to bicarbonate (later named the Larson Index) was important (a higher ratio indicating a more corrosive water). Other authors reported that chloride (Hedberg and Johansson, 1987; Velveva, 1998) and sulphate (Velveva, 1998) increased iron corrosion. When sections of 90-year-old cast iron pipes were conditioned in the laboratory with chloride at 100 mg/L, an immediate increase in iron concentrations (from 1.8 to 2.5 mg/L) was observed. Conversely, sulphate was found to inhibit the dissolution of iron oxides and thus yield lower iron concentrations (Bondietti et al., 1993). The presence of sulphate or chloride was also found to lead to more protective scales (Feigenbaum et al., 1978; Lytle et al., 2003). However, neither sulphate nor chloride was found to have an effect on iron corrosion (Van Der Merwe, 1988).

Rapid degradation of cement-based material can be caused in certain cases by elevated concentrations of sulphate. Sulphate may react with the calcium aluminates present in the hydrated cement, giving highly hydrated calcium sulpho-aluminates. These compounds have a significantly larger volume than the initial aluminates, which may cause cracks to appear and reduce the material's mechanical strength. The effect of sulphate may be reduced if chloride is also present in high concentrations (Leroy et al., 1996).

B.2.2.10 Natural organic matter

Natural organic matter (NOM) has apparently been implicated in increasing lead solubility, and some complexation of dissolved lead by organic ligands has also been demonstrated. Some organic materials, however, have been found to coat pipes, thus reducing corrosion; therefore, a reasonable prediction cannot be made about the effect of various NOM on plumbosolvency (Schock, 1990b).

Research in copper plumbing pitting has indicated that some NOM may alleviate the propensity of a water to cause pitting attacks (Campbell, 1954a,b, 1971; Campbell and Turner, 1983; Edwards et al., 1994a; Korshin et al., 1996; Edwards and Sprague, 2001). However, NOM contains strong complexing groups and has been shown to increase the solubility of copper corrosion products (Korshin et al., 1996; Rehring and Edwards, 1996; Broo et al., 1998, 1999; Berghult et al., 1999, 2001; Edwards et al., 1999; Boulay and Edwards, 2001; Edwards and Sprague, 2001). Nevertheless, the significance of NOM to cuprosolvency relative to competing ligands has not been conclusively determined (Schock et al., 1995; Ferguson et al., 1996).

Several authors have shown that NOM decreases iron corrosion rate (Larson, 1966; Sontheimer et al., 1981; Broo et al., 1999). However, experiments conducted by Broo et al. (2001) revealed that NOM increased the corrosion rate at low pH values, but decreased it at high pH values. The authors concluded that this opposite effect was due to different surface

complexes forming under different pH conditions. NOM was also found to encourage the formation of more protective scales (Campbell and Turner, 1983). However, NOM can complex metal ions (Benjamin et al., 1996), which may lead to increased iron concentrations.

Little information was found in the reviewed literature on the relationship between NOM and cement pipe degradation.

B.3 Methods for measuring corrosion

As noted above, there is no direct and simple method to measure internal corrosion of drinking water distribution systems. Over the years, a number of methods have been put forward to indirectly assess internal corrosion of drinking water distribution systems. The Langelier Index has been used in the past to determine the “aggressivity” of the distributed water towards metals. Coupon and pipe rig systems were developed to compare different corrosion control measures. As the health effects of corrosion (i.e., leaching of metals in the distribution system) became a concern, measuring the metal levels at the tap became the most appropriate method to both assess population exposure to metals and monitor corrosion control results.

B.3.1 Corrosion indices

Corrosion indices should not be used to assess the effectiveness of corrosion control programs, as they provide only an indication of the tendency of calcium carbonate to dissolve or precipitate. They were traditionally used to assess whether the distributed water was aggressive towards metals and to control for corrosion. These corrosion indices were based on the premise that a thin layer of calcium carbonate on the surface of a metallic pipe controlled corrosion. Accordingly, a number of semi-empirical and empirical relationships, such as the Langelier Index, the Ryzner Index, the Aggressiveness Index, the Momentary Excess and the Calcium Carbonate Precipitation Potential, were developed to assess the calcium carbonate–bicarbonate equilibrium. However, a deposit of calcium carbonate does not form an adherent protective film on the metal surface. The work of Edwards et al. (1996) has even shown that under certain conditions, the use of corrosion indices results in actions that may increase the release of corrosion by-products. In light of significant empirical evidence contradicting the presumed connection between corrosion and the most common of the corrosion indices, the Langelier Index, the American Water Works Association Research Foundation recommended that the use of corrosion indices for corrosion control practices be abandoned (Benjamin et al., 1996).

B.3.2 Coupons and pipe rig systems

Coupons and pipe rig systems are good tools to compare different corrosion control techniques prior to initiating system-wide corrosion control programs. They provide a viable means to simulate distribution systems without affecting the integrity of the full-scale system. However, even with a prolonged conditioning period for the materials in the water of interest, coupons used in the field or laboratory and pipe rig systems cannot give an exact assessment of the corrosion of larger distribution systems. Such tests cannot reliably reflect population exposure to distribution system contaminants, since too many factors influence contaminant concentration at the consumer’s tap.

The selection of the most appropriate materials for the conditions under study is critical to achieve the most reasonable approximation. The use of new plumbing material in simulators (e.g., pipe rigs) must be deemed to be appropriate for the corrosion of concern. For instance, new copper is appropriate when a water system uses copper in new construction. Leaded brass

faucets are appropriate when permitted under existing regulatory regimes and available to consumers. Conversely, new lead pipe is not appropriate when looking at a system that has old lead service lines or goosenecks/pig-tails with well-developed scales of lead and non-lead deposits. In fact, predicting the behaviour of these materials in response to different treatments or water quality changes may be erroneous if appropriate materials are not selected for the simulator. Although no standards exist for designing simulators, there are publications that can help guide researchers on complementary design and operation factors to be considered when these studies are undertaken (AwwaRF, 1990, 1994).

Coupons inserted in the distribution system are typically used to determine the corrosion rate associated with a specific metal; they provide a good estimate of the corrosion rate and allow for visual evidence of the scale morphology. There is currently no single standard regarding coupon geometry, materials or exposure protocols in drinking water systems (Reiber et al., 1996). The coupon metal used must be representative of the piping material under investigation. The coupons are typically inserted in the distribution system for a fixed period of time, and the corrosion rate is determined by measuring the mass loss rate per unit of surface area. The duration of the test must allow for the development of corrosion scales, which may vary from 3 to 24 months, depending on the type of metal examined (Reiber et al., 1996).

The major drawback of coupons is their poor reproducibility performance (high degree of variation between individual coupon measurements). This lack of precision is due both to the complex sequence of handling, preparation and surface restoration procedures, which provide opportunity for analysis-induced errors, and to the high degree of variability that exists in metallurgical properties or chemical conditions on the coupon surface during exposure (Reiber et al., 1996).

Pipe rig systems are more complex than coupons and can be designed to capture several water quality conditions. Laboratory experiments with pipe rig systems can also be used to assess the corrosion of metals. In addition to measuring mass loss rate per unit of surface area, electrochemical techniques can be used to determine the corrosion rate. Furthermore, pipe rig systems can simulate a distribution system and/or plumbing system and allow for the measurement of contaminant leaching, depending on which corrosion control strategy is used.

These systems, which can be made from new materials or sections of existing pipes, are conditioned to allow for the development of corrosion scales and/or passivating films that influence both the corrosion rate of the underlying metal and the metal release. The conditioning period must allow for the development of corrosion scales, which may vary from 3 to 24 months, depending on the type of metal examined. Due to this variability, 6 months is recommended as the minimum study duration (Eisnor and Gagnon, 2003).

As with coupon testing, there is currently no single standard for the use of pipe rig systems in the evaluation of corrosion of drinking water distribution systems. Eisnor and Gagnon (2003) published a framework for the implementation and design of pilot-scale distribution systems to try to compensate for this lack of standards. This framework identified eight important factors to take into consideration when designing pipe rig systems: test section style (permanent or inserts), test section materials, test section diameter, test section length, flow configuration, retention time, velocity and stagnation time.

B.3.3 Lead monitoring at the tap

Population exposure to contaminants resulting from the internal corrosion of drinking water systems arises from the corrosion of both the distribution system and the plumbing system.

Measuring the contaminant at the tap remains the best means to determine population exposure. The degree to which a system has minimized corrosivity for the contaminant can also be assessed adequately through measuring the contaminant at the tap over time and correlating it with corrosion control activities.

The U.S. EPA recognizes and approves the following four analytical methods for the determination of lead in drinking water: 1) EPA Method 200.8 (U.S. EPA, 1994b), 2) EPA Method 200.9 (U.S. EPA, 1994b), 3) Standard Method 3113B (APHA et al., 2005) and 4) ASTM Method 3559-96D (ASTM, 1996). Triantafyllidou et al. (2007) have recently shown that particulate lead may not be sufficiently dissolved for analysis purposes if it is not acidified for a long enough period of time. Holding times for a minimum of 16 hours after acidification is necessary for lead analysis and heat digestion may be required when particulate lead is present.

Atomic absorption is the most common method for the determination of lead in water, with detection limits ranging from about 0.0006 to 0.001 mg/L (0.6 to 1 µg/L); the practical quantitation limit (PQL) for these methods is stated as 0.005 mg/L (U.S. EPA, 2000, 2006a).

A proprietary differential pulse anodic stripping voltammetry method, Method 1001 (no detection limit stated) by Palintest Inc. of Kentucky (U.S. EPA, 2006a), is also approved for analysis of lead in drinking water.

B.4 Treatment/control measures for lead, copper and iron

This document defines the levels of lead at the tap as the only measure used to initiate or optimize a corrosion control program. Nevertheless, control measures for copper and iron are also described here, since both the corrosion and concentrations of these metals will be largely influenced by the corrosion control method chosen.

Corrosion of drinking water systems and the release of contaminants into the conveyed water depend on both the material that is subject to corrosion and the water that comes in contact with the material. The contact time of the water with the material greatly influences the level of metals present in the drinking water. Therefore, a first mechanism of defence to reduce exposure to contaminants from drinking water is to flush the plumbing materials prior to human consumption of the water.

Drinking water can also be made less corrosive by adjusting its pH or alkalinity or by introducing corrosion inhibitors. Corrosion inhibitors and pH and/or alkalinity adjustments to control lead, copper and/or iron levels in drinking water should be employed with caution. Pilot studies should be conducted to determine the effectiveness of the corrosion control method chosen for the particular conditions prevailing in the distribution system. Furthermore, even though a particular method is effective in reducing lead, copper and/or iron levels in pilot tests, it might not be effective in practice when it is exposed to the particular conditions of the distribution system. Thus, rigorous full-scale monitoring should also be conducted before, during and following the initiation or optimization of a system's corrosion control program.

Reducing exposure to heavy metals can also be achieved, as an interim measure, by the use of certified drinking water treatment devices.

B.4.1 Materials in drinking water distribution systems

The judicious selection of materials (i.e., materials that contain little lead, such as lead-free solders, low-lead fittings or in-line devices) is one of the possible means to reduce population exposure to the contaminants of concern. For example, the use of lead-free solders ensures that less lead is found in the drinking water as a result of solder corrosion. Since 1990,

the National Plumbing Code of Canada has prohibited lead solders from being used in new plumbing or in repairs to plumbing for drinking water supplies. Lead up to a maximum of 0.2% is still allowed in lead-free solders under the National Plumbing Code (NRCC, 2005).

Full replacement of the lead service line can significantly reduce lead concentrations at consumer's taps. Partial lead service line replacements i.e., replacing only the utility or consumer's portion, can also reduce lead concentrations. However, lead levels typically do not decrease as significantly as with full service line replacement (U.S. EPA, 2004a). Both full and partial lead service line replacement can, however, disturb or dislodge existing lead scales, and result in a significant temporary increase in lead levels at the tap (U.S. EPA 2004a; Renner, 2007). This increase can occur for 3 or more months after replacing the lead service line. Partial replacement may also induce galvanic corrosion at the site where new copper piping is attached to the remaining lead pipe. Generally, utilities should make every effort to encourage consumers to replace their portion of the lead service line. Corrosion control measures that include partial or full replacement of the lead service line should ensure that appropriate flushing is conducted after the replacement and that debris is subsequently cleaned from the screens or aerators of outlets. Good record keeping of partial replacements is also strongly recommended for future reference (U.S. EPA, 2004a). The water quality at the consumer's tap should be monitored closely following both full and partial replacement, especially for the first month after replacement. Appropriate flushing should be conducted after the replacement of the service line and when elevated levels of lead are observed. Reducing exposure to lead can also be achieved, as an interim measure, by the use of drinking water treatment devices. It must be noted that in situations where high levels of lead are possible after replacement, drinking water treatment devices may have reduced capacity and require more frequent replacement.

Health Canada recommends that, where possible, water utilities and consumers use drinking water materials that have been certified as conforming to the applicable NSF International (NSF)/American National Standards Institute (ANSI) health-based performance standard (NSF/ANSI Standard 61 applies to drinking water system components) (NSF International, 2007). These standards have been designed to safeguard drinking water by helping to ensure material safety and performance of products that come into contact with drinking water.

A recent study by Dudi et al. (2004) used the NSF/ANSI Standard 61 Section 8 testing protocol to assess the lead leaching of in-line devices such as meters and shut-off valves. The study showed that in-line devices exposed to non-aggressive tap water leached less lead than in-line devices exposed to the protocol's pH 5 water. In-line devices leached at least 4 times less lead than brass hose bibs and 3.5 times less lead than pure lead pipes using the pH 5 water. This was attributed to the fact that the protocol's pH 5 water contains 20–100 times more phosphate (a corrosion inhibitor) than is usually added to water by utilities to control lead leaching from drinking water. The authors concluded that there is no guarantee that the current protocol used by NSF/ANSI Standard 61 to measure lead leaching from in-line devices has anything to do with real water exposures, especially over long-term exposures.

In response to the questions raised by Dudi et al. (2004), statements of clarification are being added to the NSF/ANSI Standard 61 protocol to indicate that it is intended to assess the leaching potential for a group of metals, including lead. The standard's testing protocol is conducted at pH 5 and pH 10 to account for a variety of metals; metal analysis for both conditions must be met in order for a device or component to be certified under this standard. In the case of lead, a pH of 10 is considered to be aggressive.

B.4.2 Controlling pH and alkalinity

The adjustment of pH at the water treatment plant is the most common method for reducing corrosion in drinking water distribution systems and leaching of contaminants in the distributed water. Raising the pH remains one of the most effective methods for reducing lead and copper corrosion and minimizing lead, copper and iron levels in drinking water. Experience has shown that the optimal pH for lead and copper control falls between 7.5 and 9.5. The higher spectrum of this pH range would also be beneficial in reducing iron levels, but may favour iron corrosion and tuberculation. Although increasing alkalinity has traditionally been recommended for corrosion control, it is not clear if it is the best means to reduce levels of lead and copper in drinking water. The literature appears to indicate that the optimal alkalinity for lead and copper control falls between 30 and 75 mg/L as calcium carbonate. Higher alkalinity (>60 mg/L as calcium carbonate) is also preferable for the control of iron corrosion, iron level and red water occurrences. Moreover, alkalinity serves to control the buffer intensity of most water systems; therefore, sufficient alkalinity is necessary to provide a stable pH throughout the distribution system for corrosion control of lead, copper and iron and for the stability of cement-based linings and pipes.

B.4.3 Corrosion inhibitors

Two predominant types of corrosion inhibitors are available for potable water treatment: phosphate- and silicate-based compounds. The most commonly used inhibitors include orthophosphate, polyphosphate (typically, blended polyphosphates) and sodium silicate, each with or without zinc.

The successful use of corrosion inhibitors is very much based on trial and error and depends on both the water quality and the conditions prevailing in the distribution system. The effectiveness of corrosion inhibitors is largely dependent on maintaining a residual of inhibitors throughout the distribution system and on the pH and alkalinity of the water.

Measuring the concentration of inhibitors within the distribution system is part of any good corrosion control practice. Generally, direct correlations between the residual concentration of inhibitors in the distribution system and the levels of lead, copper and/or iron at the tap are not possible.

Health Canada recommends that, where possible, water utilities and consumers use drinking water additives, such as corrosion inhibitors, that have been certified as conforming to the applicable NSF/ANSI health-based performance standard or equivalent. Phosphate- and silicate-based corrosion inhibitors are included in NSF/ANSI Standard 60, Drinking Water Treatment Chemicals — Health Effects (NSF International, 2005). These standards have been designed to safeguard drinking water by ensuring that additives meet minimum health effects requirements and thus are safe for use in drinking water.

Recently, the use of tin chloride as a corrosion inhibitor for drinking water distribution systems has been added to NSF/ANSI Standard 60. However, very few experimental data on this inhibitor exist. Under certain conditions, this inhibitor reacts with the metal present at the surface of the pipe or the corrosion by-products already in place to form a more insoluble deposit on the inside walls of the pipe. Since the deposits are less soluble, levels of metals at the tap are reduced.

B.4.3.1 Phosphate-based inhibitors

Orthophosphate and zinc orthophosphate are the inhibitors most often reported in the literature as being successful in reducing lead and copper levels in drinking water (Bancroft, 1988; Reiber, 1989; Boffardi, 1993; Johnson et al., 1993; Dodrill and Edwards, 1995; Rezanian and Anderl, 1995, 1997; Schock et al., 1995; Boireau et al., 1997; MacQuarrie et al., 1997; Churchill et al., 2000; Schock and Fox, 2001; Becker, 2002; Dudi and Edwards, 2004; Kirmeyer et al., 2004). Some authors reported that the use of orthophosphate may reduce copper levels in the short term, but that in the long term the formation of more stable scales such as malachite and tenorite may be prevented (Schock and Clement, 1998; Edwards et al., 2001; Cantor et al., 2003). There is evidence that ineffective treatment for lead and copper with phosphate was successful when higher dosages were applied or when pH and orthophosphate dosages were optimized (Schock et al., 1996; Schock and Fox, 2001). Schock and Fox (2001) demonstrated successful copper control in high-alkalinity water with orthophosphate when pH and alkalinity adjustments were not successful. Typical orthophosphate residuals are between 0.5 and 3.0 mg/L (as phosphoric acid) (Vik et al., 1996).

Solubility models for lead and copper indicate that the optimal pH for orthophosphate film formation is between 6.5 and 7.5 on copper surfaces (Schock et al., 1995) and between 7 and 8 on lead surfaces (Schock, 1989). A survey of 365 water utilities under the U.S. EPA Lead and Copper Rule also revealed that utilities using orthophosphate had significantly lower copper levels only when pH was below 7.8 and lower lead levels only when pH was below 7.4 and alkalinity was below 74 mg/L as calcium carbonate (Dodrill and Edwards, 1995).

Several authors reported that orthophosphate reduced iron levels (Benjamin et al., 1996; Lytle and Snoeyink, 2002; Sarin et al., 2003), iron corrosion rates (Benjamin et al., 1996; Cordonnier, 1997) and red water occurrences (Shull, 1980; Cordonnier, 1997). Phosphate-based inhibitors, especially orthophosphate, were also shown to reduce heterotrophic plate counts and coliform bacteria in cast iron distribution systems by controlling corrosion. It was observed in an 18-month survey of 31 water systems in North America that distribution systems using phosphate-based inhibitors had fewer coliform bacteria than systems that did not have corrosion control (LeChevallier et al., 1996). Similarly, orthophosphate treatment at the rate of 1 mg/L applied to a highly corroded reactor made of cast iron immediately reduced iron oxide release and bacterial count in the reactor's water (Appenzeller et al., 2001).

The chloride, sulphate and orthophosphate salts of zinc have been found to provide substantial protection of asbestos-cement pipe when proper concentrations and pH ranges are maintained throughout the distribution system (Leroy et al., 1996). Zinc coats the pipe and protects it against fibre release and water attack. It is postulated that the zinc initially reacts with the water to form a zinc-hydroxycarbonate precipitate such as hydrozincite $[Zn_5(CO_3)_2(OH)_6]$. The zinc solid may then react with the pipe surface. A study of lead and asbestos-cement pipes in a recirculation system demonstrated that orthophosphate salt containing zinc provided corrosion inhibition for both types of pipe materials at pH 8.2 (Leroy et al., 1996).

Several authors reported that the use of polyphosphate could prevent iron corrosion and control iron concentrations (McCauley, 1960; Williams, 1990; Facey and Smith, 1995; Cordonnier, 1997; Maddison and Gagnon, 1999). However, polyphosphate does not act towards iron as a corrosion inhibitor but as a sequestrant, causing a decrease in the visual observation of red water (Lytle and Snoeyink, 2002). According to McNeill and Edwards (2001), this led many researchers to conclude that iron by-products had decreased, when in fact the iron concentrations or the iron corrosion rates may have increased.

The use of polyphosphate was reported as being successful at reducing lead levels in some studies (Boffardi, 1988, 1990, 1993; Lee et al., 1989; Hulsmann, 1990; Boffardi and Sherbondy, 1991). However, it was also reported as being ineffective at reducing lead concentrations and even detrimental towards lead in some circumstances (Holm et al., 1989; Schock, 1989; Holm and Schock, 1991; Maas et al., 1991; Boireau et al., 1997; Cantor et al., 2000; Edwards and McNeill, 2002). McNeill and Edwards (2002) showed that polyphosphate significantly increased lead in 3-year-old pipes for both 8-hour and 72-hour stagnation times. Increases in lead concentrations by as much as 591% were found when compared with the same conditions without inhibitors. The authors recommended not using polyphosphate to control for lead. Only limited data are available on the impact of polyphosphate on copper solubility. In a case study of three water utilities, Cantor et al. (2000) reported that the use of polyphosphate increased copper levels at the tap. In a copper pipe rig study, Edwards et al. (2002) reported that although polyphosphate generally reduced soluble copper concentrations, copper concentrations significantly increased at pH 7.2 and alkalinity of 300 mg/L as calcium carbonate, since polyphosphates hinder the formation of the more stable malachite scales.

B.4.3.2 Silicate-based inhibitors

Only limited data are available on the impact of sodium silicate on lead and copper solubility. As sodium silicate is a basic compound, it is always associated with an increase in pH, making it difficult to attribute reductions in lead or copper concentrations to sodium silicate alone when an increase in pH may also result in a decrease in lead and copper concentrations.

A study conducted by Schock et al. (2005a) in a medium-size utility was able to solve problems from iron in source water as well as lead and copper leaching in the plumbing system. The problems were solved simultaneously through the addition of sodium silicate with chlorination. Sodium silicate was added to the three wells that contained elevated levels of iron and manganese and that serviced homes containing lead service lines. A fourth well required only chlorination and pH adjustment with sodium hydroxide. At the three wells, an initial silicate dose of 25–30 mg/L increased the pH from 6.3 to 7.5 and immediately resulted in 55% and 87% reductions in lead and copper levels, respectively. An increase in the silicate dose to 45–55 mg/L increased the pH to 7.5 and resulted in an even greater reduction in the lead and copper levels (0.002 mg/L and 0.27 mg/L, respectively). It is also interesting to note that the quality of the water after treatment, as it relates to colour and iron levels, was equal or superior to that prior to treatment. However, the use of sodium silicate alone was not shown conclusively in the literature to reduce lead or copper concentrations.

Between 1920 and 1960, several authors reported reductions in red water occurrences when using sodium silicate (Tresh, 1922; Texter, 1923; Stericker, 1938, 1945; Loschiavo, 1948; Lehrman and Shuldener, 1951; Shuldener and Sussman, 1960). However, a field study conducted in the distribution network of the City of Laval, Quebec, in the summer of 1997 revealed no beneficial effects of using low levels of sodium silicate (4–8 mg/L; pH range of 7.5–8.8) to control iron concentrations in old cast iron and ductile iron pipes. A camera inserted inside a cast iron pipe 1) prior to the injection of sodium silicate, 2) prior to the injection of sodium silicate and immediately following the mechanical removal of the tubercles and 3) after 5 months of sodium silicate use revealed that no reductions in the degree of tuberculation or the prevention of the formation of tubercles were found using sodium silicates at these low concentrations (Benard, 1998). Although very few studies have proven the efficiency of sodium silicates as corrosion inhibitors or their true mechanism of action, manufacturers recommend

that a large dose of sodium silicate be initially injected to form a passivating film on the surface of the pipe. Manufacturers recommend concentrations ranging from 20 to 30 mg/L; once the film is formed, concentrations from 4 to 10 mg/L are recommended to maintain this film on the surface of the pipes (Katsanis et al., 1986).

Experiments that studied effects of high levels of silica at different pH found that at pH 8, silica may play a role in the stabilization of cement pipe matrix by interfering with the formation of protective ferric iron films that slow calcium leaching (Holtschulte and Schock, 1985).

B.4.4 Flushing and maintenance

Since the level of trace metals increases upon stagnation of the water, flushing the water present in the plumbing system can significantly reduce the levels of lead and copper. In that respect, flushing can be seen as an exposure control measure. A study by Gardels and Thomas (1989) showed that 60–75% of the lead leached from common kitchen faucets appears in the first 125 mL of water collected from the faucet. They further concluded that after 200–250 mL, 95% or more of the lead has normally been flushed from faucets (assuming no lead contribution from other sources upstream of the faucet). In a study on contamination of tap water by lead solders, Wong and Berrang (1976) concluded that the first 2 L of water from cold water taps should not be used for human consumption if the water has been stagnant for a day. In Canadian studies, in which the cold water tap of homes was flushed for 5 minutes, no levels of trace metals exceeded their respective Canadian drinking water guidelines at that time (Méranger et al., 1981; Singh and Mavinic, 1991). However, flushing the cold water tap in buildings may not be sufficient to reduce the levels of lead and copper below the guidelines (Singh and Mavinic, 1991; Murphy, 1993). Murphy (1993) demonstrated that the median lead concentration in samples collected from drinking fountains and faucets in schools had increased significantly by lunchtime after a 10 minute flush in the morning. The authors concluded that periodic flushing throughout the day would be necessary to adequately reduce lead concentrations.

When lead service lines are the source of lead, flushing the system until the water turns cold is not an appropriate measure, since it is generally the point at which the water from the service line reaches the consumer. Collection of lead profiles at representative sites by sampling several litres sequentially, can provide significant insights into lead leaching. It can also determine if flushing alone will be successful in reducing lead concentrations and the length of time required for flushing.

In 2000, Washington, DC, utilities switched from chlorine to chloramines as the residual disinfectant in the distribution system. This caused very high levels of lead to leach, primarily from the service lines. Data collected during this corrosion crisis revealed that lead levels were not at the highest level in the first-draw samples at some homes, but were sometimes highest after 1 minute of flushing (Edwards and Dudi, 2004). Samples collected after flushing were found to contain lead concentrations as high as 48 mg/L. In some cases, the concentration of lead in samples did not return to safe levels even after 10 minutes of flushing. In the end, Washington, DC, utilities advised its consumers to flush their water for 10 minutes prior to consumption and provided them with filters to remove lead (Edwards and Dudi, 2004). Flushing strategies included showering, laundry, toilet flushing or dishwashing prior to consuming the water first thing in the morning. It should be noted that in some cases flushing may not be sufficient to reduce lead concentrations at the tap. Therefore, utilities should conduct the appropriate monitoring to ensure that flushing is an appropriate measure before recommending flushing to consumers.

Good practice also calls for the flushing of larger distribution systems on a regular basis, especially in dead ends, to get rid of loose corrosion by-products and any attached microorganisms.

Maintenance activities such as the routine cleaning of debris from aerators or screens on faucets may also be important for reducing lead levels at the tap. Debris on aerators or screens can include particulate lead which can be abraded and pass through the screen during periods of water use. This can result in a significant increase of particulate lead in the water from the tap which can be variable and sporadic. Depending on the type of particulate lead present, elevated lead concentrations can also be difficult to accurately measure depending on the preparation method that is used for sample analysis (Triantafyllidou et al., 2007) . For these reasons, it is also important to ensure that sampling is done with the aerator or screen in place so that potential particulate lead contributions may be detected.

B.4.5 Drinking water treatment devices

Drinking water treatment devices can be installed at the point of entry or point of use in both residential and non-residential settings to further reduce contaminant concentrations. Since the concentrations of lead, copper and iron may increase in plumbing systems, and because exposure to these contaminants from drinking water is only a concern if the contaminants are ingested (i.e., inhalation and dermal absorption are not significant routes of exposure), point-of-use treatment devices installed at drinking water taps are considered to be the best approach to reduce concentrations to safe or aesthetic levels immediately before consumption.

Health Canada does not recommend specific brands of drinking water treatment devices, but it strongly recommends that consumers look for a mark or label indicating that the device or component has been certified by an accredited certification body as meeting the appropriate NSF/ANSI drinking water material standards. These standards have been designed to safeguard drinking water by helping to ensure the material safety and performance of materials that come into contact with drinking water. Certification organizations provide assurance that a product conforms to applicable standards and must be accredited by the Standards Council of Canada (SCC). Certification bodies can certify treatment devices for reduction of lead, copper and iron to the relevant NSF/ANSI standards. These standards list lead and copper as health-based contaminants, whereas iron is listed as an aesthetic-based contaminant. In Canada, the following organizations have been accredited by the SCC to certify drinking water devices and materials as meeting NSF/ANSI standards:

- Canadian Standards Association International (www.csa-international.org);
- NSF International (www.nsf.org);
- Water Quality Association (www.wqa.org);
- Underwriters Laboratories Inc. (www.ul.com);
- Quality Auditing Institute (www.qai.org);
- International Association of Plumbing & Mechanical Officials (www.iapmo.org).

An up-to-date list of accredited certification organizations can be obtained from the SCC (www.scc.ca).

Table 3 illustrates the water treatment technologies used in treatment devices that are capable of reducing lead, copper and iron levels in drinking water.

Table 3: Water treatment technologies for the reduction of lead, copper and iron^a

Contaminant	Treatment technology	NSF/ANSI Standard	Reduction claim	
			Influent (mg/L)	Effluent (mg/L)
Lead	Adsorption (i.e., carbon/charcoal)	53	0.15	0.010
	Reverse osmosis	58	0.15	0.010
	Distillation	62	0.15	0.010
Copper	Adsorption (i.e., carbon/charcoal)	53	3	1.3
	Reverse osmosis	58	3	1.3
	Distillation	62	4	1.3
Iron	Adsorption (i.e., carbon/charcoal)	42 (aesthetic)	3–5	0.3

^a Source: NSF International (2006).

B.5 Rationale for monitoring programs for assessing corrosion

The sampling protocols and action levels for the monitoring protocols presented below are based on an understanding of the variations in lead concentrations observed at the tap, which depend on the period of stagnation, the age and source of lead, and other factors such as analytical limitations.

B.5.1 Residential monitoring programs

Previous residential monitoring programs conducted in the United States and Europe have demonstrated that lead levels at the tap vary significantly both across a system and within one site (AwwaRF, 1990, Karalekas et al., 1978; Bailey and Russel, 1981; Shock, 1990a, 1990b; U.S. EPA 1991a). As discussed in section B.2.2, the concentration of lead at the tap depends on a variety of chemical and physical factors including water quality (pH, alkalinity, temperature, chlorine residual, etc.), stagnation time, as well as the age, type, size and extent of the lead based materials. Water use and the volume of water collected have also been identified as important factors affecting the concentration of lead at the tap. Statistically, the greater the variability, the larger the sample population size must be to obtain results that are representative of a system. In addition, when monitoring is conducted to assess the effectiveness of changes in a treatment approach to corrosion control, it is important to reduce the variability in the lead levels at the tap (AwwaRF, 1990). Monitoring programs must, therefore, include controls for the causes of variability in order to obtain results that are representative and reproducible (Schock 1990a; AwwaRF, 1996, 2004; European Commission, 1999).

For residential monitoring programs, sampling considerations should include ensuring that sampling is done at the kitchen tap, with the aerator or screen on and at flow rates typically used (approx. 4-5 L/min) by consumers (van den Hoven and Slatts, 2006). These steps help to ensure that the sample collected is representative of the typical lead concentrations from the tap. In addition, it is recommended that the 4-L samples be taken in 1-L aliquots since this lead profile will help provide the best information on the source of lead.

B.5.2 Determination of sampling protocols and action level for residential monitoring program - option 1 (two tier)

The objectives of the residential monitoring program - option 1 (two tier protocol) are to identify and diagnose systems in which corrosion of lead from a variety of material is an issue; to assess the potential for consumers to be exposed to elevated concentrations of lead; and to assess the quality and effectiveness of corrosion control programs. Consideration of the sampling protocols used in various studies of lead levels at the tap as well as studies on the factors that affect the variability of lead was given in the selection of the residential monitoring program-option 1. A two-tier approach was determined to be an effective method for assessing system-wide corrosion and identifying the highest potential levels of lead. It is also effective in providing the appropriate information for selecting the best corrective measures and evaluating the effectiveness of corrosion control for residential systems in Canada.

In some cases, the responsible authority may wish to collect samples for both tiers during the same site visit. This step eliminates the need to return to the residence if the action level for Tier 1 is not met. The analysis for the second tier are then done only on the appropriate samples, based on the results of the Tier 1 samples.

B.5.2.1 Tier 1 sampling protocol

The first tier sampling protocol determines the contribution of lead at the consumer's tap from the internal plumbing following a period of stagnation and from the transitory contact with the lead service line. A first-draw 1-L sample is taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been stagnant for a minimum of six hours. When more than 10% of the sites (defined as the 90th percentile) have a lead concentration greater than 0.015 mg/L, it is recommended that utilities take corrective measures including conducting additional sampling following the Tier 2 sampling protocol.

The Tier 1 sampling protocol has been widely used for assessing system-wide lead levels and has been demonstrated to be an effective method for identifying systems both with and without lead service lines that would benefit from implementing corrosion control (AwwaRF, 1990, U.S. EPA 1990, 1991a). The U.S. EPA conducted an analysis of extensive system-wide data and determined that if sufficient sites are sampled then a Tier 1 sampling protocol can accurately represent lead concentrations across a systems as well as trigger corrective measures when needed (U.S. EPA 1991a).

Each component of a sampling protocol such as the stagnation time, the volume of water collected and the action level has important implications to the overall assessment of corrosion in a system. Selection of a 6-hour stagnation period is based on reducing the variability in lead levels at the tap as well as ensuring that high lead levels are detected if they occur in a system. The accurate detection of the high lead levels in a system is important so that the appropriate corrective measures can be implemented and it can be demonstrated that corrosion control has been optimized.

A recent review of lead variability at the tap identified stagnation time as the most important physical factor in the consideration of a monitoring program (AwwaRF, 2004). The standard deviation of lead concentrations at the tap typically ranges between 50 and 75 percent (Schock et al., 1990a). Sampling following periods of stagnation that are closest to equilibrium has been demonstrated to reduce the variability in lead levels at the tap (Bailey et al.,1986; U.S. EPA, 1991a). Similarly, U.S. EPA experiments found that the lowest standard deviations of lead

levels over a variety of stagnation times in lead pipe occurred in standing samples greater than six hours (AwwaRF, 1990).

Reducing the variability in lead concentrations at the tap is particularly important in systems where lead levels are close to the action level (0.015 mg/L) and in systems that need to demonstrate optimization. Selection of a stagnation time that is most likely to measure the highest lead levels is important to be able to demonstrate that a reduction in lead concentrations is due to treatment changes (or other corrective measures) rather than due to other factors that affect the variability of lead. Demonstrating that a significant reduction in elevated lead concentrations is due to corrosion control is subsequently important in evaluating if a system has been optimized. In particular, as lead levels decline in a system, the variability also needs to be reduced so that there is an adequate degree of confidence that the decreases in lead levels are due to treatment changes (AwwaRF, 2004).

Lead has also been shown to leach, during no-flow periods, from soldered joints and brass fittings (Neff et al., 1987; Schock and Neff, 1988). Studies examining sources of lead at the tap have found leaded solder and/or brass fittings to be a significant source of elevated lead concentrations following a period of stagnation (Lee et al., 1989; Singh and Mavinic, 1991; AwwaRF, 2004; U.S. EPA, 2007). Depending on the age and type of the material, the concentration of lead from brass fittings have been shown to increase significantly following stagnation periods between 4 and 20 hours (Lytle and Shock, 2000). To increase the likelihood that high lead levels resulting from the corrosion of lead based materials (leaded solder, brass fittings and in-line devices) are detected in a system, it is important to sample following a period of stagnation that approaches an equilibrium value (i.e., after more than 6 hours).

The overnight stagnation period can vary considerably between sites, however, the mean overnight stagnation period has been reported to be 7.3 hours (Bailey and Russell, 1981). The most conservative standing time prior to sampling is between 8 and 18 hours, since it reflects peak concentrations of lead. However, this standing time might be difficult to achieve from an operational standpoint. It was shown that only negligible differences in lead concentrations exist between standing times of 8 hours and 6 hours (Lytle and Schock, 2000). Six hours is therefore, selected as the minimum standing time prior to sampling lead at the tap for residential monitoring program-option 1. It should be noted that it is not a requirement for the six hour stagnation time to occur overnight, in order to facilitate the collection of Tier 1 samples from multiple residences in one day, utilities may consider collecting samples from residences that are vacant for six hours during other periods of the day.

Sample volume is also considered to be an important factor in determining lead concentrations at consumers' taps (AwwaRF, 1990, 2004). Elevated lead concentrations have been observed in samples collected from the tap ranging from the 1st litre to the 12th litre depending on the source and location of the lead containing material in the distribution system. Recent studies (Sandvig, 2006; Campbell and Douglas, 2007; Huggins, 2007; Kwan, 2007; U.S. EPA, 2007; Craik et al., 2008) have indicated that the largest contribution of lead at the tap generally occurs in samples that are representative of water that has been stagnant in a lead service line. However, collection of multiple litres of water from each site is generally considered onerous and, therefore, a smaller volume of water is often collected for conducting system wide corrosion assessments. Several studies have indicated that collection of a one litre sample following a six-hour stagnation period is effective at assessing system wide corrosion levels (Frey, 1989; Lee et al., 1989; U.S. EPA, 1991a). Collection of one litre determines the lead concentration resulting from contact with plumbing material that may contain lead such as

brass fittings and lead solder following a period of stagnation as well as water that has been in transitory contact with a lead service line, if present. Data collected from several utilities in the United States indicates that lead concentrations in the first litre of water can be significantly elevated due to contributions from both the internal plumbing as well as the lead service line. The data indicated that the concentration of lead in the first litre of water from residences with lead service lines compared with residences without a lead service line were significantly higher and was dependent on the water quality (Karalekas et al., 1978; U.S. EPA, 1990, 1991a). A recent study conducted by a Canadian utility also demonstrated that lead concentrations in the first litre at residences with lead service lines is significantly higher than in residences with non-lead service lines (Craik et al., 2008). Therefore, a one litre sample volume is selected for the Tier 1 sampling protocol since it provides informative data for assessing corrosion and is also practical for sample collection and analysis.

The action level for the Tier 1 sampling protocol is based on the concentration of lead in the site representing the 90th percentile value, as measured during a monitoring event. Additional information on how to determine the 90th percentile is provided in section C.2. A 90th percentile value of 0.015 mg/L is selected on the basis of an analysis of lead concentrations across many systems conducted by the U.S. EPA (1990, 1991a). In the promulgation of the final Lead and Copper Rule, the EPA analyzed data of lead levels at the tap collected from 39 medium size systems (over 100, 000 sampling sites) representing a variety of water qualities. The data indicated that over 80 % of the systems without lead service lines were able to achieve 90th percentile lead concentrations of 0.015 mg/L with pH adjustment or the addition of corrosion inhibitors. Systems with lead service lines had substantially higher lead levels and only 25% of the systems were able to meet an action level of 0.015 mg/L, however, in these cases additional corrective measures such as lead service line replacement were considered appropriate.

Selection of a 90th percentile value of 0.015 mg/L for the Tier 1 action level is also based on analytical limitations. A 90th percentile value of 0.015 mg/L is chosen because it does not require assumptions concerning values less than the practical quantitation limit (PQL) of the analytical methods of 0.005 mg/L. As data for lead in drinking water is generally a log-normal distribution, a large number of lead values from a system would be expected to be below the PQL for lead. If an average value were to be used, the analytical uncertainties and/or assumptions associated with values below the PQL could influence the results. The 90th percentile value of 0.015 mg/L is also chosen as the most conservative value, since it corresponds approximately to an average lead concentration of 0.005 mg/L (U.S. EPA, 1991a). Concentrations of lead of 0.005 mg/L are considered to be maximum background levels found in water leaving the drinking water treatment plant. Lead concentrations greater than 0.005 mg/L indicate that the elevated levels of lead are being contributed from brass fittings or meters, lead solder in plumbing and/or lead service lines present in the distribution or internal plumbing system.

The Tier 1 action level is intended to trigger corrective measures including conducting additional sampling. In cases where less than 10% of sites (defined as the 90th percentile) have lead concentrations above 0.015 mg/L, utilities should provide consumers in residences with a lead concentration above 0.010 mg/L information on methods to reduce exposure to lead. These measures can include flushing the appropriate volume of water prior to consumption following a period of stagnation, and checking screens/aerators for debris which may contain lead, such as lead solder, and replacing their portion of the lead service line. It is also recommended that

utilities conduct follow-up sampling for these sites to assess the effectiveness of the corrective measures undertaken by the consumer.

This sampling protocol will provide utilities with the water quality information needed to protect the most sensitive populations from unsafe concentrations of lead by determining if consumers need to be educated to flush their drinking water systems after periods of stagnation. The samples collected are also used from an operational standpoint to determine if the water distributed has a tendency to be corrosive towards lead or not and if so, to help determine the next steps that should be taken in implementing a corrosion control program. The Tier 1 sampling technique is considered to be the most informative when compared with other routine sampling techniques and should be used to increase the likelihood that system-wide problems with lead will be correctly identified, including the occurrence of elevated concentrations of lead resulting from an overnight stagnation period in a variety of leaded material.

B.5.2.2 Tier 2 sampling protocol

Tier 2 sampling is only required when the first tier sampling identified more than 10% of sites (defined as the 90th percentile) with lead concentrations above 0.015 mg/L. Sampling is conducted at 10 % of the sites sampled in Tier 1, specifically the sites in which the highest lead concentrations were measured. For smaller systems (i.e serving 500 people or less), a minimum of 2 sites should be sampled to provide sufficient lead profile data for the system.

Four consecutive 1-L samples are taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been stagnant for a minimum of six hours. Each 1-L sample is analysed individually to obtain a profile of lead contributions from the faucet, plumbing (lead in solder, brass and bronze fittings, brass water meters, etc.) and a portion or all of the lead service line. Alternatively, utilities that choose to collect four 1-L samples during the site visits for Tier 1 sampling can proceed with analysis of the remaining three 1-L samples once the analysis of the samples identifies the appropriate residences.

The objectives of Tier 2 sampling are to provide information on the source and potentially highest levels of lead, which will help utilities select the best corrective measures. It will also provide the best information for assessing the effectiveness and optimization of the corrosion control program.

In order to obtain information on the potentially highest levels of lead sampling after a period of stagnation is important. In particular, the Tier 2 protocol is intended to capture water that has been stagnant not only in the premise plumbing but also in a portion or all of the lead service line (if present). Similarly to other leaded materials (i.e., leaded solder and brass fittings) lead concentrations of water that has been stagnant in lead pipe, also increases significantly with time periods up to 8 hours. Several factors affect the slope of the stagnation curves for lead pipe in drinking water. Generally, the concentration of lead increases rapidly in the first 300 minutes. The typical stagnation curve for lead pipe is very steep for stagnation times shorter than 6 hours and, therefore, small differences in the amount of time that water is left to stagnate may cause considerable variability in the lead concentration (Kuch and Wagner, 1983; AwwaRF, 1990, 2004; Schock, 1990a).

Another important factor that contributes to lead levels at the tap is found in the volume of water that has been in contact with the lead service line following a period of stagnation. Lead profiling studies conducted in Canada and the United States have indicated that the highest concentration of lead at the tap in residences with lead service lines occurs in samples that are representative of the water that has stagnated in the lead service line (Campbell and Douglas,

2007; Huggins, 2007; Kwan, 2007; U.S. EPA, 2007; Craik et al., 2008). Data from these studies indicates that when water is stagnant in the lead service line for six hours, the maximum concentration of lead can be found between the 4th and 12th litres of sample volume. Generally, substantially elevated lead concentrations were observed in the 4th, 5th or 6th litres of sample volume in a number of studies (Campbell and Douglas, 2007; Douglas et al., 2007; Sandvig, 2007; Craik et al., 2008). Extensive profiling of lead levels in homes with lead service lines in Washington, D.C., following a switch to chloramination, demonstrated that the average mass of lead release (concentration adjusted for actual volume) attributed to the lead service line was 470 µg (73 µg/L) compared with 26 µg (26 µg/L) in the first litre sample and 72 µg (31 µg/L) in samples from the remaining home piping and components prior to the lead service line (U.S. EPA, 2007).

Determining the potential for elevated concentrations of lead from water that has been stagnant in lead service lines is, therefore, an important component of a sampling protocol for assessing corrosion in residential distribution systems and subsequent corrosion control optimization. Comparing samples with the highest lead concentrations before and after corrosion control implementation will provide utilities with essential data in evaluating if treatment has been optimized. This will ultimately help demonstrate that the highest lead levels have been reduced to the greatest extent possible. It is estimated that in Canada collection of a minimum of 4 ×1-L samples following a period of stagnation of 6-hours will increase the likelihood that the highest concentrations of lead will be detected. Since the volume of sample needed to obtain water that has been stagnant in the lead service line will depend on the plumbing configuration at each site, utilities should conduct a broad characterization of the types of high-risk sites to estimate if collection of 4 ×1-L will be sufficient.

Collection of four 1-L samples to be analysed individually is selected, since this will provide a profile of the lead contributions from the faucet, the interior plumbing of the home and in many cases all or a portion of the lead service line. Previous studies have indicated that 95% of the lead contributed from faucets is flushed in the first 200-250 mL. In addition, the contribution from leaded solder can generally be found in the first 2 litres of water flushed from the plumbing system. Collection of four 1-L samples to be analysed individually will, therefore, provide the water supplier with information on both the highest potential lead levels at the tap as well as the source of the lead contamination. This information can then be used to determine the best corrective measures for the system and to provide data to help assess if corrosion control has been optimized.

B.5.3 Determination of sampling protocols and action levels for residential monitoring program-option 2 (lead service line residences)

This protocol is intended to provide jurisdictions in which sampling after a 6-hour stagnation time is not practical and/or regulatory obligations restrict the use of the two tier approach outlined above, with an alternate tool. Option 2 of the residential monitoring programs measures the concentration of lead in water that has been in contact for a transitory and short period of time (30 minutes) with the lead service line as well as with the interior plumbing (e.g., lead solder, leaded brass fittings). Four consecutive 1-L samples are taken at the consumer's cold drinking water tap (without removing the aerator or screen) after the water has been fully flushed for 5 minutes and the water has then been left to stagnate for 30 minutes. Each 1-L sample is analysed individually to obtain a profile of lead contributions from the faucet, plumbing (lead in solder, brass and bronze fittings, brass water meters, etc.) and a portion or all of the lead service

line. If the average lead concentration from the four samples taken at each site is greater than 0.010 mg/L at more than 10% of the sites (90th percentile) during one monitoring event, it is recommended that utilities take corrective measures.

Selection of this protocol as an alternative method for residential monitoring is based on adaptation of a sampling protocol used in a variety of European studies that were intended to estimate the average weekly exposure of consumers to lead at the tap (Baron, 1997, 2001; European Commission, 1999). Although the protocol was used in these studies for estimating the average weekly exposure, it may also be useful for obtaining information on the corrosivity of water towards lead pipe. It is, therefore, presented as a tool that can be used to identify residential sites with lead service lines (LSLs) that may have elevated lead concentrations. As discussed in detail below the protocol has been adapted so that it can be used as a tool for assessing corrosion, however, it is intended to apply to residences with lead service lines only due to the limitations inherent to this protocol.

The European studies evaluated different sampling protocols to identify methods that could be used to estimate the average weekly concentration of lead at a consumer's tap (Baron, 1997, 2001; European Commission, 1999). In the European Commission (1999) study, common sampling methodologies (random daytime, fully flushed and fixed stagnation time) were compared with the composite proportional methodology to determine which one was the most representative of a weekly average amount of lead ingested by consumers. These studies identified the average lead concentration from two 1-L samples collected after the water had been fully flushed for 5 minutes and then left to stagnate for 30 minutes as an effective method for estimating the average lead concentration at a consumer's tap. The use of a 30 minute stagnation time is also considered representative of the average inter-use stagnation time of water in a residential setting (European Commission, 1999; Baron 2001; van den Hoven, 2006).

The European studies from which this protocol was adapted also analyzed the data to determine if a 30 minute stagnation protocol could be used for identifying areas in a system that may have elevated lead concentrations. The authors concluded that if a sufficient number of samples were taken to provide statistically valid data, then collection of two consecutive litres of water following a 30 minute stagnation period could potentially be used for conducting assessments of systems or areas in a system in which corrosion control should be implemented (European Commission, 1999; van den Hoven and Slaats, 2006).

An important aspect of these studies is that a large percentage of the sites that were monitored had internal lead plumbing and/or a lead service line and the authors concluded that eighty percent of the properties that were not accurately detected as problem properties had lead service pipes and more than 5 metres of non-lead internal plumbing (copper, galvanized steel or plastic). The studies indicated that collection of two consecutive 1-L samples of water would underestimate the average weekly exposure of consumers from these types of sites and that the collection of a larger volume of water would be needed to detect problem properties but a volume was not specified. In addition, since 60 % of the sites sampled in the European study had lead service lines and/or internal lead piping, sampling water that had been stagnant for 30 minutes in lead pipes was identified as a critical aspect of accurately identifying properties in which elevated lead concentrations may occur using this protocol.

Results of lead profiling from two Canadian utilities indicate that the concentration of lead in the 4th, 5th or 6th litre of sample volume (lead service line) following a period of stagnation of 30 minutes are higher than the concentrations in the 1st and 2nd litres (Campbell and Douglas, 2007; Douglas et al., 2007; Craik et al., 2008). Increasing the volume of water collected used in

the European studies collected to four consecutive 1-L samples should enable utilities to obtain a better understanding of systems in which corrosion of lead service lines may be an issue.

Data of lead levels at the tap in two Canadian cities, determined using a variety of sampling protocols, support the use of a protocol in which four consecutive 1-L samples are collected following a 30 minute stagnation period as a tool for identifying residences in which elevated lead concentrations may occur due to corrosion from a lead service line (Douglas et al., 2007; Craik et al., 2008). These studies found that, in general, contributions from the lead service line can be detected following a 30 minute stagnation time in the samples ranging from the 3rd to 6th litre. Therefore, this protocol is presented as an option for utilities that wish to conduct a residential monitoring program for sites with lead service lines. This method has not, however, been verified as being effective for assessing corrosion of distribution system materials other than lead service lines or internal lead plumbing. There is no data to indicate that it would be effective in assessing corrosion problems where only lead solder, brass fittings containing lead, piping or other leaded material are present in the plumbing system.

The action level for residential monitoring program-option 2 is based on the guideline value for lead, the MAC of 0.010 mg/L. If the average concentration of lead in the four samples from the same site is greater than 0.010 mg/L at more than 10% of the sites (90th percentile) then responsible authorities need to implement corrective actions. The average concentration of lead is used for comparison with 0.010 mg/L since it is believed that this will more accurately detect systems that will benefit from the implementation of corrosion control. Analysis of limited data from a Canadian utility (Campbell and Douglas, 2007) that has implemented corrosion control suggests that comparison of each individual sample to 0.010 mg/L may result in inappropriate conclusions regarding the need for treatment. An average value is, therefore, believed to be a more appropriate value for comparison with the action level. However, analysis of each individual litre of water collected is recommended so that a better understanding of the source of lead and the potentially higher lead concentrations can be obtained and used to select the appropriate corrective measures for the system.

In cases where less than 10% of sites have average lead concentrations above 0.010 mg/L, utilities should provide consumers in residences with an individual sample concentration above 0.010 mg/L of lead, information on methods to reduce exposure to lead. It is also recommended that utilities conduct follow-up sampling for these sites to assess the effectiveness of the corrective measures undertaken by the consumer.

Since this protocol is being used for assessing corrosion after a short period of stagnation contact with the lead service line is critical for increasing the likelihood that elevated lead concentrations will be detected if they occur. In cases where a utility is aware that the lead service line may only be captured with a greater sample volume, collection of four 1-L samples should be considered a minimum. Responsible authorities should be aware of the limitations of this protocol and should incorporate the practice of assessing potentially higher lead levels through sampling after a 6-hour stagnation. A reduced subset of 6 hour stagnation samples should be taken before and after corrosion control measures to ensure an accurate assessment of corrosion in the system and optimization of corrosion control.

B.5.3.1 Limitations

In general, the objectives of a residential monitoring program are to identify and diagnose systems in which corrosion of lead from a variety of material is an issue; to assess the potential for consumers to be exposed to elevated concentrations of lead; and to assess the

quality and effectiveness of corrosion control programs. The residential monitoring program-option 2 for residences with lead service lines has not been assessed for these purposes, rather it is intended as a tool for identifying elevated lead concentrations at residences with lead service lines. It is important to note that this sampling protocol has not been evaluated to determine its effectiveness for detecting corrosion of other plumbing materials nor does it measure the potentially higher levels of lead that may be present in water stagnating for longer periods in the household plumbing and lead service lines.

Studies indicate that concentrations of lead approach an equilibrium value between 5 and 7 hours of stagnation depending on the diameter of the pipes (5/8 inch and 3/4 inch). In addition, the concentration of lead increases exponentially in the first 300 minutes of stagnation in lead pipe. Lead contributions from other material such as leaded brass fittings and lead solder has also been found to increase significantly following 4-20 hours of stagnation. There is limited field data comparing lead levels at the tap following different periods of stagnation and therefore, it is difficult to evaluate if a 30 minute stagnation period is accurate for assessing corrosion. Limited studies suggest that lead concentrations following a period of stagnation of 30 minutes are substantially lower in the equivalent sample volume than those measured at the same tap following six hours of stagnation (AwwaRF, 1990; Douglas et al., 2007; Craik et al., 2008). Therefore, the possibility of underestimating the highest concentration of lead at consumer's taps may be significant when using a stagnation time of 30 minutes.

In 1990, the U.S. EPA analyzed extensive system-wide studies of lead levels at the tap determined by collection of a one litre sample following six hours of stagnation (first-draw) (U.S. EPA 1990 and 1991a). The analysis indicated that 1-L first-draw sampling was effective at identifying elevated lead concentrations from materials other than lead service lines in utilities with a pH lower than 8 or that were not adding corrosion inhibitors. In analysing the data in the EPA document (U.S. EPA, 1991a) it is apparent that a six hour stagnation period is an essential component of the sampling protocol. A large number of systems had lead concentrations between 15-30 µg/L and at these lower concentrations, a shorter stagnation period may not have detected the problems in these systems. A similar observation can be made from one litre samples collected after a minimum of six hours stagnation from lead service lines in 11 different systems. The EPA analysis of this data determined 48 % of these systems had 90th percentile lead concentrations below 30 µg/L (0.030 mg/L) and 25 % of the systems had concentrations between 10 µg/L (0.010 mg/L) and 30 µg/L (0.030 mg/L) (U.S. EPA, 1991a). These data suggest that a longer stagnation time is important for accurately identifying systems that would benefit from corrosion control in the lower lead level range.

Several recent studies indicate the important contribution that leaded materials other than lead service lines can make to lead levels at the tap (Kimborough, 2001; U.S. EPA, 2004a). Lead profiling studies conducted in Washington, D.C. following a change from chlorination to chloramination indicated that elevated concentrations of lead from plumbing components such as brass fittings and tin-lead solder can occur when changes are made to the water quality. The average first-draw concentrations of lead from these profiles were 26 µg/L for the first litre and 31 µg/L for the premise plumbing (U.S. EPA, 2007). If sampling had occurred after a shorter stagnation period it is possible that corrosion would not have been accurately assessed under these conditions.

One of the important aspects of a corrosion control program is to assess the quality and effectiveness of corrosion control treatment when it is implemented. Many studies have been conducted which have evaluated the effectiveness of corrosion control treatments by measuring

the levels of first draw lead levels before and after treatment is initiated. By correlating first-draw lead levels and the values of different water quality parameters such as pH, alkalinity and inhibitor concentration, the effectiveness of the treatment can be evaluated (Karalekas et al., 1983, U.S. EPA, 1991a). Comparison of lead concentrations which are closest to maximum values are considered to be essential in order to determine if treatment has been optimized. In particular, systems in which the lead concentrations are only slightly above the action level (0.010 mg/L) may have difficulty demonstrating optimization unless the variability in lead levels in the system is small. Collection of samples after a longer stagnation period when the lead concentrations are likely to be higher may provide more statistically valid data for demonstrating optimization.

The European study from which the 30 minute stagnation period protocol was adapted, recommends various sampling protocols for evaluating the effect of corrosion control treatment versus the effectiveness of measures taken at specific properties such as lead pipe replacement. A 30 minute stagnation period sampling protocol was identified as a suitable protocol for measuring the effectiveness of lead pipe replacement, however, it was not identified as a suitable protocol for assessing corrosion control treatment effectiveness (European Commission, 1999).

B.5.4 Determination of residential monitoring sites

The suggested number of monitoring sites for different system sizes presented in Table 2 are adapted from the U.S. EPA Lead and Copper Rule (LCR) (U.S. EPA, 1991a). In the development of the LCR, the U.S. EPA estimated the minimum number of monitoring sites that would be required to adequately characterize the distribution of lead levels at the tap across a system. As part of this analysis, the U.S. EPA considered the need to ensure that the number of monitoring sites was reasonable for utilities as well as representative of system-wide lead levels at the tap. Data from studies of lead levels at the tap conducted by several utilities in the United States was used as the basis for a statistical analysis of system-wide lead levels. The data used in the analysis was based on first draw one-litre samples following a minimum stagnation period of six hours (AwwaRF, 1990).

The system-wide studies indicated that lead levels at the tap have a lognormal distribution and between twenty-five and forty percent of the locations sampled had lead concentrations greater than 0.015 mg/L. An analysis of the data was conducted using statistical sampling methods such as those used in quality control applications. The results of the analysis determined that the number of monitoring sites provided in Table 2 will correctly identify, with approximately 90% confidence, systems serving more than 100 people in which the 90th percentile lead concentration is greater than 0.015 mg/L (U.S. EPA, 1991b). It should be noted that the U.S. EPA evaluation was conducted using data collected using a 6-hour stagnation sampling protocol and an action level of 0.015 mg/L. Data using a 30 minute stagnation period and an action level of 0.010 mg/L were not evaluated in this context. Therefore, the confidence level that systems with lead concentrations above 0.010 mg/L will be accurately detected using this protocol is not known and cannot be easily estimated without doing a similar analysis with a much larger data set.

Given the variability of lead levels at the tap additional measures are considered appropriate to increase the level of confidence that the suggested number of monitoring sites will detect elevated lead levels at the tap. Targeting high- risk locations such as those with lead service lines within the suggested number of monitoring sites as well as conducting sampling during periods when water temperatures are higher is expected to increase the confidence level

that the entire system has been adequately represented. The EPA indicated that monitoring two times per year and targeting high- risk residences are necessary to increase this level of confidence. This was noted as being particularly important for systems serving 100 people or less.

In the statistical analysis conducted by the EPA it was noted that a 90% confidence level is not achieved with the suggested number of monitoring sites for systems serving fewer than 100 people, however, collecting a larger number of samples was not considered practical for these types of systems. The EPA determined that sampling the suggested number of sites at high-risk locations would, however, be reasonable for representing lead levels in the system (U.S. EPA, 1991b).

B.5.5 Determination of sampling protocols and action levels for non-residential monitoring programs

The objectives of the sampling protocols and action levels for non-residential sites such as child care centres, schools and office buildings are to locate specific lead problems within the building and identify where and how to proceed with remedial actions. The intention is to minimize lead concentrations at the cold drinking water outlets (i.e., fittings/fixtures such as faucets and fountains) used for drinking and cooking and therefore protect occupants from exposure to lead. The sampling protocols and action levels are based on an understanding of the variations in lead concentrations observed at outlets in a non-residential building due to sources of lead within the plumbing and water use patterns.

In some cases, responsible authorities may want to collect Tier 1 and Tier 2 samples at the same time to eliminate the need to return to the site. In this case authorities should be aware that the confidence in some sample results will decrease since flushing water through one outlet may compromise the flushed samples taken from other outlets that are located in close proximity.

B.5.5.1 Tier 1 sampling protocol

A first-draw 250-mL sample is taken at the locations identified in the sampling plan after the water has been stagnant for a minimum of 8 hours but generally not more than 24 hours. To ensure that representative samples are collected, the aerator or screen on the outlet should not be removed prior to sampling. If the lead concentration is equal to or exceeds 0.020 mg/L (lead action level) at any of the monitoring locations, corrective measures should be taken.

The Tier 1 sampling protocol has been used in non-residential settings for locating specific lead issues, determining how to proceed with remedial measures and demonstrating that remediation has been effective. Numerous studies have been published on extensive sampling programs of lead at the tap conducted in schools and other non-residential buildings. These studies demonstrated that collection of 250 mL samples following a period of stagnation of a minimum of 8 hours but generally not more than 24 hours is effective at identifying outlets with elevated lead concentrations (Gneadinger, 1993; Murphy, 1993; Maas et al., 1994; Bryant, 2004; Boyd et al., 2008a, 2008b). Using this sampling method, several studies were able to determine the source of lead within schools and develop a remediation plan (Boyd et al, 2008a, 2008b; U.S. EPA, 2008).

As with residential monitoring programs, each component of a sampling protocol such as the stagnation time, the volume of water collected and the action level has important

implications as to the usefulness of the data collected in non-residential settings. Since the objectives of conducting sampling in non-residential buildings is different than in residential settings, the volume of water collected and the lead action levels are also different.

The Tier 1 and Tier 2 sampling protocols for non-residential sites are based on collection of a 250 mL sample volume. Studies have demonstrated that to evaluate the amount of lead leaching from outlets such as kitchen faucets, more than 95% of the lead can be found in the first 200 to 250 mL of water from the faucet (Gardels and Sorg, 1989). Lead levels in non-residential buildings have generally been found to decrease significantly following flushing of the outlet for 30 seconds. This suggests that the fountain or faucet and the connecting plumbing components can be major contributors to elevated lead concentrations at outlets in non-residential buildings (Bryant, 2004; Boyd et al., 2008a, 2008b). Collection of a larger volume of water, such as 1 litre would include a longer line of plumbing prior to the outlet. This plumbing may contain valves, tees and soldered joints that could contribute to the lead concentration in the 1 litre sample, however, it would not be possible to identify which material was releasing lead. In addition, it is suggested that collecting such a large volume from a drinking water fountain might dilute the initial high concentrations observed in the outlet. This is not desirable since water collected from sections of plumbing further from the outlet typically have lower lead concentrations (U.S. EPA, 2004b). Therefore, collection of a smaller sample volume (250 mL) than those typically used to assess corrosion (one litre and greater) in residential systems is considered important for sampling in non-residential buildings. A 250-mL sample volume is selected for sampling in non-residential buildings as it represents water from the fitting (fountain or faucet) and a smaller section of plumbing and is, therefore, more effective at identifying the source of lead at an outlet (U.S. EPA, 2006b).

As discussed in section B.5.2.1., studies examining sources of lead at the tap have found leaded solder and/or brass fittings to be a significant source of elevated lead concentrations following a period of stagnation (Lee et al., 1989, Singh and Mavinic, 1991, AwwaRF, 2004, U.S. EPA, 2007). Depending on the age and type of the material, the concentration of lead from brass fittings have been shown to increase significantly following stagnation periods between 4 and 20 hours (Lytle and Shock, 2000). As a result, the water use pattern in a building is an important factor in determining lead concentrations at the tap. Since water use patterns are often intermittent in non-residential buildings such as day care centres, schools and office buildings, it is important to sample following a period of stagnation. The most conservative standing time prior to sampling is between 8 and 18 hours, since it is most likely to measure peak concentrations of lead. Therefore, first flush samples should be collected following a minimum period of stagnation of 8 hours but not greater than 24 hours so that they are representative of the longer periods in which outlets are not used for drinking during most days of the week in a non-residential building.

An action level of 0.020 mg/L is based on the premise that a 250-mL first draw sample is being collected that has a smaller volume size than those typically collected to assess corrosion at residential sites which are generally one litre or greater. A direct comparison of the action levels for the residential protocols versus the action level for the non-residential protocols is not possible. However, if additional volumes of water were collected following the initial 250 mL sample (i.e., 250 mL to 1000 mL) it may correspond to a lower concentration in a one litre sample. This is due to the fact that the subsequent volumes would most likely contain lower concentrations of lead than that seen in the initial 250 mL sample and result in a dilution effect (U.S. EPA, 2004b).

Tier 1 sampling is used to identify which outlets in a building may be contributing to elevated lead concentrations. When the action level of 0.020 mg/L is exceeded, interim corrective measures should be taken to protect the health of sensitive populations in situations with exposure patterns such as those found in non-residential buildings. Occupants of the building and other interested parties such as parents should be informed of the results of any sampling conducted in the building.

B.5.5.2 Tier 2 sampling protocol

In order to help identify the source of lead at outlets that exceed the Tier 1 action level, follow-up samples are taken of the water that has been stagnant in the upstream plumbing but not in the outlet itself. The results can then be compared to assess the sources of elevated lead and to determine the appropriate corrective measures. In order to be able to compare the results, a second 250 mL sample is collected following the same period of stagnation. To obtain water that has been stagnant in the plumbing prior to the outlet, a 250-mL sample is taken after a period of stagnation of a minimum of 8 hours but generally not more than 24 hours followed by a 30-second flush. Water fountains and cold water outlets exceeding the Tier 1 action level are re-sampled, in the same year and in the same season. Tier 2 action level is also established at 0.020 mg/L since the sample volume is 250 mL. Thirty second flushing was selected, since it should normally eliminate the water present in the outlet.

If the lead concentration in the second 250-mL sample decreases below 0.020 mg/L, then it can be concluded that the water fountain or the cold drinking water outlet and/or the plumbing in the immediate vicinity is the source of the lead. If concentrations of lead above 0.020 mg/L are found in the Tier 2 samples, then the lead sources may include the plumbing materials that are behind the wall, a combination of both the outlet and the interior plumbing and/or contributions of lead from the service connection. When lead concentrations exceed the Tier 2 action level, immediate corrective measures should be taken and the lead sources should be determined and remediation measures implemented.

The results of Tier 1 and Tier 2 sampling should be interpreted in the context of the plumbing profile so that an assessment of the lead contributions can be made and the appropriate interim and long-term corrective measures can be taken. Competent authorities can develop the plumbing profile using the questions provided in part C. Information on other sampling that can be conducted to help determine the source of lead if it has not been identified as well as detailed information on the interpretation of Tier 1 and Tier 2 sampling results can be obtained from other reference material (U.S. EPA, 2006b).

B.5.6 Determination of non-residential monitoring sites

In general the level of lead in drinking water entering non-residential buildings from a distribution system is low. It is recommended that at each monitoring event, samples be taken from an outlet close to the point where the water enters the non-residential building. This will determine the concentration of lead contributed by the either the service line or the main water distribution system (water main). Ideally, samples should be collected after a appropriate period of flushing so that they are representative of water from the service line and from the water main. The volume of water to flush will depend on the characteristics of the building plumbing system (i.e., the distance between the service line and the water main). In some situations, e.g. where there is a lead service line to the building, it may be difficult to obtain a sample that is

representative of water from the water main due to contributions of lead from the service line. In this case, an alternate sample location may need to be selected.

The occurrence of elevated lead concentrations within buildings such as schools is typically the result of leaching from plumbing materials and fittings and water use patterns (U.S. EPA, 2006b; Boyd et al., 2007; Pinney et al., 2007). Studies evaluating lead levels at drinking water fountains and taps in schools in Canada and the U.S. have demonstrated that levels can vary significantly within buildings and can be randomly distributed (Boyd et al., 2007; Pinney et al., 2007). An evaluation of lead levels in schools in Seattle found that twenty percent of drinking fountains had concentrations of lead above 0.020 mg/L in the first draw 250-mL samples. The lead was attributed to galvanized steel pipe, 50:50 lead:tin solder, brass components such as bubbler heads, valves, ferrules and flexible connectors. As a result it is important to measure lead levels at fountains and outlets used for consumption in non-residential buildings to determine if elevated lead levels may be present and identify where corrective measures are required to protect the health of the occupants.

Although limited information is available on the variability of lead levels at individual fountains and outlets within non-residential buildings, studies have shown that it is not possible to predict elevated levels. The number of monitoring sites that should be sampled in a non-residential building should be based on the development of a sampling plan. A plumbing profile of the building should be completed to assess the potential for lead contamination at each drinking water fountain or cold drinking water or cooking outlet. Competent authorities can develop the plumbing profile using the questions provided in part C. Information in the plumbing profile can then be used to develop a sampling plan that is appropriate for the type of building that is being sampled e.g child care centre and schools versus office buildings.

Authorities that are responsible for maintaining the water quality within non-residential buildings will need to do more extensive sampling at individual outlets based on the sampling plan developed for the building. The sampling plan should prioritize drinking water fountains and cold water outlets used for drinking or cooking based on information obtained in the plumbing profile, including but not limited to, areas containing lead pipe, solder or brass fittings and fixtures, areas of stagnation, and area that provide water to consumers that include infants, children and pregnant women.

When sampling at kitchen taps in non-residential buildings, the aerators and screens should also be left in place and at flow rates typically used (approx. 4-5 L/min). However, for other types of outlets, such as water fountains, lower flow rates are typical and should be used when sampling. These steps help to ensure that the sample collected is representative of the average water quality consumed from the type of outlet being sampled. It is also important to note that opening and closing shut-off valves to fittings and fixtures (i.e., faucets and fountains) prior to sampling has been shown to significantly increase lead concentrations (Seattle Public Schools, 2005). After opening a shut-off valve, outlets should be completely flushed and then allowed to stagnate for the appropriate period of time.

Part C. Acronyms, tables and references

C.1 Acronyms

ANSI	American National Standards Institute
ASTM	American Society for Testing and Materials
CPVC	chlorinated polyvinyl chloride
EC	European Community
EPA	Environmental Protection Agency (United States)
MAC	maximum acceptable concentration
MDL	method detection limit
NOM	natural organic matter
NSF	NSF International
ORP	oxidation–reduction potential
PE	polyethylene
PQL	practical quantitation limit
PVC	polyvinyl chloride
SCC	Standards Council of Canada

C.2 Guidance on determination of 90th percentile

The action levels associated with the residential sampling protocols are based on the concentration of lead in the 90th percentile sample, as measured during a monitoring event. The 90th percentile value can be determined by arranging the results for each monitoring event in ascending order from the site with the lowest lead concentration to the site with the highest lead concentration. For the sampling protocol presented in A.2.2 in which four samples are collected from each site, the average lead concentration is used as the value for the site.

Each site is then assigned a number from #1 for the site with the lowest (average) lead concentration through to the site with the highest lead concentration. The number assigned to the site with the highest lead concentration should be the same as the total number of sites sampled during the monitoring event. The total number of sites sampled in one monitoring event is multiplied by 0.9 to determine the site number that represents the 90th percentile lead concentration (provided in the table below). For systems that only need to collect samples from 5 sites, the average of the value for the 4th highest site and the value for the 5th highest site are used to determine the 90th percentile lead concentration.

Suggested number of monitoring sites and site indicating 90th percentile value ^a

System size (number of people served)	Number of sites (annual monitoring)	Site indicating 90 th percentile value	Number of sites (reduced annual monitoring)	Site indicating 90 th percentile value
>100 000	100	90 th highest site	50	45 th highest site
10 001–100 000	60	54 th highest site	30	27 th highest site
3301–10 000	40	36 th highest site	20	18 th highest site
501–3300	20	18 th highest site	10	9 th highest site
101–500	10	9 th highest site	5	Average of 4 th and 5 th highest site
≤100	5	Average of 4 th and 5 th highest site	5	Average of 4 th and 5 th highest site

^a Adapted from U.S. EPA (1991a).

C.3 Principal factors influencing the corrosion and leaching of lead, copper, iron and cement

Factors	Key effects
Age of the pipes	Leaching of lead, copper, iron and cement usually decreases with aging of distribution materials. Heavily tuberculated aged iron pipes are often a source of red water problems.
Stagnation time	Lead and iron levels at the tap rapidly increase with water stagnation in the plumbing system, but ultimately reach fairly constant levels after 8 or more hours. Copper levels rapidly increase with initial water stagnation, but can then decrease or continue to increase, depending on the oxidant levels. Long residence time may also increase water quality deterioration from cement-based materials.
pH	Lead, copper and iron levels at the tap usually decrease with increasing pH. Higher pH favours iron corrosion and a higher degree of tuberculation. Low pH favours leaching from cement. In turn, cement leaching increases pH.
Alkalinity	Lead and copper levels at the tap usually increase with low alkalinity. Copper levels usually increase with higher alkalinity. Low alkalinity will favour iron leaching. Low alkalinity will favour leaching from cement. In turn, cement leaching will increase alkalinity.
Temperature	No simple relationship exists between lead, copper and iron levels at the tap and temperature.
Calcium	Lead, copper and iron levels at the tap are not significantly influenced by calcium. Low calcium concentration in the drinking water will favour leaching from cement. In turn, cement leaching will increase calcium concentration in the drinking water.
Free chlorine	The presence of chlorine may yield stable lead scales. Free chlorine may increase copper corrosion rates at low pH. Free chlorine may decrease copper corrosion rates at high pH. Free chlorine may increase lead and iron corrosion rates.
Chloramines	Chloramines may dissolve lead scales formed under chlorinated water conditions. The presence of chloramines may yield unstable lead scales. Little information on the effect of chloramines on copper or iron was found.
Chloride and sulphate	Chloride alone has not been shown to conclusively influence lead levels at the tap. Chloride may reduce the rate of copper corrosion up to relatively high concentrations. High concentrations of chloride may cause copper pitting. Lead and copper levels at the tap may not be significantly influenced by sulphate. Sulphate may cause copper pitting. Higher chloride to sulphate ratios may lead to higher lead levels at the tap. No clear relationship exists between chloride or sulphate and iron corrosion. High levels of sulphate may induce the formation of cracks in cement pipes.
Natural organic matter (NOM)	The effects of NOM on levels of lead, copper and iron at the tap are not conclusively determined. NOM may decrease copper pitting and iron corrosion. NOM may increase lead, copper and iron solubility.

C.4 Conditions favouring lead leaching and indicators of lead leaching in drinking water distribution and plumbing systems

C.4.1 At the treatment plant

Condition	Comment
When pH is less than 7.5 or greater than 9.5	Although pH is controlled at the treatment plant, it may vary within the distribution system. Low-pH water has been strongly correlated with higher lead levels at the tap. A pH exceeding 9.5 can lead to an increase in lead solubility.
When alkalinity is less than 30 mg/L	Although alkalinity is controlled at the treatment plant, it may vary within the distribution system. Low-alkalinity water has been correlated with higher lead levels at the tap. In addition, low-alkalinity water offers poor buffering capacity and can jeopardize pH stability.
Treatment change	Any treatment change that will have a chemical, biological or physical impact on the distributed water should be carefully monitored in the distribution system. Lead corrosion and lead levels are easily influenced by small changes in the quality of the water distributed. Lead levels at the tap and within the distribution system should be closely monitored during a treatment change, especially a disinfectant change.
Change from chlorine to chloramines	Changing the residual disinfectant treatment will have an impact on the electrochemical potential and the pH of the water. This, in turn, may destabilize corrosion by-products within the distribution and plumbing systems. Lead levels at the tap and within the distribution system should be closely monitored during a treatment change, especially a disinfectant change.

C.4.2 Within the distribution system

Condition	Comment
Lead-based fittings or in-line devices	Lead in goosenecks/pig-tails, valve parts or gaskets used in water treatment plants or distribution mains can release lead.
Old unlined cast iron pipes	Old unlined cast iron pipes are heavily corroded. The presence of tubercles reduces the diameter of the pipe and offers niches for microorganisms to proliferate. The high surface-to-pipe ratio, long residence time and greater microbiological activity may change the water's pH, alkalinity and chemical balance. These pipes, often present in old sectors, may also be followed by old lead service lines.
Dead ends	Dead ends provide a stagnation period where the contact time between the water and the contaminant is increased. This longer contact time favours microbiological and chemical activity.
Microbiological activity	Biofilms are present in distribution and plumbing systems. The presence of microorganisms will influence the biochemical balance of the water and subsequently influence corrosion.
Nitrification	Nitrification could play a role in depressing pH and increasing lead dissolution, especially when chloramine is used as a secondary disinfectant.
Change in hydraulic flow	A sudden change in hydraulic flow may release solids previously attached as corrosion by-products.
Lead service lines	Lead service lines will continue to leach lead after many years of service. A strong correlation between the period of stagnation and lead release from lead service lines has been established. Partial lead service line replacement may result in temporary increases of lead levels due to filings or hydraulic disturbances, which release solids previously attached as corrosion by-products.

C.4.3 Within the plumbing system

Condition	Comment
Lead service lines	Lead service lines will continue to leach lead after many years of service. A strong correlation between the period of stagnation and lead release from lead service lines has been established. Partial lead service line replacement may result in temporary increases of lead levels due to filings or hydraulic disturbances, which release solids previously attached as corrosion by-products.
Leaded-brass fittings or in-line devices	Leaded brass fittings and in-line devices, including water meters, may contain up to 8% lead. Lead may be released from these devices. Water meters are found in residential homes, but are typically the responsibility of the municipality.
Lead solder	Lead solders may be present in plumbing systems installed prior to 1990. These solders continue to be a source of lead at the tap.
New faucets	Newly installed faucets may contain lead-based brass (up to 8% lead) and be a source of lead for a period of time.
Stagnation time	There is a strong correlation between the period of stagnation and lead release. The lead concentration will peak after 8 hours.

C.4.4 At the tap

Condition	Comment
Consumers' complaints	Consumers' complaints provide a good source of information to determine where lead problems may occur. Complaints may arise from direct concern about lead concentration or indirect aesthetic concerns about the water.
Colour, turbidity or debris	The presence of colour, turbidity or debris at the consumer's tap can be a good source of information with respect to corrosion. Although most often correlated with iron, it may also indicate the presence of conditions favouring lead release.
Lead levels	Lead levels remains the only truly reliable information to evaluate population exposure to lead from drinking water.

C.5 Guidance on prioritizing residential monitoring sites

All provinces and territories use the National Plumbing Code as a basis for their own regulations. Regulations regarding lead used in plumbing materials were phased in across the country, therefore the timing of when lead service lines and other lead-based plumbing materials stopped being used may differ depending on the region. This information is a general guide in selecting sites that may have leaded material in the distribution system including lead solder and brass fittings and fixtures.

Type of Material	Date Material was Prohibited /Limited for Use	Comment
Lead service lines	1975	The National Plumbing Code (NPC) prohibited the use of lead as an acceptable material for pipes in 1975. All provinces and territories use the NPC as a basis for their own regulations. Regulations regarding lead used in plumbing materials were phased in across the country.
Lead solder used in plumbing	1986-1990	Under the NPC, all fittings must comply with standard ASME 112.18.1/CSA B125.1 for plumbing supply fittings (formerly CSA B125.1). The CSA B125.1 standard limited the content of lead solder to $\leq 0.2\%$ in 1986. The 1990 version of the NPC officially prohibited lead solders from being used in new plumbing or in repairs to plumbing.
Lead-containing brass fittings, faucets and valves	Current	Lead-containing brass fittings, faucets and valves may contain up to 8% lead. Studies have found that these types of materials may provide a continuous source of lead in plumbing systems. ASME 112.18.1/CSA B125.1 references NSF/ANSI Standard 61 Drinking Water System Components -Health Effects. NSF/ANSI 61 is a voluntary standard which is designed to safeguard drinking water by ensuring material safety and performance of product that come into contact with drinking water. Material that has not been certified to NSF/ANSI 61 may be a source of lead in plumbing systems.
New plumbing and repairs	Current (within five years)	If new plumbing or repairs are less than 5 years old and materials such as brass faucets were used, elevated lead levels may be found until passivation has occurred (U.S. EPA, 2006b).

C.6 Plumbing profile determination (adapted from U.S. EPA, 2006b)

The following questions will help competent authorities determine whether lead is likely to be a problem in their facility(ies), and will help prioritize sampling efforts.

1. When was the original building constructed? Where any buildings or additions have been added to the original facility, a separate plumbing profile should be completed for each building, addition or wing.
2. If built or repaired since 1990, were lead-free plumbing and solder used in accordance with the National Plumbing Code or the applicable provincial regulation? What type of solders have been used? (Your local plumbing code authority or building inspectors may be able to provide guidance regarding when high-lead material were last used on a regular basis in your area.)
3. When were the most recent plumbing repairs made (note locations)?
4. With what material is the service connection (the pipe that carries water to the school from the public water system's main in the street) made? Note the location where the service connection enters the building and connects to the interior plumbing.
5. Specifically, what are the potable water pipes made of in your facility (note the locations)? Options: lead; galvanized metal; plastic; copper; cast iron; other. Note the location of the different types of pipe, if applicable, and the direction of water flow through the building. Note the areas of the building that receive water first, and which areas receive water last.
6. Do you have tanks in your plumbing system (pressure tanks, gravity storage tanks)? Note the location of the tanks and any available information about the tanks (manufacturer, date of installation.)
7. Was lead solder used in your plumbing system? Note the location of lead solder.
8. Are there fittings such as faucets or valves, that can contain brass that are used in your drinking water system? (Note: Most faucets are brass on the inside) You may want to note the location on a map or diagram of your facility and make extensive notes that would facilitate future analysis of lead samples results.
9. How many of the following outlets provide water for consumption? Note the location.
 - a. Water coolers
 - b. Bubblers
 - c. Ice Makers
 - d. Kitchen Taps
 - e. Drinking Fountains or Tap

-
10. Have the brands and models of water coolers used in the building been checked to see if they may contain lead?
 11. Do outlets that provide drinking water have accessible screens or aerators? (Standard faucets usually have screens. Many coolers and bubblers also have screens). Note the locations.
 12. Have these screens been cleaned? Note the locations.
 13. Can you detect signs of corrosion, such as frequent leaks, rust-coloured water, or stained dishes or laundry? Note the locations.
 14. Is any electrical equipment grounded to water pipes? Note the locations.
 15. Have there been any complaints about water taste (metallic, etc.) or rusty appearance? Note the locations.
 16. Check building files to determine whether any water samples have been taken from your building for any contamination (also check with your public water supplier)
 - a. Name of contaminant(s)?
 - b. What concentrations of these contaminants were found?
 - c. What was the pH level of the water?
 - d. Is testing done regularly at your facility?
 17. Other plumbing questions:
 - a. Are blueprints of the building available?
 - b. Are there known plumbing “dead-ends”, low use areas, existing leaks or other “problem areas”?
 - c. Are renovations being planned for part or all of the plumbing system?

C.7 References

- Anderson, K.E. (1983) Nickel in tap water. *Contact Dermatitis*, 9: 140–143.
- APHA (American Public Health Association), American Water Works Association and Water Environment Federation (2005) Standard methods for the examination of water and wastewater. 21st edition. American Public Health Association, Washington, DC.
- Appenzeller, B.M.R., Batté, M., Mathieu, L., Block, J.C., Lahoussine, V., Cavard, J. and Gatel, D. (2001) Effect of adding phosphate to drinking water on bacterial growth in slightly and highly corroded pipes. *Water Res.*, 35(4): 1100–1105.
- ASTM (1996) ASTM annual book of standards. Vols. 11.01 and 11.02. American Society for Testing and Materials, Philadelphia, PA.
- Atlas, D., Coombs, J. and Zajcek, O.T. (1982) The corrosion of copper by chlorinated drinking waters. *Water Res.*, 16: 693–698.
- AwwaRF (1990) Lead control strategies. AWWA Research Foundation and American Water Works Association, Denver, CO.
- AwwaRF (1994) Development of a pipe loop protocol for lead control. AWWA Research Foundation, Denver, CO.
- AwwaRF (2004) Post optimization lead and copper control monitoring strategies. Report 90996F. AWWA Research Foundation, Denver, CO.
- AwwaRF (2007) Performance and metal release of non-lead brass meters, components, and fittings. Report 91174. AWWA Research Foundation, Denver, CO.
- Bailey, R.J and Russell, P.F (1981) Predicting drinking water lead levels. *Science and Technology Letter*, 2: 57-66.
- Bailey, R.J, Holmes D., Jolly, P.K. and Lacey, R.F. (1986) Lead concentration and stagnation time in water drawn through lead domestic pipes. Water Research Centre (Wrc) Environment Report TR 243.
- Bancroft, D.A. (1988) Corrosion control program in Danvers, Massachusetts. *J. N. Engl. Water Works Assoc.*, 102(3): 163–171.
- Baron, J. (1997) La mesure du plomb au robinet de l'utilisateur. Etude des méthodes d'échantillonnage. *TSM* (5): 47-53.
- Baron, J. (2001) Monitoring strategy for lead in drinking water at consumer's tap: field experiments in France. *Water Science and Technology: Water supply* 1(4):193-200.
- Becker, A. (2002) The effect of corrosion inhibitors in drinking water installations of copper. *Mater. Corros.*, 53: 560–567.
- Beckett, M.A., Snoeyink, V.L. and Jim, K. (1998) A pipe loop system for evaluating iron uptake in distribution systems. In: Proceedings of the 1998 American Water Works Association Water Quality Technology Conference, San Diego, CA. American Water Works Association, Denver, CO.
- Benard, I. (1998) Évaluation de l'effet du silicate comme inhibiteur de corrosion dans un réseau de distribution de l'eau potable. École polytechnique de Montréal, Montreal, Quebec (Master's thesis).
- Benjamin, M.M., Sontheimer, H. and Leroy, P. (1996) Corrosion of iron and steel. In: Internal corrosion of water distribution systems. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. p. 46.

-
- Berend, K. and Trouwborst, T. (1999) Cement-mortar pipes as a source of aluminum. *J. Am. Water Works Assoc.*, 91(7): 91–100.
- Berghult, B., Hedberg, T. and Broo, A.E. (1999) Drinking water distribution: Corrosion control in Swedish municipalities. *J. Water Supply Res. Technol. – Aqua*, 48(2): 44–52.
- Berghult, B., Broo, A.E. and Hedberg, T. (2001) Corrosion control measures in Sweden and the effect of succession order. *Water Sci. Technol. Water Supply*, 1(3): 47–58.
- Birden, H.H., Calabrese, E.J. and Stoddard, A. (1985) Lead dissolution from soldered joints. *J. Am. Water Works Assoc.*, 77(11): 66–70.
- Boffardi, B.P. (1988) Lead in drinking water — causes and cures. *Public Works*, 119(11): 67–70.
- Boffardi, B.P. (1990) Minimization of lead corrosion in drinking water. *Mater. Perform.*, 29(8): 45–49.
- Boffardi, B.P. (1993) The chemistry of polyphosphate. *Mater. Perform.*, 8: 50–53.
- Boffardi, B.P. and Sherbondy, A.M. (1991) Control of lead corrosion by chemical treatment. *Corrosion*, 47(12): 966–975.
- Boireau, A., Benezet-Toulze, M., Randon, G. and Cavard, J. (1997) Limitation de la solubilisation du plomb par ajout de produit filmogène. Transposition d’une étude sur pilote à un réseaux réel. *Tech. Sci. Méth. Génie Urbain Génie Rural*, 92(5): 63–72.
- Bondietti, G., Sinniger, J. and Stumm, W. (1993) The reactivity of Fe(III) (hydr)oxides: Effects of ligands in inhibiting the dissolution. *Colloids Surfaces A: Physicochem. Eng. Aspects*, 79(2–3): 157.
- Boulay, N. and Edwards, M. (2001) Role of temperature, chlorine, and organic matter in copper corrosion by-product release in soft water. *Water Res.*, 35(3): 683–690.
- Boyd, G.R., Pierson, G.L., Kirmeyer, G.J., Britton, M.D., and English, R.J (2007) Lead release from end-use plumbing components in Seattle public schools. In: *Proceedings of the 2007 American Water Works Association Distribution Research Symposium*, Reno Nevada. American Water Works Association, Denver, CO.
- Boyd, G.R., Pierson, G.L., Kirmeyer, G.J. and English, R.J (2008a) Lead variability testing in Seattle Public Schools. *J. Am. Water Works Assoc.*, 100(2): 53–64.
- Boyd, G.R., Pierson, G.L., Kirmeyer, G.J., Britton, M.D., and English, R.J (2008b) Lead release from new end-use plumbing components in Seattle Public Schools. *J. Am. Water Works Assoc.*, 100:3: 105-114.
- Britton, A. and Richards, W.N. (1981) Factors influencing plumbosolvency in Scotland. *J. Inst. Water Eng. Sci.*, 35(4): 349–364.
- Broo, A.E., Berghult, B. and Hedberg, T. (1997) Copper corrosion in drinking water distribution systems — The influence of water quality. *Corros. Sci.*, 39(6): 1119–1132.
- Broo, A.E., Berghult, B. and Hedberg, T. (1998) Copper corrosion in water distribution systems — The influence of natural organic matter (NOM) on the solubility of copper corrosion products. *Corros. Sci.*, 40(9): 1479–1489.
- Broo, A.E., Berghult, B. and Hedberg, T. (1999) Drinking water distribution — The effect of natural organic matter (NOM) on the corrosion of iron and copper. *Water Sci. Technol.*, 40(9): 17–24.
- Broo, A.E., Berghult, B. and Hedberg, T. (2001) Drinking water distribution — Improvements of the surface complexation model for iron corrosion. *Water Sci. Technol. Water Supply*, 1(3): 11–18.
-

-
- Bryant, S.D. (2004) Lead contaminated drinking waters in the public schools of Philadelphia. *J of Toxic.*, 42(3): 287-294.
- Campbell, A. and Douglas, I. (2007) Corrosion control in Ottawa. In: Proceedings of the Ontario Water Works Association Distribution System Workshop, Toronto, ON. Ontario Water Works Association, Markham, ON.
- Campbell, H.S. (1954a) The influence of the composition of supply waters, especially of traces of natural inhibitor on pitting corrosion of copper water pipes. *Proc. Soc. Water Treat. Exam.*, 3: 100–117.
- Campbell, H.S. (1954b) A natural inhibitor of pitting corrosion of copper in tap waters. *J. Appl. Chem.*, 4: 1954.
- Campbell, H.S. (1971) Corrosion, water composition and water treatment. *Proc. Soc. Water Treat. Exam.*, 20: 11–34.
- Campbell, H.S. and Turner, M.E.D. (1983) The influence of trace organics on scale formation and corrosion. *J. Inst. Water Eng. Sci.*, 37(1): 55–72.
- Cantor, A.F., Denig-Chakroff, D., Vela, R.R., Oleinik, M.G. and Lynch, D.L. (2000) Use of polyphosphate in corrosion control. *J. Am. Water Works Assoc.*, 92(2): 95–102.
- Cantor, A.F., Park, J.K. and Vaiyavatjamai, P. (2003) Effect of chlorine on corrosion. *J. Am. Water Works Assoc.*, 95(5): 112–123.
- Churchill, D.M., Mavinic, D.S., Neden, D.G. and MacQuarrie, D.M. (2000) The effect of zinc orthophosphate and pH–alkalinity adjustment on metal levels leached into drinking water. *Can. J. Civil Eng.*, 27(6): 33–43.
- Colling, J.H., Whincup, P.A.E. and Hayes, C.R. (1987) The measurement of plumbosolvency propensity to guide the control of lead in tapwaters. *J. Inst. Water Environ. Manage.*, 1(3): 263–269.
- Colling, J.H., Croll, B.T., Whincup, P.A.E. and Harward, C. (1992) Plumbosolvency effects and control in hard waters. *J. Inst. Water Environ. Manage.*, 6(6): 259–269.
- Conroy, P.J. (1991) Deterioration of water quality in distribution systems — the effects of water quality arising from *in situ* cement lining (APP 9770). Water Research Centre, Swindon, Wiltshire, U.K. (Report No. DoE 2435-SW (P)).
- Conroy, P.J., Kings, K., Olliffe, T., Kennedy, G. and Blois, S. (1994) Durability and environmental impact of cement mortar linings. Water Research Centre, Swindon, Wiltshire, U.K. (Report No. FR 0473).
- Cordonnier, J. (1997) Protection des réseaux de distribution par les inhibiteurs de corrosion. Choix et optimisation. *Tech. Sci. Méth. Génie Urbain Génie Rural*, 92(5): 75–82.
- Craik, S., Gammie, L., Gao, M., Melnychuk, P. and Bruineman, C. (2008) Lead at customer’s taps results of the 2007 sampling program. Final report by EPCOR Water services, Quality Assurance.
- De Mora, S.J. and Harrison, R.M. (1984) Lead in tap water: Contamination and chemistry. *Chem. Br.*, 20(10): 900–904.
- Dodrill, D.M. and Edwards, M. (1995) Corrosion control on the basis of utility experience. *J. Am. Water Works Assoc.*, 87(7): 74–85.
- Douglas, B.D. and Merrill, D.T. (1991) Control of water quality deterioration caused by corrosion of cement-mortar pipe linings. AWWA Research Foundation, American Water Works Association, Denver, CO.
- Douglas, B.D., Merrill, D.T. and Caitlin, J.O. (1996) Water quality deterioration from corrosion of cement-mortar linings. *J. Am. Water Works Assoc.*, 88(7): 99–107.
-

-
- Douglas, I., Guthmann, J., Muylwyk Q. and Snoeyink, V. (2004) Corrosion control in the City of Ottawa — Comparison of alternatives and case study for lead reduction in drinking water. In: Robertson, W. and Brooks, T. (Ed.). 11th Canadian National Drinking Water Conference and Second Policy Forum. Calgary, Alberta, Canada. April 3 - 6.
- Douglas, I., Lemieux, F. and Weir, D. (2007) Testing the Waters: Putting Canada's New Corrosion Control Guideline into Practice. In: Proceedings of the 2007 American Water Works Association Research Symposium "Distribution Systems: The Next Frontier", Reno, NV. March 2-3. American Water Works Association, Denver, CO." .
- Dudi, A. and Edwards, M. (2004) Galvanic corrosion of lead bearing plumbing devices. In: Reconsidering lead corrosion in drinking water: Product testing, direct chloramine attack and galvanic corrosion. Faculty of the Virginia Polytechnic Institute and State University, Blacksburg, VA. Dudi, A. (Masters' Thesis). pp. 69-105.
- Dudi, A., Schock, M.R., Nestor, M. and Edwards, M. (2004) Lead leaching from in-line brass devices: A critical evaluation of the existing standard. In: Reconsidering lead corrosion in drinking water: Product testing, direct chloramine attack and galvanic corrosion. Faculty of the Virginia Polytechnic Institute and State University, Blacksburg, VA. Dudi, A. (Masters' Thesis). pp. 37-68.
- Edwards, M. and Dudi, A. (2004) Role of chlorine and chloramine in corrosion of lead-bearing plumbing materials. *J. Am. Water Works Assoc.*, 96(10): 69–81.
- Edwards, M. and Ferguson, J.F. (1993) Accelerated testing of copper corrosion. *J. Am. Water Works Assoc.*, 85(10): 105–113.
- Edwards, M. and McNeill, L.S. (2002) Effect of phosphate inhibitors on lead release from pipes. *J. Am. Water Works Assoc.*, 94(1): 79–90.
- Edwards, M. and Sprague, N. (2001) Organic matter and copper corrosion by-product release: A mechanistic study. *Corros. Sci.*, 43(1): 1–18.
- Edwards, M. and Triantafyllidou, S. (2007). Chloride-to-sulfate mass ratio and lead leaching to water. *J. Am. Water Works Assoc.*, 99(7): 96–109.
- Edwards, M., Ferguson, J.F. and Reiber, S.H. (1994a) The pitting corrosion of copper. *J. Am. Water Works Assoc.*, 86(7): 74–90.
- Edwards, M., Meyer, T.E. and Rehring, J.P. (1994b) Effect of selected anions on copper corrosion rates. *J. Am. Water Works Assoc.*, 86(12): 73–81.
- Edwards, M., Schock, M.R. and Meyer, T.E. (1996) Alkalinity, pH, and copper corrosion by-product release. *J. Am. Water Works Assoc.*, 88(3): 81–94.
- Edwards, M., Jacobs, S. and Dodrill, D.M. (1999) Desktop guidance for mitigating Pb and Cu corrosion by-products. *J. Am. Water Works Assoc.*, 91(5): 66–77.
- Edwards, M., Powers, K., Hidmi, L. and Schock, M.R. (2001) The role of pipe ageing in copper corrosion by-product release. *Water Sci. Technol. Water Supply*, 1(3): 25–32.
- Edwards, M., Hidmi, L. and Gladwell, D. (2002) Phosphate inhibition of soluble copper corrosion by-product release. *Corros. Sci.*, 44(5): 1057–1071.
- Eisnor, J.D. and Gagnon, G.A. (2003) A framework for the implementation and design of pilot-scale distribution systems. *J. Water Supply Res. Technol. – Aqua*, 57(7): 501–520.

Emde, K.M.E., Smith, D.W. and Facey, R.M. (1992) Initial investigation of microbially influenced corrosion (MIC) in a low temperature water distribution system. *Water Res.*, 26(2): 169–175.

European Commission (1999) Developing a new protocol for the monitoring of lead in drinking water. Directorate General for Science, Research and Development (Report No. REPORT EUR 19087 EN).

Facey, R.M. and Smith, D.W. (1995) Soft, low-temperature water-distribution corrosion: Yellowknife, NWT. *J. Cold Reg. Eng.*, 9(1): 23–40.

Feigenbaum, C., Gal-Or, L. and Yahalom, J. (1978) Scale protection criteria in natural waters. *Corrosion*, 34(4): 133.

Ferguson, J.F., Franqué, O.V. and Schock, M.R. (1996) Corrosion of copper in potable water systems. In: *Internal corrosion of water distribution systems*. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 231–268.

Flournoy, R.L., Monroe, D., Chestnut, N. and Kumar, V. (1999) Health effects from vinyl chloride monomer leaching from pre-1997 PVC pipe. In: *Proceedings of the 1999 AWWA National Conference*, Chicago, IL. American Water Works Association, Denver, CO. pp. 1–20 (Paper Tu22-4).

Frature, I., Deslouis C., Kiene, L., Levi, Y. and Tribollet, B. (1999) Free chlorine consumption induced by cast iron corrosion in drinking water distribution systems. *Water Res.*, 33(8): 1781–1790.

Frey, M. The AWWA lead information survey: a final report. *J. Am. Water Works Assoc.*, 81(9): 64–68.

Gardels, M.C. and Thomas, J.S. (1989) A laboratory study of the leaching of lead from water faucets. *J. Am. Water Works Assoc.*, 81(7): 101–113.

Gnaedinger, R.H. (1993) Lead in school drinking water. *J of Environ. Health*, 55(6):15-18.

Gregory, R. (1990) Galvanic corrosion of lead solder in copper pipework. *J. Inst. Water Environ. Manage.*, 4(2): 112–118.

Hatch, G.B. (1969) Polyphosphate inhibitors in potable water. *Mater. Prot.*, 8(11): 31–35.

Hedberg, T. and Johansson, E. (1987) Protection of pipes against corrosion. *Water Supply*, 5(3/4): SS20-1 – SS20-7.

Hidmi, L. and Edwards, M. (1999) Role of temperature and pH in $\text{Cu}(\text{OH})_2$ solubility. *Environ. Sci. Technol.*, 33(15): 2607–2610.

Holm, T.R. and Schock, M.R. (1991) Potential effects of polyphosphate products on lead solubility in plumbing systems. *J. Am. Water Works Assoc.*, 83(7): 76–82.

Holm, T.R., Smothers, S.H., Xiaofeng, Z. and Schock, M.R. (1989) Polyphosphate water-treatment products: Their effects on the chemistry and solubility of lead in potable water systems. In: *Proceedings of the 1989 American Water Works Association Water Quality Technology Conference*, Philadelphia, PA. American Water Works Association, Denver, CO.

Holtschulte, H. and Schock, M.R. (1985) Asbestos–cement and cement-mortar-lined pipes. In: *Internal corrosion of water distribution systems*. AWWA Research Foundation and DVGW Engler Bunte Institute, Denver, CO. pp. 417–512.

Hong, P.K.A. and Macauley, Y. (1998) Corrosion and leaching of copper tubing exposed to chlorinated drinking water. *Water Air Soil Pollut.*, 108(3–4): 457–471.

-
- Horsley, M.B., Northup, B.W., O'Brien, W.J. and Harms, L.L. (1998) Minimizing iron corrosion in lime softened water. In: Proceedings of the 1998 American Water Works Association Water Quality Technology Conference, San Diego, CA. American Water Works Association, Denver, CO.
- Hoyt, B.P., Kirmeyer, G.J. and Courchene, J.E. (1979) Evaluating home plumbing corrosion problems. *J. Am. Water Works Assoc.*, 71(12): 720.
- Huggins, D. (2007) City of London lead testing and remediation programs. In: Proceedings of the Ontario Water Works Association Distribution System Workshop, Toronto, ON. Ontario Water Works Association, Markham, ON.
- Hulsmann, A.D. (1990) Particulate lead in water supplies. *J. Inst. Water Environ. Manage.*, 4: 19–25.
- InfraGuide (2001) Developing a water distribution system renewal plan. A best practice report published by the National Guide to Sustainable Municipal Infrastructure, Ottawa, Ontario (<http://www.infraguide.ca>).
- Johnson, B., Yorton, R., Tran, T. and Kim, J. (1993) Evaluation of corrosion control alternatives to meet the Lead and Copper Rule for eastern Massachusetts. *J. N. Engl. Water Works Assoc.*, 107(3): 24–45.
- Karalekas, P.C., Ryan, C.R., Larson, C.D., and Taylor, F.B. (1978) Alternative methods for controlling the corrosion of lead pipes. *J. N. Engl. Water Works Assoc.*, 92(2): 159-178.
- Karalekas, P.C., Ryan, C.R. and Taylor, F.B. (1983) Control of lead, copper, and iron pipe corrosion in Boston. *J. Am. Water Works Assoc.*, 75(2): 92–95.
- Kashinkunti, R.D., Metz, D.H., Hartman, D.J. and DeMarco, J. (1999) How to reduce lead corrosion without increasing iron release in the distribution system. In: Proceedings of the 1999 American Water Works Association Water Quality Technology Conference, Tampa Bay, FL. American Water Works Association, Denver, CO.
- Katsanis, E.P., Esmonde, W.B. and Spencer, R.W. (1986) Soluble silicate corrosion inhibitors in water systems. *Mater. Perform.*, 25: 19–25.
- Kimbrough, D.E. (2001) Brass corrosion and the LCR monitoring program. *J. Am. Water Works Assoc.*, 93(2): 81–91.
- Kirmeyer, G., Murphy, B., Sandvig, A., Korshin, G., Shaha, B., Fabbicino, M. and Burlingame, G. (2004) Post-optimization lead and copper control monitoring strategies. Awwa Research Foundation, Denver, CO.
- Korshin, G.V., Pery, S.A.L. and Ferguson, J.F. (1996) Influence of NOM on copper corrosion. *J. Am. Water Works Assoc.*, 88(7): 36–47.
- Kuch, A. and Wagner, I. (1983) A mass transfer model to describe lead concentrations in drinking water. *Water Supply*, 17(10): 1330–1307.
- Kwan, P. (2007) Lead in water: release before and after a lead service line replacement. In: Proceedings of the Ontario Water Works Association Distribution System Workshop, Toronto, ON. Ontario Water Works Association, Markham, ON.
- Larson, T.E. (1966) Chemical corrosion control. *J. Am. Water Works Assoc.*, 49(12): 1581.
- Larson, T.E. and Skold, R.V. (1958) Current research on corrosion and tuberculation of cast iron. *J. Am. Water Works Assoc.*, 50(11): 1429–1432.
- LeChevallier, M.W., Babcock, T.M. and Lee, R.G. (1987) Examination and characterization of distribution system biofilms. *Appl. Environ. Microbiol.*, 53(12): 2714–2724.

-
- LeChevallier, M.W., Cawthon, C.D. and Lee, R.G. (1988) Inactivation of biofilm bacteria. *Appl. Environ. Microbiol.*, 54: 2492–2499.
- LeChevallier, M.W., Lowry, C.D., Lee, R.G. and Gibbon, D.L. (1993) Examining the relationship between iron corrosion and the disinfection of biofilm bacteria. *J. Am. Water Works Assoc.*, 87(7): 111–123.
- LeChevallier, M.W., Welch, N.J. and Smith, D.B. (1996) Full-scale studies of factors related to coliform regrowth in drinking water. *Appl. Environ. Microbiol.*, 62(7): 2201–2211.
- Lee, R.G., Becker, W.C. and Collins, D.W. (1989) Lead at the tap: Sources and control. *J. Am. Water Works Assoc.*, 81(7): 52–62.
- Lehrman, L. and Shuldener, H.L. (1951) The role of sodium silicate in inhibiting corrosion by film formation on water piping. *J. Am. Water Works Assoc.*, 43(3): 175–188.
- Leroy, P. (1993) Lead in drinking water — Origins; solubility; treatment. *J. Water Supply Res. Technol. – Aqua*, 42(4): 223–238.
- Leroy, P., Schock, M.R., Wagner, I. and Holtschulte, H. (1996) Cement-based materials. In: *Internal corrosion of water distribution systems*. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 313–388.
- Lin, N.-H., Torrents, A., Davis, A.P. and Zeinali, M. (1997) Lead corrosion control from lead, copper–lead solder, and brass coupons in drinking water employing free and combined chlorine. *J. Environ. Sci. Health A*, 32(4): 865–884.
- Loschiavo, G.P. (1948) Experiences in conditioning corrosive army water supplies in New England. *Corrosion*, 4(1): 1–14.
- Lyon, T.D.B. and Lenihan, M.A. (1977) Corrosion in solder jointed copper tubes resulting in lead contamination of drinking water. *Br. Corros. J.*, 12(1): 41–45.
- Lyons, J.J., Pontes, J. and Karalekas, P.C. (1995) Optimizing corrosion for lead and copper using phosphoric acid and sodium hydroxide. In: *Proceedings of the 1995 American Water Works Association Water Quality Technology Conference*, New Orleans, LA. American Water Works Association, Denver, CO.
- Lytle, D.A. and Schock, M.R. (2000) Impact of stagnation time on metal dissolution from plumbing materials in drinking water. *J. Water Supply Res. Technol. – Aqua*, 49(5): 243–257.
- Lytle, D.A. and Schock, M.R. (2005) Formation of Pb(IV) oxides in chlorinated water. *J. Am. Water Works Assoc.*, 97(11): 102–114.
- Lytle, D.A. and Snoeyink, V.L. (2002) Effect of ortho- and polyphosphate on the properties of iron particles and suspensions. *J. Am. Water Works Assoc.*, 94(10): 87–99.
- Lytle, D.A., Schock, M.R., Dues, N.R. and Clark, P.J. (1993) Investigating the preferential dissolution of lead from solder particulates. *J. Am. Water Works Assoc.*, 85(7): 104–110.
- Lytle, D.A., Sarin, P. and Snoeyink, V.L. (2003) The effect of chloride and orthophosphate on the release of iron from a drinking water distribution system cast iron pipe. In: *Proceedings of the 2003 American Water Works Association Water Quality Technology Conference*, Philadelphia, PA. American Water Works Association, Denver, CO.
- Lytle, D.A., Sorg, T.J. and Frietch, C. (2004) Accumulation of arsenic in drinking water distribution systems. *Environ. Sci. Technol.*, 38(20): 5365–5372.

-
- Maas, R.P., Patch, S.C., Kucken, D.J. and Peek, B.T. (1991) A multi-state study of the effectiveness of various corrosion inhibitors in reducing residential lead levels. In: Proceedings of the 1991 American Water Works Association Annual Conference, Philadelphia, PA. American Water Works Association, Denver, CO.
- Maas, R.P., Patch, S.C., and Gagnon, A.M. (1994) The dynamics of lead in drinking water in U.S. workplaces and schools. *J. Am. Ind. Hyg. Assoc.*, 55: 829-832
- MacQuarrie, D.M., Mavinic, D.S. and Neden, D.G. (1997) Greater Vancouver Water District drinking water corrosion inhibitor testing. *Can. J. Civil Eng.*, 24(1): 34–52.
- Maddison, L.A. and Gagnon, G.A. (1999) Evaluating corrosion control strategies for a pilot scale distribution system. In: Proceedings of the 1999 American Water Works Association Water Quality Technology Conference, Tampa Bay, FL.
- McCauley, R.F. (1960) Use of polyphosphate for developing protective calcite. *J. Am. Water Works Assoc.*, 52(6): 721.
- McNeill, L.S. and Edwards, M. (2001) Iron pipe corrosion in distribution systems. *J. Am. Water Works Assoc.*, 93(7): 88–100.
- McNeill, L.S. and Edwards, M. (2002) Phosphate inhibitor use at U.S. utilities. *J. Am. Water Works Assoc.*, 94(7): 57–63.
- Méranger, J.C., Subramanian, K.S. and Chalifoux, C. (1981) Survey for cadmium, cobalt, chromium, copper, nickel, lead, zinc, calcium, and magnesium in Canadian drinking water supplies. *J. Assoc. Off. Anal. Chem.*, 64(1): 44–53.
- Merill, D.T. and Sanks, R.L. (1978) Corrosion control by deposition of CaCO₃ films. Part 3. A practical approach for plant operators. *J. Am. Water Works Assoc.*, 70(1): 12.
- Murphy, E.A. (1993) Effectiveness of flushing on reducing lead and copper levels in school drinking water. *Environ. Health Perspect.*, 101(3): 240–241.
- NACE International (2000) NACE International glossary of corrosion-related terms. National Association of Corrosion Engineers International, Houston, TX (Item No. 26012).
- Neff, C.H., Schock, M.R. and Marden, J. (1987) Relationships between water quality and corrosion of plumbing materials in buildings. Vol. 1. Galvanized steel and copper plumbing systems. U.S. Environmental Protection Agency, Washington, DC (Report No. EPA/600/2-87/036A).
- Neuman, W.E. (1995) AWWC experience with zinc orthophosphate treatment. *J. N. Engl. Water Works Assoc.*, 109: 57–60.
- Nielsen, K. (1983) Control of metal contaminants in drinking water in Denmark. *J. Water Supply Res. Technol. – Aqua*, 32(4): 173–182.
- Nielsen, K. and Andersen, A. (2001) Metal release from domestic water installations. In: Proceedings of the 6th International CEOCOR Congress, Giardini/Naxos, Italy. Committee on the Study of Pipe Protection and Corrosion, Brussels.
- NRCC (2005) National Plumbing Code. National Research Council of Canada, Ottawa, Ontario.
- NSF International (2005) NSF/ANSI Standard 60: Drinking water treatment additives — health effects. Ann Arbor, MI. p. 27.
- NSF International (2006) Web page (<http://www.nsf.org>).

NSF International (2007) NSF/ANSI Standard 61: Drinking water treatment components — health effects. Ann Arbor, MI.

Oliphant, R.J. (1983a) Lead contamination of potable water arising from soldered joints. *Water Supply*, 1(2/3): SS 18-5 – SS 18-9.

Oliphant, R.J. (1983b) Summary report on the contamination of potable water by lead from soldered joints. WRC Engineering, Swindon, Wiltshire, U.K. (Report No. ER 125E).

Oliphant, R.J. (1993) Changing perception of the significance of potential sources of lead contamination in domestic water systems. *Water Supply*, 11(3/4): 339–412.

Peters, N.J., Davidson, C.M., Britton, A. and Robertson, S.J. (1999) The nature of corrosion products in lead pipes used to supply drinking water to the City of Glasgow, Scotland, UK. *Fresenius J. Anal. Chem.*, 363(5/6): 562–565.

Pinney, K., Craik, S., Gamal El-Din, M., Kindzierski, W., Gammie, L., Emde, K., and Westergard, J. (2007) Opportunities for improving drinking water quality in large buildings. In: *Proceedings of the Western Canada Water and Wastewater Association Annual Conference*, Edmonton, AB. Western Canada Water and Wastewater Association, Calgary, AB.

Pisigan, R.A. and Singley, J.E. (1987) Influence of buffer capacity, chlorine residual, and flow rate on corrosion of mild steel and copper. *J. Am. Water Works Assoc.*, 79(2): 62–70.

Reda, M.R. and Alhajji, J.N. (1996) Role of solution chemistry on corrosion of copper in tap water: Effect of sulfate ion concentration on uniform and localized attack. *Corrosion*, 52(2): 232–239.

Rehring, J.P. and Edwards, M. (1996) Copper corrosion in potable water systems: Impacts of natural organic matter and water treatment processes. *Corrosion*, 52(4): 301–317.

Reiber, S.H. (1987) Corrosion monitoring and control in the Pacific Northwest. *J. Am. Water Works Assoc.*, 71(2): 71–74.

Reiber, S.H. (1989) Copper plumbing surfaces: An electrochemical study. *J. Am. Water Works Assoc.*, 87(7): 114.

Reiber, S.H. (1991) Galvanic stimulation of corrosion on lead–tin soldered-sweated joints. *J. Am. Water Works Assoc.*, 83(7): 83–91.

Reiber, S.H. and Dostal, G. (2000) Well water disinfection sparks surprises. *Opflow*, 26(3): 1, 4–6, 14.

Reiber, S.H., Ryder, R.A. and Wagner, I. (1996) Corrosion assessment technologies. In: *Internal corrosion of water distribution systems*. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 445–486.

Renner, R. (2004) Leading to lead. *Sci. Am.*, 291(1): 22, 24.

Renner, R. (2006) Lead in water linked to coagulant. *Environ. Sci. Technol.*, 40(17): 5164–5165.

Renner, R. (2007) Lead water pipe replacement should go all the way. *Environ. Sci. Technol. Online News* 05-09-2007 http://pubs.acs.org/subscribe/journals/esthag-w/2007/sept/science/rr_leadreplace.html

Rezania, L.W. and Anderl, W.H. (1995) Copper corrosion and iron removal plants. The Minnesota experience. In: *Proceedings of the 1995 American Water Works Association Water Quality Technology Conference*, New Orleans, LA. American Water Works Association, Denver, CO.

-
- Rezania, L.W. and Anderl, W.H. (1997) Corrosion control for high DIC groundwater phosphate or bust. In: Proceedings of the 1997 American Water Works Association Annual Conference, Atlanta, GA. American Water Works Association, Denver, CO.
- Sadiki, A. and Williams, D.T. (1999) A study on organotin levels in Canadian drinking water distributed through PVC pipes. *Chemosphere*, 38(7): 1541–1548.
- Sandvig, A. (2006) Field evaluation of the impact of faucet replacement on lead levels measured at the tap. In: Proceedings of the 2007 American Water Works Association Distribution Research Symposium, Reno Nevada. American Water Works Association, Denver, CO.
- Samuels, E.R. and Méranter, J.C. (1984) Preliminary studies on the leaching of some trace metals from kitchen faucets. *Water Res.*, 18(1): 75–80.
- Sarin, P., Bebee, J., Becket, M.A., Jim, K.K., Lytle, D.A., Clement, J.A., Kriven, W.M. and Snoeyink, V.L. (2000) Mechanism of release of iron from corroded iron/steel pipes in water distribution systems. In: Proceedings of the 2000 American Water Works Association Annual Conference, Denver, CO. American Water Works Association, Denver, CO.
- Sarin, P., Clement, J.A., Snoeyink, V.L. and Kriven, W.M. (2003) Iron release from corroded, unlined cast-iron pipe. *J. Am. Water Works Assoc.*, 95(11): 85–96.
- Sathyanarayana, S., Beaudet, N., Omri, K., and Karr, K. (2006) Predicting children's blood lead levels from exposure to school drinking water in Seattle, Washington, USA. *Ambulatory Pediatrics*, 6(5):288-292.
- Schock, M.R. (1980) Response of lead solubility to dissolved carbonate in drinking water. *J. Am. Water Works Assoc.*, 72(12): 695–704.
- Schock, M.R. (1989) Understanding corrosion control strategies for lead. *J. Am. Water Works Assoc.*, 81(7): 88–100.
- Schock, M.R. (1990a) Causes of temporal variability of lead in domestic plumbing systems. *Environ. Monit. Assess.*, 15(1): 59–82.
- Schock, M.R. (1990b) Internal corrosion and deposition control. In: *AWWA water quality and treatment: A handbook of community water supplies*. McGraw-Hill, Inc., New York, NY (for the American Water Works Association).
- Schock, M.R. (2005) Distribution systems as reservoirs and reactors for inorganic contaminants. In: *Distribution system water quality challenges in the 21st century: A strategic guide*. American Water Works Assoc., Denver, CO.
- Schock, M.R. and Clement, J.A. (1998) Lead and copper control with non-zinc orthophosphate. *J. N. Engl. Water Works Assoc.*, 112(1): 20–33.
- Schock, M.R. and Fox, J.C. (2001) Solving copper corrosion problems while maintaining lead control in a high alkalinity water using orthophosphate. In: Proceedings of the 2001 American Water Works Association Annual Conference, Washington, DC. American Water Works Association, Denver, CO.
- Schock, M.R. and Gardels, M.C. (1983) Plumbosolvency reduction by high pH and low carbonate–solubility relationships. *J. Am. Water Works Assoc.*, 75(2): 87–91.
- Schock, M.R. and Giani, R. (2004) Oxidant/disinfectant chemistry and impacts on lead corrosion. In: Proceedings of the 2004 American Water Works Association Water Quality Technology Conference, San Antonio, TX. American Water Works Association, Denver, CO.
- Schock, M.R. and Neff, C.H. (1988) Trace metal contamination from brass fittings. *J. Am. Water Works Assoc.*, 80(11): 47–56.

-
- Schock, M.R., Lytle, D.A. and Clement, J.A. (1995) Effect of pH, DIC, orthophosphate, and sulfate on drinking water cuprosolvency. U.S. Environmental Protection Agency, Cincinnati, OH (Report No. EPA/600/R-95/085).
- Schock, M.R., Wagner, I. and Oliphant, R.J. (1996) Corrosion and solubility of lead in drinking water. In: Internal corrosion of water distribution systems. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 131–230.
- Schock, M.R., Harmon, S.M., Swertfeger, J. and Lohmann, R. (2001) Tetravalent lead: A hitherto unrecognized control of tap water lead contamination. In: Proceedings of the 2001 American Water Works Association Water Quality Technology Conference, Nashville, TN. American Water Works Association, Denver, CO.
- Schock, M.R., Lytle, D.A., Sandvig, A.M., Clement, J.A. and Harmon, S.M. (2005a) Replacing polyphosphate with silicate to solve lead, copper, and source water iron problems. *J. Am. Water Works Assoc.*, 97(11): 84–93.
- Schock, M.R., Scheckel, K., DeSantis, M. and Gerke, T. (2005b) Mode of occurrence, treatment, and monitoring significance of tetravalent lead. In: Proceedings of the 2005 American Water Works Association Water Quality Technology Conference, Quebec, QC. American Water Works Association, Denver, CO.
- Seattle Public Schools (2005). Water quality remediation plan: Results of special lead sampling at Decatur (AE II) School. Available at <http://www.seattleschools.org/area/ehs/drinkingwater/HDR/AttachmentE.pdf>.
- Sharrett, A.R., Carter, A.P., Orheim, R.M. and Feinleib, M. (1982) Daily intake of lead, cadmium, copper, and zinc from drinking water: The Seattle study of trace metal exposure. *Environ. Res.*, 28: 456–475.
- Sheiham, I. and Jackson, P.J. (1981) The scientific basis for control of lead in drinking water by water treatment. *J. Inst. Water Eng. Sci.*, 35(6): 491–515.
- Shuldener, H.L. and Sussman, S. (1960) Silicate as a corrosion inhibitor in water systems. *Corrosion*, 16: 354–358.
- Shull, K.E. (1980) An experimental approach to corrosion control. *J. Am. Water Works Assoc.*, 72(5): 280–285.
- Singh, I. and Mavinic, D.S. (1991) Significance of building and plumbing specifics on trace metal concentrations in drinking water. *Can. J. Civil Eng.*, 18(6): 893–903.
- Singley, J.E. (1994) Electrochemical nature of lead contamination. *J. Am. Water Works Assoc.*, 86(7): 91–96.
- Snoeyink, V.L. and Wagner, I. (1996) Principles of corrosion of water distribution systems. In: Internal corrosion of water distribution systems. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 1–28.
- Sontheimer, H., Kollo, W. and Snoeyink, V.L. (1981) The siderite model of the formation of corrosion-resistant scales. *J. Am. Water Works Assoc.*, 71(11): 572–579.
- Sorg, T.J., Schock, M.R. and Lytle, D.A. (1999) Ion exchange softening: Effects on metal concentrations. *J. Am. Water Works Assoc.*, 91(8): 85–97.
- Stericker, W. (1938) Sodium silicates in water to prevent corrosion. *Ind. Eng. Chem.*, 30(3): 348–351.
- Stericker, W. (1945) Protection of small water systems from corrosion. *Ind. Eng. Chem.*, 37(8): 716–720.
- Stumm, W. (1960) Investigation on the corrosive behavior of waters. *J. Sanit. Eng. Div. Proc. Am. Soc. Civil Eng.*, 86: 27–45.
- Subramanian, K.S., Connor, J.W. and Méranter, J.C. (1991) Leaching of antimony, cadmium, lead, silver, tin, and zinc from copper piping with non-lead based solder joints. *J. Environ. Sci. Health*, 26(6): 911–928.

Switzer, J.A., Rajasekharan, V.V., Boonsalee, S., Kulp, E.A. and Bohannon, E.M.W. (2006) Evidence that monochloramine disinfectant could lead to elevated Pb levels in drinking water. *Environ. Sci. Technol.*, 40(10): 3384–3387.

Taylor, J.S. and Wiesner, M. (1999) Membranes. In: *AWWA water quality and treatment: A handbook of community water supplies*. McGraw-Hill, Inc., New York, NY (for the American Water Works Association).

Texter, C.R. (1923) The prevention of corrosion in hot water supply systems and boiler economizer tubes. *J. Am. Water Works Assoc.*, 10(9): 764–772.

Tresh, J.C. (1922) The action of natural waters on lead. *Analyst*, 47(560): 459–468, 500–505.

Treweek, G.P., Glicker, G., Chow, B. and Spinker, M. (1985) Pilot-plant simulation of corrosion in domestic pipe materials. *J. Am. Water Works Assoc.*, 77(10): 74–82.

Triantafyllidou, S., Parks, J. and Edwards, M. (2007). Lead particles in potable water. *J. Am. Water Works Assoc.*, 99(6):107–117.

Tuovinen, O.H., Button, K.S., Vuorinen, A., Carlson, L., Mair, D.M. and Yut, L.A. (1980) Bacterial, chemical, and mineralogical characteristics of tubercles in distribution pipelines. *J. Am. Water Works Assoc.*, 71(11): 626–635.

U.S. EPA (1990) Influence of plumbing, lead service lines and water treatment on lead levels at the tap: analysis of available data. U.S. Environmental Protection Agency, Office of Drinking Water, Washington, DC.

U.S. EPA (1991a) 40 CFR Parts 141 and 142, Maximum Contaminant Level Goals and National Primary Drinking Water Regulations for Lead and Copper; Final Rule. U.S. Environmental Protection Agency, Washington, DC.

U.S. EPA (1991b) Memorandum from Jeff Cohen to the record on required number of samples May, 6th, 1991. Office of Water, U.S. Environmental Protection Agency, Washington, DC.

U.S. EPA (1992) Lead and Copper Rule guidance manual. U.S. Environmental Protection Agency, Washington, DC (Report No. EPA/811/B-92/002).

U.S. EPA (1994a) Lead in drinking water in schools and non-residential buildings. Office of Water, U.S. Environmental Protection Agency, Washington, DC (Report No. EPA 812-B-94-002).

U.S. EPA (1994b) Methods for the determination of metals in environmental samples, Supplement 1. Office of Water, U.S. Environmental Protection Agency, Washington, DC (Report No. EPA/600/R-94/111).

U.S. EPA (2000) 40 CFR Parts 141 and 142, National Primary Drinking Water Regulations for Lead and Copper; Final Rule. U.S. Environmental Protection Agency, Washington, DC.

U.S. EPA (2003) Revised guidance manual for selecting lead and copper control strategies. U.S. Environmental Protection Agency, Washington, DC (Report No. EPA-816-R-03-001).

U.S. EPA (2004a) US EPA lead service line replacement workshop. October 26 - 27, 2004, Atlanta, GA. U.S. Environmental Protection Agency, Washington, DC.
http://www.epa.gov/safewater/lcrr/pdf/summary_lcmr_review_lead_line_replacement_workshop_10-26-04.pdf

U.S. EPA (2004b) Controlling lead in drinking water for schools and day care facilities: a summary of state programs: National report. U.S. Environmental Protection Agency, Office of Washington, DC (Report No. EPA-810-R-04-001).

U.S. EPA (2006a) Lead and Copper Rule state file review: National report. U.S. Environmental Protection Agency, Washington, DC (Report No. EPA-816-R-06-001).

U.S. EPA (2006b) 3Ts for reducing lead in drinking water in schools: revised technical guidance. United States Environmental Protection Agency, Washington, DC.

U.S. EPA (2007) Elevated lead in D.C. drinking water- a study of potential causative events, final summary report Office of Water, U.S.Environmental Protection Agency, Washington, DC (Report No. EPA 812-B-94-002).

U.S. EPA (2008) Case Study of School Program to Reduce Lead in Drinking Water Stoughton Public Schools Stoughton, MA. U.S. Environmental Protection Agency, Office of Washington, DC.
http://www.epa.gov/safewater/schools/casestudy_stoughtonschools.html

Van den Hoven, T., and Slaats, N. (2006) In: Analytical Methods for Drinking Water. John Wiley & Sons, Ltd., New York, NY.

Van Der Merwe, S.W. (1988) The effect of water quality variables on the corrosion behavior of water coagulated with a cationic polyelectrolyte and with lime/activated silica. *Water Supply*, 6(4): SS2.

Velveva, L. (1998) The corrosion performance of steel and reinforced concrete in a tropical humid climate. A review. *Corros. Rev.*, 16(3): 235.

Vik, E.A., Ryder, R.A., Wagner, I. and Ferguson, J.F. (1996) Mitigation of corrosion effects. In: *Internal corrosion of water distribution systems*. 2nd edition. AWWA Research Foundation and DVGW Technologiezentrum Wasser, Denver, CO. pp. 389–444.

Viraraghavan, T., Subramanian, K.S. and Rao, B.V. (1996) Drinking water at the tap: Impact of plumbing materials on water quality. *J. Environ. Sci. Health A*, 31(8): 2005–2016.

Volk, C., Dundore, E., Schiermann, J. and LeChevallier, M.W. (2000) Practical evaluation of iron corrosion control in a drinking water distribution system. *Water Res.*, 34(6): 1967–1974.

Williams, S.M. (1990) The use of sodium silicate and sodium polyphosphate to control water problems. *Water Supply*, 8: 195.

Wong, C.S. and Berrang, P. (1976) Contamination of tap water by lead pipe and solder. *Bull. Environ. Contam. Toxicol.*, 15(5): 530–534.